




Sika[®] MB Redline

FAST SETTING EPOXY MOISTURE BARRIER

- Cured in 3 hours for a fast turnaround
- Super low perm rating of 0.06 g/m²-24 hours-mmHg
- Superior moisture protection for floor covering installation systems

Available in
2 gal. unit



BUILDING TRUST



Sika® MB Redline

FAST SETTING EPOXY MOISTURE BARRIER

WHERE TO USE

- Concrete, cement, self-leveling and gypsum substrates
- OSB, plywood, parquet and cork
- Quarry and terrazzo
- Water-soluble adhesive and cutback adhesive





















NOTE: Always refer to current PDS and SDS for detailed performance specifications prior to use.

TYPICAL DATA (Material and curing conditions @ 73°F (23°C) and 50% R.H.)	
Color	Red
Chemistry	Two component epoxy
Density (ASTM C185)	70 lbs/cu.ft.
Cure Time	<ul style="list-style-type: none"> ■ 60°F (10°C) - 3.5 hours ■ 73°F (23°C) - 3 hours
Water Vapor Permeability (ASTM E-96)	0.06 g/m ² -24hour-mmHG

FEATURES AND BENEFITS

- Solvent-free (100% solids)
- Convenient, easy to mix packaging
- Easy roller application and low viscosity
- Excellent penetration up to 1/4" and stabilization of the substrate
- Reduction of adhesive consumption
- Substrate consolidator and adhesion promoter

Sika® Classification Table

Strength					
Flow					
Speed					
Moisture Protection					



FOR MORE INFORMATION:

Contact Sika: Phone 800.933.SIKA(7452) Website: www.sikasecure.com

Sika Corporation
 201 Polito Avenue
 Lyndhurst, NJ 07071
 Phone: 201-933-8800
 Fax: 201-933-6225



BUILDING TRUST

