

Sikagard® 307 W

Single component, waterborne modified acrylic/polyurethane dispersion based surface coating with a gloss finish

Description	Sikagard 307 W is a single component waterborne polyurethane based coating, designed with specific hygiene functionality. The in film preservation is designed to remain permanently locked in and active ensuring no growth of surface micro-organisms on the Sikagard 307 W. Sikagard 307 W is available in white. Custom colors required 10 to 15 business days lead time.
Where to Use	<ul style="list-style-type: none"> ■ Internal walls and ceilings of environments that require continuously sanitary conditions. ■ Pharmaceutical ■ Food & Beverage ■ Bio-tech manufacturing ■ Hospitals ■ Clean rooms ■ Laboratories
Advantages	<ul style="list-style-type: none"> ■ Single component waterbased, low odor ■ Hard finish and impact; scratch and abrasion resistant ■ Gloss, easy clean finish ■ Non-yellowing ■ Fast development of physical strength ■ Rapid drying, same day re-coat if necessary ■ One coat finish (airless spray) ■ Leach resistant in film preservative
Chemical Resistance	Standard 10% solutions of acids and alkalis, including Nitric Acid AND Caustic Soda, failed to cause breakdown of the Sikagard 307 W.

Typical Data

Chemical Base	Waterborne acrylic/polyurethane copolymer dispersion		
VOC Content	0.22 lb/gal. or 81.7 g/l		
Water Vapor Transmission	perms @ 4 mil DFT		
Fire Retardancy	Excellent resistance to surface spread of flame.		
Accelerated Weathering	ASTM G53-88- 5,000 hours Q.U.V. ('B' lamps) – no discoloration, chalking or crazing. Slight loss of gloss.		
Tensile Elongation	(BS EN ISO 527-3-Unreinforced)		
@ 24 hours - maximum stress (tensile load at break) =	6.8 N/mm ² or 987 psi	elongation at break =	110%
@ 48 hours - maximum stress (tensile load at break) =	7.2 N/mm ² or 1045 psi	elongation at break =	87%
@ 72 hours - maximum stress (tensile load at break) =	13.2 N/mm ² or 1920 psi	elongation at break =	50%
Adhesion	Coarse Concrete:	261 psi	1.8 MPa (N/mm ²)
	Smooth Concrete:	754 psi	5.2 MPa (N/mm ²)
	Brick:	551 psi	3.8 MPa (N/mm ²)
	Cement cladding board:	174 psi	1.2 MPa (N/mm ²)
	Steel:	710 psi	4.9 MPa (N/mm ²)
Tensile Strength	2326 psi (16 N/mm ²) (BS EN ISO 527-3 – Unreinforced)		
Density	10.43 lbs per gallon (~1.26 kg/l) (DIN EN ISO 2811-1)		
Hardness (Persoz)	125		
Solids Content	49% by weight and 36% by volume.		
Gloss	>60 gloss units at 60 degree (Classified as "gloss" to BS EN 13300:2001)		
Opacity (Contrast Ratio)	>99.5% (130 micron film) (Classified as "Class 1" to BS EN 13300:2001)		
Resistance to QUV	No appreciable change other than a minor reduction in gloss. (ASTM G154-04:2500 hours QUV-B)		
Surface Granularity	<0.01 mm (Classified as "fine" to BS EN 13300:2001)		
Abrasion Resistance	113 mg weight loss (ASTM D 4060, CS10 Wheel, 1000 g load)		
Scratch Resistance	Short cure (overnight) – slight penetration at 2000 grams longer cure (7 days) – penetration at 3000 grams, surface marking evident.		
Packaging	5 gallon pails		
Shelf Life	24 months (when stored under the recommended conditions).		
Storage Conditions	50°F (10°C) to 90°F (32°C)		

How to Use Surface

The substrate must be sound, clean, dry and free of all contaminants such as dirt, oil, laitance, mold, grease and surface treatments. Remove loose material mechanically, or high pressure washing. All surfaces to be coated should be clean and free from dampness. Prefill any static cracks with a proprietary flexible latex/acrylic caulk. Consult Sika Technical Service.

New Drywall: Minimum level 4 finish, prime with Sika Bonding Primer thinned 10% with water. (**Note:** 307 W cannot be applied directly over Sika Bonding Primer. An intermediate coat of Sikagard 203 W is required at 6-8 mils.)

Painted Surfaces: Always ensure that the existing paint is fully adhered and sound. Abrade surface using 100 grit screen or paper. Epoxy paints, bitumen paints must be abraded using 100 grit and primed using Sika Bonding Primer, followed by a 6-8 mil coat of Sikagard 203 W. All painted surfaces that are abraded require cleaning.

CMU Block, poured in place concrete: Spalled, flaking or damaged areas should be repaired using compatible materials. Sikagard 307 W can be used as a primer when diluted with 25% water.

Sikagard 203 W can be used as a block filler on new block. Like surfaces that requires a fill/parge coat should use Sikagard EpoCem 75 (consult product data sheet). Sikagard 307 W can be applied directly to cured/sanded EpoCem 75.

Cement screeds, plaster asbestos cement, lining boards: For absorbent substrates Sikagard 307 W may be diluted with 25% of clean water as a primer to kill suction. Dusty/friable substrates, seal with Sika Bonding Primer and an immediate coat of Sikagard 205 W to stabilize.

Concrete: Ensure new concrete is at least 10 days, preferably 28 days old, with moisture content of 20% WME or less. Prime using Sikagard 307 W diluted 25% with water.

Wood: (Damp Free maximum 18% wood moisture equivalent)

Apply Sikagard 307 W directly. If wood is prone to raised grain then prime with Sikagard 307 W diluted with 25% water, when dry, lightly sand and apply Sikagard 307 W to correct film thickness.

Metals: Remove rust to bright metal. Apply Sikalastic Metal Primer WB or Sikalastic Metal Primer, use 2 coats on badly pitted or blast prepared surfaces. Non-ferrous metals can be wired brushed to remove oxidation products, prime as above. Degrease or use proprietary metal pre-treatment fluid on galvanized if greasy.

Plastics/Insulation: Most plastics can be coated directly. Use Sika Bonding Primer on self-skinning or slab-stock polyurethane/polystyrene foams. Product is not suitable for open fibrous insulation. Dusty/friable substrates require sealing with Sika Bonding Primer and an immediate coat of Sikagard 205 W to stabilize.

Overcoating Sikagard 307 W: Clean off all contamination lightly abrade with 100 grit and apply Sikagard 307 W directly.

Mixing	Pre-mix material using a drill and jiffy blade (300-450 rpm)
Application	<p>Rollers - Product may be applied by short to medium 1/4" - 3/8" pile synthetic rollers. Two coats are recommended. Rollers are also used during reinforcement embedment.</p> <p>Brushes - A wide soft nylon or bristle brush, Two coats are recommended, ideally product is applied with second coat at 90° to first.</p> <p>Spray Equipment - Most types of industrial airless spray equipment e.g. GRACO ULTRA are suitable, pressure 3000 p.s.i. tip size .11 to .15 and 60° fan angle. Although the product is designed with built in flow, the finer tip sizes provide the smoothest finish.</p>
Tooling & Finishing	Note: All reinforcements using Flexitape and Reemat GFM must use Sikagard 203 W as the base coat.



Cure Mechanism @ 50°F/60% R.H.: Touch dry 45 mins, through cure 1 hour.
 @ 68°F/55% R.H.: Touch dry 30 mins, through cure 45 mins.
 @ 86°F/50-60% R.H.: Touch dry 15-20 mins, through cure 30-45 mins.

Application of Sikagard 307 W over Sikagard 307 W

Substrate Temp.	Minimum	Maximum
50°F (10°C)	4 hours	7 days
68°F (20°C)	1 hours	7 days
86°F (30°C)	1 hours	7 days

Application of Sikagard 307 W over Sikagard 203 W

Substrate Temp.	Minimum	Maximum
50°F (10°C)	24 hours	7 days
68°F (20°C)	4 hours	7 days
86°F (0°C)	4 hours	7 days

Coverage 400 sq.ft./gal., 4 mils WFT, recommended 2 coats

- Limitations**
- Do not apply near foodstuffs in unventilated conditions. Always ensure adequate ventilation.
 - Do not thin or brush out like conventional paints (thinning for primer use is permissible).
 - Do not apply the products below a minimum temperature of 40°F (4°C) or a maximum of 90°F (32°C) throughout the application period. Conditions must remain a minimum of 40°F (4°C) and 5°F (-15°C) above the dew point.
 - Protect from frost and heat (above 90°F {32°C}).
 - Product is not suitable for open fibrous insulation.
 - Sikagard 307 W is normally intended to be used internally, however if used externally the natural weathering process of the material may cause slight darkening of the colors and progressive loss of gloss with time. All colors are intermixable.
 - If there is any question as to whether or not the product will adhere to an existing coating or surface, a test patch should be applied and evaluated for compatibility and adhesion.
 - Application by roller may result in a slight surface texture when using standard coverage rates. If a smoother finish is required apply 3 thinner coats to achieve desired DFT. Previous coat must be completely dry prior to overcoating.
 - Ensure entire surface is fully dried before proceeding. Cracking may occur when overcoating undried surfaces or when material is applied in a heavy application.
 - Good ventilation is required for Sikagard 307 W to dry properly.
 - Gloss is effected by humidity and temperature.
 - The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.
 - If additional heating is required, do not use gas, oil, paraffin or other fossil fuel heaters; these methods produce large quantities of carbon dioxide and water vapor, which may adversely affect the finish. Use only electric powered warm air blower systems.
 - New concrete should be allowed to cure/hydrate for a minimum of 10 days and preferably 28 days.

CAUTION **WARNING: IRRITANT.** Polyurethane (Mixture), Butyl Carbitol (CAS: 112-34-5) and N-methyl-2-pyrrolidone (CAS: 872-50-4). Causes eye/skin/respiratory irritation. Harmful if swallowed.
WARNING: This product contains a chemical known to the State of California to cause birth defects or other reproductive harm.

First Aid **Eyes** – Hold eyelids apart and flush thoroughly with water for 15 minutes. **Skin** – Remove contaminated clothing. Wash skin thoroughly for 15 minutes with soap and water. **Inhalation** – Remove to fresh air. **Ingestion** – Do not induce vomiting. Dilute with water. **Contact a physician. In all cases, contact a physician immediately if symptoms persist.**

Handling and Storage Avoid direct contact. Wear personal protective equipment (chemical resistant goggles/gloves/clothing) to prevent direct contact with skin and eyes. Use only in well ventilated areas. Open doors and windows during use. Use a properly fitted NIOSH respirator if ventilation is poor. Wash thoroughly with soap and water after use. Remove contaminated clothing and launder before reuse.



Industrial Flooring

Clean Up	Clean brushes and spray equipment with water. Dried Sikagard 307 W can be removed with paint stripper, cellulose thinners, xylene or toluene. Use personal protective equipment (chemical resistant gloves/ goggles/clothing). Without direct contact, sweep up spilled or excess product and place in suitable sealed container. Dispose of excess product and container in accordance with applicable local, state, and federal regulations.
Additional Info	Technical Data Sheets are updated periodically. To ensure the most current version is being used, visit Technical Resources on www.sikafloorusa.com . Proper material application is the responsibility of the user. Site visits made by Sika personnel are for making technical recommendations only and not for supervising or providing quality control.

KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY

All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at www.sikacorp.com or by calling 800-933-7452.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available online at www.sikafloorusa.com or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use.

Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKASHALL NOT BELIEABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKASHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Visit our website at www.sikafloorusa.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537

