



Sika[®] MB

EPOXY MOISTURE BARRIER AND CONSOLIDATOR

- Super low perm rating of 0.06 g/m²-24 hours-mmHg
- Superior moisture protection for floor covering installation systems
- Substrate consolidator and adhesion promoter
- Compatible with SikaBond[®] wood flooring adhesives, Sika[®] AcouBond system, Sika[®] Level product range and SikaQuick[®] products

Available in
2.64 gal.unit



BUILDING TRUST



Sika® MB

EPOXY MOISTURE BARRIER AND CONSOLIDATOR

WHERE TO USE

- Concrete, cement, self-leveling, patch and gypsum substrates
- OSB and plywood
- Quarry and terrazzo tiles
- Water-soluble adhesive and cutback adhesive

NOTE: Always refer to current PDS and SDS for detailed performance specifications prior to use.

TYPICAL DATA (Material and curing conditions @ 73°F (23°C) and 50% R.H.)


Color	Blue
Chemistry	Two component epoxy
Density (ASTM C185)	69 lbs/cu.ft.
Cure Time	<ul style="list-style-type: none"> ■ 50°F (10°C) 18 hours ■ 73°F (23°C) 8 hours ■ 86°F (30°C) 6 hours
Compressive Strength	10,000 psi (69 MPa) at 7 days
Shore D Hardness	83 at 7 days (mixed A&B)
Water Vapor Permeability (ASTM E-96)	0.06 g/m ² -24hour-mmHG

FEATURES AND BENEFITS

- Solvent-free (100% solids)
- Convenient, easy to mix packaging
- Easy roller application and low viscosity
- Excellent penetration up to 1/4" and stabilization of the substrate
- Reduction of adhesive consumption
- Suitable on floors with radiant heating and below floating floors

Sika® Classification Table

Strength					
Flow					
Speed					
Moisture Protection					



FOR MORE INFORMATION:

Contact Sika: Phone 800.933.SIKA(7452) Website: www.sikasecure.com

Sika Corporation
 201 Polito Avenue
 Lyndhurst, NJ 07071
 Phone: 201-933-8800
 Fax: 201-933-6225



BUILDING TRUST

