

SikaTop® Seal 107

Flexible, waterproofing and protective slurry mortar

Description	SikaTop® Seal 107 is a two-component, polymer-modified, cementitious waterproofing and protective slurry mortar for concrete. It is slightly flexible to tolerate fine cracks and suitable in both interior and exterior applications.
Advantages	<p>SikaTop® Seal 107 provides the following beneficial properties:</p> <ul style="list-style-type: none"> ■ Improves the watertightness of water-containing concrete tanks, reservoirs, and clearwells. ■ Protects against water penetration, yet water vapor permeable (breathable). ■ Excellent freeze/thaw resistance. ■ Good adhesion to sound, prepared substrates. ■ Easy and fast mixing and application. ■ Good abrasion resistance. ■ Protects against concrete carbonation (80 mils SikaTop® Seal 107 is equivalent to 6 inches of concrete). ■ Can be mixed to slurry or trowelable consistency. ■ Improves concrete/masonry appearance. ■ Available in concrete gray and off-white. ■ Approved for potable water contact.
Where to use	<ul style="list-style-type: none"> ■ Horizontal surfaces subjected to light foot traffic (balconies). ■ For waterproofing of drinking water, tanks, reservoirs, and clear wells. ■ For internal and external waterproofing and damp-proofing concrete, mortar blockwork and brickwork. ■ For protection of concrete structures against the deleterious effects of deicing salts and freeze/thaw cycles. ■ For sealing "hairline" cracks in concrete structures not subject to movement surfaces. ■ For interior and exterior waterproofing of basements. ■ Vertical surfaces.
Coverage	<ul style="list-style-type: none"> ■ For damp-proofing: apply one coat at 40 mils. ■ For waterproofing: apply two coats at 40 mils per coat. Theoretical thickness (wet film) on smooth substrates: 40 ft.²/gal. = 40 mils (2 kg./m² = 1 mm). The above figures are theoretical and do not allow for substrate profile and wastage. Three coats may be required in areas of extremely high water infiltration.
Packaging	44 lb. unit - when mixed yields 2.65 gallons (10 l) Component 'A' - 1 gal. plastic jug; 4/carton. Component 'B' - 35.5 lb. multi-wall bag.

Typical Data (Material and curing conditions @ 73°F (23°C) and 50% R.H.)

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

Shelf Life	1 year when unopened.		
Storage	Protect Component 'A' from freezing and Component 'B' from moisture. Store dry at 40°- 95°F (4°- 35°C). Condition material to 65°-75°F conditions before using.		
Colors	Concrete gray and off white.		
Mixing Ratio	Component 'A': Component 'B'. Slurry consistency 1:4.1 by weight (full unit) Trowelable consistency 1:4.5 by weight (90% liquid to full bag)		
Density (wet mix)	125 lbs./ft. ³ (2.0 kg./l.) = 16.6 lbs./gal.		
Working Time	Approximately 60 minutes at 68°F; Approximately 30 minutes at 86°F		
Compressive Strength (ASTM D-695) @ 28 days	Type White 3,000 psi (20.7 MPa) Type Gray 3,400 psi (23.4 MPa)		
Tensile Strength (ASTM C-307) 28 days	White 870 psi (6.0 MPa) Gray 990 psi (6.8 MPa)		
Bond Strength (ACI 503R-30 Modified): Pull-off Test	28 days	180 psi (1.25 N/mm ²)	
Flexibility (ASTM D522 modified)	Approximately 25%		
Watertightness under hydrostatic pressure (DIN 1048 mod.)			
Water Pressure	Penetrated Water	Water Absorption	
feet (bar)	grains (grams)	grains	(grams)
		ft ² • hours (m ² • hours)	
16 (0.5)	0 (0)	0	(0)
33 (1)	15 (1)	3	(2)
99 (3)	31 (2)	10	(7)
Rendering mortars absorbing less than 91 grains/ft. ² • h (64 grams/m ² • h) are considered watertight.			
Vapor Permeability (ASTM E-96)	U.S. perms: 28 days 18 (not a vapor barrier)		
Carbon Dioxide Diffusion Coefficient (μCO₂)	Approximately 35,000, equivalent to 6 inches of concrete		
Water Vapor Diffusion Coefficient (μH₂O)	Approximately 500 ("breathable")		

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://USA.SIKA.COM/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.



How to Use

Substrate Preparation	Concrete, mortar and masonry surfaces must be clean, free from grease, oil and loosely adhering particles. All surfaces must be as true and flat as possible. An open-textured, sandpaper-like substrate is ideal (CSP-3). All surfaces must be saturated surface dry (SSD), with no standing water at time of application. It is necessary to stop water ingress prior to the application of SikaTop® Seal 107. Use a quick setting, waterproof slurry (SikaSet®) to seal water leaks.
Mixing	The consistency of the mix can be altered by reducing the amount of Component 'A' (liquid) to be used. Under normal circumstances, when the full quantities of both components are mixed together, a slurry consistency will result. For a trowelable consistency use only 90% of component 'A'. Mix in a clean container by slowly adding the powder component to the liquid component and mixing with slow speed drill and mixing paddle.
Application	<p>SikaTop® Seal 107 can be applied by trowel, notched trowel, stiff bristle, or spray equipment. Work the material well into the prepared substrate, filling all pores and voids.</p> <p>For brush consistency: Apply the first coat of SikaTop® Seal 107 with horizontal brush strokes and leave to harden (4 to 8 hours). Apply the second coat with vertical brush strokes.</p> <p>For trowel consistency: Apply the first coat with a notched trowel and leave to harden (4 to 8 hours). Apply the second coat with a flat trowel.</p> <p>For spray application: Use a hopper gun spray equipment, textured sprayer (e.g. Texspray E110c), or a rotor/stator pump equipment. Allow the first coat to harden (4 to 8 hours) prior to the application of the second coat. As soon as the mortar layer starts to set, a uniform surface texture can be obtained by rubbing the surface with a fine sponge or a plastic trowel. Do not overwork SikaTop® Seal 107 during finishing and avoid the use of additional water. [Where required, a third coat of SikaTop® Seal 107 may be applied no later than 24 hours after the second coat (in this case, do not trowel or sponge finish the second coat). If intercoat period exceeds 24 hours, light grit blasting is required prior to further application].</p> <p>Balcony Waterproofing Layer: Fill in any spalled areas in the existing substrate with the appropriate Sika repair mortar as required. Apply an appropriately sized closed cell backer rod along transition (wall-slab) to prevent three-sided adhesion. Apply a continuous cant bead of Sikaflex® 11-FC or Sikaflex® 2C, to a depth of 1/8" minimum and 1/2 inch thickness. Allow sealant to cure sufficiently. Substrate must be SSD with no standing water at time of application. Apply a 1/16" thick layer of SikaTop® Seal 107 over the entire balcony. While the material is still wet apply a "360 degree pull" non-alkaline, woven fiberglass mesh to reinforce the 107 layer along static hairline cracks, wall to slab transitions and patched areas. Using trowels remove any wrinkles in the mesh by forcing down into the SikaTop® Seal 107. Ensure the mesh is completely embedded and covered with SikaTop® Seal 107. If any areas are not covered apply additional SikaTop® Seal 107 over top of mesh to cover. Trowel to a smooth uniform finish. Allow curing so that surface can take foot traffic without harming the coating.</p>
Tooling & Finishing	Curing: As with all cement based products, curing is important. Protect newly applied product against direct sunlight, wind, rain and frost.
Limitations	<ul style="list-style-type: none"> ■ If rain is anticipated within 1-2 days after application, the surface should be protected in order to prevent streaking. ■ Not an aesthetic coating. ■ Minimum ambient and substrate temperatures are 45°F (7°C) and rising at the time of application. ■ Maximum application thickness per coat = 80 mils (2 mm). Do not apply less than 20 ft.²/gal. = 1 m²/liter. ■ As with all cement based materials, avoid contact with aluminum to prevent adverse chemical reaction and possible product failure. Insulate potential areas of contact by coating aluminum bars, rails, posts etc. with an appropriate epoxy such as Sikadur® Hi-Mod 32. ■ Allow 2 days of air curing before subjecting SikaTop® Seal 107 to submersion.

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

KEEP CONTAINER TIGHTLY CLOSED. KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. FOR PROFESSIONAL USE ONLY.

For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheet before using the product. In case of emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at <http://usa.sika.com/> or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. SALE OF SIKA PRODUCTS ARE SUBJECT SIKA'S TERMS AND CONDITIONS OF SALE AVAILABLE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING 201-933-8800.

Visit our website at usa.sika.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Sika and SikaTop® are registered trademarks. Printed in Canada.

