

Sika® ComfortFloor Decorative

Description	Sika ComfortFloor Decorative is an ergonomic, sound dampening, low emission floor which is UV stable, aesthetically pleasing, easy to care for and to maintain while contributing to project LEED certification. ComfortFloor Decorative is an 80-120 mil, seamless, fluid applied urethane floor system comprised of a 100% solids epoxy primer, pigmented self leveling low VOC aliphatic urethane wear course, optional decorative vinyl flake and a wear resistant, clear waterbased urethane topcoat.
Where to Use	Particularly suitable for all commercial and public buildings including healthcare facilities, schools, retail spaces, laboratories, nursing facilities, showrooms, lobbies, museums and office space. For interior use only.
Advantages	<ul style="list-style-type: none"> ■ Exceedingly low VOC emission ■ Flexible and resilient ■ Good acoustic isolation ■ Good mechanical resistance ■ Good UV resistance ■ Reduces footfall sound ■ Attractive, permanent multicolored patterns possible using colored flakes ■ Solvent Free ■ Non shrinking after cure ■ High strength ■ Contains Rapidly Renewable raw material ■ Low maintenance and life cycle cost versus tile, sheet goods and carpet ■ Tough, durable and seamless floor ■ (optional) Integral cove base and curbs ■ Excellent adhesion in areas with heavy traffic and rolling loads such as carts, gurneys and wheelchairs ■ Use of this Sikafloor system can help contribute to project LEED certification

Typical Data

Chemical Base	PUR
Bond Strength	> 400 psi (concrete failure) (ASTM D-4541)
Hardness	≤ 84 (14 days / +23°C) (ASTM D-2240, Shore A)
Impact Resistance	>160 in/lbs (ASTM D-4226)
Impact Sound Reduction	1 dB (ISO 140-8)
Impact Insulation Class (IIC)	40 (8" slab no ceiling) (ASTM E492-09/ASTM E989-06) 55 (w/1 layer 5/8" gypsum board ceiling) (ASTM E492-09/ASTM E989-06) 36 (6" slab no ceiling) (ASTM E492-09/ASTM E989-06)
Increased Impact Insulation (ΔIIC)	10 (ASTM E2179)
Sound transmission Class (STC)	52 (ASTM E90-04/ASTM E413-04)
Noise Reduction Coefficient (NRC)	.05 (ASTM C423-09A/ASTM E795-05)
Crack Bridging/Elongation	passed (ASTM C-1305)
Elongation at Break	70%
VOC Content	Sikafloor 107 Primer - 0 g/l Sikafloor 300N - 2 g/l Sikafloor 304W - 69 g/l
Closed Chamber Emission	Passed (California 01350 - 14 day)
Closed Chamber Emission	Passed (ISO 16000-6 - 28 day)
Physiological Harmlessness	Passed (DIN EN 71 Teil 3)
Gloss of 304W Topcoat	5-15 (ASTM D-523, 60°)
Coefficient Of Friction	> 0.60 (ASTM D-2047)
Resistance to Chair Castors	No damage (EN 425)
Abrasion Resistance	≤ 0.04gm (CS-17, 1000 gms, 1000 cycles) (ASTM D-4060)
Installed Thickness	80 - 120 mils (2 - 3 mm)
Static Load Limit	≤ 0.002 in (800 lb load) (ASTM F-970)
Flammability	Class I (ASTM E-648)
Smoke Density	<450 (ASTM E662)
Resistance to Heat	Δ E 0.12 (7 days at 158°F/70°C) (ASTM F-1514)
Compatibility w/Underfloor Heating Systems	Very good
Thermal Insulation	Very good
Cure Rate	Light Foot traffic - 12 hours Normal operations - 48 hours
Shelf Life:	When stored in recommended storage conditions, in original factory sealed cans, shelf life is 1 year.
Packaging:	Liquid components are packaged in pre-proportioned kits.
Colors:	Refer to Sika ComfortFloor Color Card.

Chemical Resistance	Sika ComfortFloor Decorative Pro must be sealed with Sikafloor 304 W or another suitable Sikafloor topcoat. For chemical resistance of the system, please consult the appropriate topcoat chemical resistance chart by visiting www.sikafloorusa.com or contacting Sika Technical Service at 1-800-933-SIKA.
How To Use	
Surface Preparation	Surface must be clean, sound and dry. Remove dust, laitance, grease, curing compounds, bond inhibiting impregnations, waxes and any other contaminants. All projections, rough spots, etc. should be dressed off to achieve a level surface prior to the application and concavities should be filled. Repairs to the substrate, filling of blowholes/voids and surface levelling must be carried out using appropriate products from the Sikafloor, Sikadur and Sikagard range of materials. Concrete - Should be cleaned and prepared to achieve a laitance and contaminant free, open textured surface by shot blasting or equivalent mechanical means. (CSP-3 as per ICRI guidelines). Sweep and vacuum any remaining dirt and dust with a wet/dry vacuum. Removing residual dust will help ensure a tenacious bond between the primer and substrate. Whenever shot-blasting is utilized, be careful to leave concrete with a uniform texture. Over blasting will result in reduced coverage rates of the primer and/or subsequent topcoats. It is also possible that the texture of the shotblast pattern may show through the last coat. This is known as tracking. The compressive strength of the concrete substrate should be at least 3500 psi (24 MPa) at 28 days and at least 250 psi (1.7 MPa) in tension at the time of application of Sikafloor 107.
Application	Please refer to component technical data sheets for specific information regarding the following products. Sikafloor 107 Primer: Sikafloor 107 Primer is poured and spread evenly by roller, trowel or squeegee at the rate of 160-320 square feet per mixed gallon at 5 - 10 mils wet film thickness. Coverage will vary depending on the porosity of the prepared floor. This product has a limited pot life. Product should not be applied by dipping roller into kit container, but by pouring a bead of product in the form of a ribbon on the surface to be coated. Sikafloor 300N: Sikafloor 300N is poured and spread evenly using a two step process at a thickness of 80 mils by means of a serrated trowel, Swedish knife, pin rake or gauge rake. Sikafloor 300N is rolled immediately (within 10 minutes of application) in two directions with a spiked roller to ensure even thickness and to remove entrapped air. Spike rolling after 10 minutes may result in surface blemishes or lack of level in the finished film. If flakes are to be applied, broadcast them at this time using a consistent upward throw. Sikafloor 304 W and Sikafloor 305 W: Measure and mark the area to ensure consistent coverage of each kit of topcoat at 5 wet mils. Over or under application of the topcoat may result in inconsistencies in the finish. Pre-coat the edge areas with brush and small roller. Ensure maintenance of a wet edge. Sikafloor 304 W is poured onto the substrate. The product is spread on the substrate in the pouring direction with a ½" or 3/8" lambskin roller and with the same roller across the pouring direction. Use the roller and extend the overlap for pour to pour consistency.
Critical Recoat Time	Consult specific product data sheets for recoat times.
Tooling & Finishing	A seamless finish can be achieved if a "wet" edge is maintained during application.
Removal	Clean all tools and application equipment with solvent immediately after use. Hardened and/or cured material can only be removed mechanically. Strictly follow solvent manufacturer's warnings and instructions for use.
Limitations	<ul style="list-style-type: none"> ■ Do not apply ComfortFloor Decorative on substrates with rising moisture. ■ Do not apply on substrate surfaces with a slope > 1%. ■ Freshly applied ComfortFloor Decorative must be protected from damp, condensation and water for at least 24 hours. ■ Uncured material reacts in contact with water which will result in foaming. During application, care must be taken that no condensation drops into freshly applied components of the ComfortFloor systems. ■ The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking. ■ For exact color matching, ensure the Sikafloor 300N in each area is applied from the same control batch number. ■ Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading, may lead to imprints in the resin. ■ If heating is required to bring the substrate and environment temperature to recommended levels, use only electric powered air blower systems. Do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both carbon dioxide and water vapor, which may adversely affect the finish. ■ If there is any question as to whether or not the product will adhere to an existing coating or surface, a test patch should be applied and evaluated for compatibility and adhesion. ■ Topcoat application by roller may result in surface texture when using standard coverage rates. If a smoother finish is required, apply the product utilizing spray equipment. ■ Ensure the entire surface is cured prior to introducing traffic onto the newly applied topcoat. Product which has not fully cured may scratch. ■ Good ventilation is required for Sikafloor 304 W to cure properly. ■ Gloss is affected by fluctuations in temperature and humidity. <p>Substrate Temperature: 50°F (+10°C) min. / 86°F (+30°C) max. Ambient Temperature: 50°F (+10°C) min. / 86°F (+30°C) max. Substrate Moisture Content: Conduct quantitative anhydrous calcium chloride testing in accordance with ASTM-F1869. Maximum acceptable test result is 3 pounds per 1,000 ft² per 24 hours. Determine the surface moisture content by using an impedance moisture meter designed for use on concrete as detailed in ASTM E-1907. Acceptable test results shall be 4% by mass or less. If over, use Sikafloor EpoCem 81/82 or contact Sika Technical Services for recommendations. Relative Air Humidity: 80% r.h. max. Dew Point: Beware of condensation! The substrate and uncured floor must be at least 5°F (3°C) above dew point to reduce the risk of condensation or blooming on the floor finish.</p>



Caution	PART R: CAUTION: IRRITANT, SENSITIZER. Contains: Castor Oil (CAS: 8001-79-4), Epoxy Resin (CAS: 25068-38-6). May cause eye/skin irritation. May be harmful if inhaled/swallowed. May cause skin sensitization. PART H: WARNING: IRRITANT, SENSITIZER. Contains Hexamethylene Diisocyanate Polymer (CAS: 28182-81-2) and Hexamethylene diisocyanate (HDI) (CAS: 822-06-0). Causes eye/skin/respiratory irritation. Harmful if swallowed. May cause skin/respiratory sensitization.
First Aid	Eyes – Hold eyelids apart and flush thoroughly with water for 15 minutes. Skin – Remove contaminated clothing. Wash skin thoroughly for 15 minutes with soap and water. Inhalation – Remove to fresh air. Ingestion – Do not induce vomiting. Dilute with water. Contact physician. In all cases contact a physician immediately if symptoms persist.
Handling & Storage	Avoid direct contact. Wear personal protective equipment (chemical resistant goggles/gloves/clothing) to prevent direct contact with skin and eyes. Use only in well ventilated areas. Open doors and windows during use. Use a properly fitted NIOSH respirator if ventilation is poor. Wash thoroughly with soap and water after use. Remove contaminated clothing and laundry before reuse
Clean Up	Use personal protective equipment (chemical resistant gloves/goggles/clothing). Without direct contact, sweep up spilled or excess product and place in suitable sealed container. Dispose of excess product and container in accordance with applicable local, state, and federal regulations.
Additional Info	Technical Data Sheets are updated periodically. To ensure the most current version is being used, visit Technical Resources on www.sikafloorusa.com . Proper material application is the responsibility of the user. Site visits made by Sika personnel are for making technical recommendations only and not for supervising or providing quality control. Before applying for protection against specific chemical environments, consult Chemical Resistance Guide or Sika Technical Service.

KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY

All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at www.sikausa.com or by calling 800-933-7452.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available online at www.sikafloorusa.com or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use.

Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKASHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKASHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Visit our website at www.sikafloorusa.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537

