

Sikadur® 22, Lo-Mod

Low-modulus, medium-viscosity,
epoxy resin binder

Construction

Description	Sikadur® 22, Lo-Mod is a 2-component, 100% solids, moisture-tolerant, epoxy resin binder. It conforms to the current ASTM C-881, Type III, Grade-2, Class-C and AASHTO M-235 specifications.
Where to Use	Use neat as the binder resin for a skid-resistant broadcast overlay. Use also as the binder resin for epoxy mortar and concrete for patching and overlays.
Advantages	<ul style="list-style-type: none"> ■ Tolerant to moisture both before and after cure. ■ Convenient easy mix ratio A:B = 1:1 by volume. ■ Excellent strength development. ■ Leveling viscosity for easy, efficient application of a broadcast overlay. ■ Material is USDA-certifiable.
Coverage	1 gal. yields 231 in ³ Mortar Binder - 1 gal. of mixed Sikadur® 22 Lo-Mod with the addition of 5 gal. by loose volume of an oven dried sand, yields approximately 808 in ³ of epoxy mortar.
Packaging	4 gallon units / 110 gallon unit / 660 gallon totes. Note: Part A of the Sikadur 22 Lo-Mod, Sikadur 22 Lo-Mod FS and Sikadur 21 Lo-Mod LV is a universal component of these three products.

Typical Data [Material and curing conditions @ 73°F (23°C) and 50% R.H.]

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

Shelf Life	2 years in original, unopened containers.		
Storage Conditions	Store dry at 40°-95°F (4°-35°C). Condition material to 65°-85°F (18°-29°C) before using.		
Color	Clear to light amber.		
Mixing Ratio	Component 'A':Component 'B' = 1:1 by volume.		
Viscosity	Approximately 2,000 cps.		
Pot Life	Approximately 30 minutes (200 gram mass).		
Tack-Free Time	40°F (4°C)	73°F (23°C)	90°F (32°C)
	6-8 hours	5 hours	2.5 hours
Traffic Time	24 hours		
Tensile Properties (ASTM D-638)	Mortar 1:3	Neat	
14 day Tensile Strength	2,200 psi (15.2 MPa)	5,700 psi (39.3 MPa)	
Elongation at Break	-	>30 %	
Modulus of Elasticity	4.78 x 10 ⁵ psi (3,240 MPa)	1.9 x 10 ⁵ psi (1,310 MPa)	
(Neat tested @ 0.5 in/min.)			
Tensile Strength (ASTM C307)	Mortar 1:3	Neat	
14 day	1400 psi (9.7MPa)	2800 psi (19.3 MPa)	
Shear Strength (ASTM D-732)	Mortar 1:3	Neat	
7 day Shear Strength	3,000 psi (22.7 MPa)	5,700 psi (37.2 MPa)	
Water Absorption (ASTM D-570)		Neat	
7 day (24 hour immersion)		0.26 %	
Direct Tensile (ASTM C-1503; ACI 503):	Mortar 1:3	Neat	
7 day	510 psi concrete fail	570 psi concrete fail	
Abrasion (Taber Abrader)	Mortar 1:3	Neat	
14 day Weight loss, 1,000 cycles (H-22 wheel; 1,000 gm weight)	1.8 gm	.030 gm	



PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

Compressive Properties (ASTM D-695) Mortar 1:3

Compressive Strength, psi (MPa)

	40°F* (4°C)	73°F * (23°C)	90°F* (32°C)	73°F* (23°C) NEAT
8 hour	-	1,900 (13.1)	2,800 (19.3)	-
16 hour	-	4,300 (29.6)	5,000 (34.5)	-
1 day	2,200 (15.2)	5,200 (35.9)	5,200 (35.9)	480 (3.3)
3 day	6,500 (44.8)	6,800 (46.9)	5,900 (40.7)	2,200 (15.2)
7 day	7,900 (59.5)	7,200 (49.6)	6,100 (42.1)	3,400 (23.4)
14 day	8,800 (60.7)	7,600 (52.4)	6,100 (42.1)	3,400 (23.4)
28 day	9,500 (65.5)	7,900 (54.5)	6,100 (42.1)	3,400 (23.4)

Compressive Modulus

28 day 6.6 x 10⁴ psi (455 MPa)

* Material cured and tested at the temperatures indicated.

How to Use

Surface Preparation Surface must be clean and sound. It may be dry or damp, but free of standing water. Remove dust, laitance, grease, curing compounds, impregnations, waxes and any other contaminants.

Preparation Work: Concrete - Should be cleaned and prepared to achieve a laitance and contaminant free, open textured surface (CSP 3-4 as per ICRI) by blast cleaning or equivalent mechanical means.

Steel - Should be cleaned and prepared thoroughly by blast cleaning to white metal finish.

Mixing Proportion equal parts by volume of Component 'A' and 'B' into clean pail. Mix thoroughly for 3 min. with Sika paddle on low-speed (400-600 rpm) drill until uniformly blended. Mix only that quantity that can be used within pot life.

To prepare epoxy mortar - Slowly add 5 parts by loose volume of oven-dried sand to 1 part of mixed Sikadur® 22 Lo-Mod until uniform in consistency.

Application **Broadcast Overlay** - Prime the prepared substrate with Sikadur® 22 Lo-Mod. While primer is still tacky, spread mixed Sikadur® 22 Lo-Mod with a 3/16 in. notched squeegee. When material levels, broadcast the oven-dried aggregate slowly allowing it to settle in the epoxy binder. Ultimately the broadcast aggregate should be applied to excess at a rate of 2 lbs./ft² Remove excess broadcast aggregate after epoxy has set. Priming is an optional step in the broadcast overlay applications.

Epoxy Mortar - Prime prepared substrate with mixed Sikadur® 22 Lo-Mod or Sikadur® 21 Lo Mod LV. While primer is still tacky, apply epoxy mortar by trowel or vibrating screed. Finish with finishing trowel. Priming is mandatory when using the 22 Lo Mod as an epoxy mortar.

Limitations

- Minimum substrate and ambient temperature 40°F (4°C).
- For on grade, split-slab and unvented metal pan deck, please consult Sika Technical Service regarding moisture limitations.
- Minimum age of concrete before application is 21-28 days depending upon curing and drying conditions.
- Do not use on exterior slab on grade.
- Maximum thickness 1/2 in. (13 mm) exterior exposed to thermal change.
- Do not dilute. Addition of solvents will prevent proper cure.
- Use oven-dried aggregates only.
- Material is a vapor barrier after cure.
- Not an aesthetic product. Color may alter due to variations in lighting and/or UV exposure.

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

KEEP CONTAINER TIGHTLY CLOSED. KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. FOR PROFESSIONAL USE ONLY.

For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheet before using the product. In case of emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at <http://usa.sika.com/> or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. SALE OF SIKA PRODUCTS ARE SUBJECT SIKA'S TERMS AND CONDITIONS OF SALE AVAILABLE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING 201-933-8800.

Visit our website at usa.sika.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Sika and Sikadur are registered trademarks.
Printed in Canada.

