

## PRODUCT DATA SHEET

# Sika® Primer-207 AGR

## PIGMENTED, SOLVENT-BASED PRIMER FOR VEHICLE GLASS APPLICATIONS

### TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

<b>Chemical base</b>	Solvent-based polyurethane solution
<b>Color (CQP001-1)</b>	Black
<b>Solid content</b>	27 %
<b>Application temperature</b>	5 – 40 °C
<b>Application method</b>	Brush, felt or foam applicator
<b>Consumption</b>	depending on substrate porosity 50 ml/m <sup>2</sup>
<b>Flash-off time</b>	above 5 °C 10 minutes <sup>A</sup> maximum 24 hours <sup>A</sup>
<b>Shelf life (CQP016-1)</b>	Stix 13 months <sup>B</sup> All other package sizes 12 months <sup>B</sup>

CQP = Corporate Quality Procedure

<sup>A)</sup> in specific application, temperature and flash-off time may be different<sup>B)</sup> stored in sealed container in up-right position in a dry place between 5 and 25 °C

### DESCRIPTION

Sika® Primer-207 AGR is a solvent-based black primer, which reacts with moisture and forms a thin layer. This layer acts as a link between substrates and adhesives.

Sika® Primer-207 AGR is specifically formulated for the treatment of bond faces prior to application of Sika's 1-component Polyurethanes. This primer provides excellent adhesion without previous activation step on many substrates. Sika® Primer-207 AGR fluoresces under long-wave UV light for a limited period of time. This feature is used for in-process control.

### AREAS OF APPLICATION

Sika® Primer-207 AGR is used to improve adhesion on the different substrates used for bonding vehicle glass such as float glass, ceramic-coated glass, plastics, pre-coatings, painted surfaces, E-coats and metals.

Seek manufacturer's advice and perform tests on original substrates before using Sika® Primer-207 AGR on materials prone to stress cracking.

This product is suitable for experienced professional users only. Test with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

### METHOD OF APPLICATION

Surfaces must be clean, dry and free from grease, oil, dust and contaminants.

Adhesion on substrates may be improved by adding and/or combining pre-treatment processes such as scuffing, cleaning and activating.

#### Application

Shake the Sika® Primer-207 AGR can vigorously until you hear the mixing ball rattle and then continue shaking for an additional 10 seconds. Apply a thin but covering coat with a brush, felt or foam applicator.

Ideal application and surface temperature are between 15 °C and 25 °C.

Consumption and method of application depend on the specific nature of the substrates. Tightly reseal container immediately after each use.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, label and Safety Data Sheet which are available at <http://usa.sika.com/> or on request at [tsmh@us.sika.com](mailto:tsmh@us.sika.com). Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instructions for each Sika product as set forth in the current Product Data Sheet, label and Safety Data Sheet prior to product use.

PRODUCT DATA SHEET

Sika® Primer-207 AGR

Version 01.01 (01 - 2019), en\_US

014761012070001010

### IMPORTANT NOTE

If Sika® Primer-207 AGR is used below 5 °C further testing under worst case conditions is mandatory.

Sika® Primer-207 AGR is a moisture reactive system. In order to maintain product quality it is important to reseal the container with the inner plastic liner immediately after use. Once the surface pre-treatment operation is completed, the cap has to be screwed on.

Dispose of the product after the expiration date or within one month after opening for the first time, whichever comes first. Stix are for single application only.

If gelling, separation or a significant increase in viscosity is noted, discard the primer immediately.

Never dilute or mix this product with any other substances.

If used on transparent or translucent substrates such as float glass, organic glass, etc., an adequate UV protection is mandatory.

### DETECTION OF THE LUMINESCENCE

Sika® Primer-207 AGR can be visualized by using a light source with a wavelength of 320 to 420 nm as inline control. By reducing foreign light such as sunlight or artificial light during the detecting process the quality of the detection can be increased significantly.

Note: The luminescent effect will degrade with time.

### FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Working instructions issued for a defined application may further specify technical data contained in this Product Data Sheet.

Copies of the following publications are available on request:

- Safety Data Sheets
- Sika AGR Technician Training Manual

### PACKAGING INFORMATION

Stix	1.4 ml
Can	100 ml
	250 ml

### BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

### HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

### LIMITED PRODUCT WARRANTY

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, label and Safety Data Sheet which are available at <http://usa.sika.com/> or on request at [tsmh@us.sika.com](mailto:tsmh@us.sika.com). Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instructions for each Sika product as set forth in the current Product Data Sheet, label and Safety Data Sheet prior to product use.

PRODUCT DATA SHEET  
Sika® Primer-207 AGR  
Version 01.01 (01 - 2019), en\_US  
014761012070001010

Sika Corporation  
30800 Stephenson Highway  
Madison Heights, MI 48071  
U.S.A.  
Telephone: +1 248-577-0020  
Email: [tsmh@us.sika.com](mailto:tsmh@us.sika.com)  
[www.sikausa.com](http://www.sikausa.com)

