

PRODUCT DATA SHEET

Sikasil® WS-290

ULTRA LOW MODULUS, NEUTRAL CURE SILICONE SEALANT

PRODUCT DESCRIPTION

Sikasil® WS-290 is a one-part, neutral-curing, ultra low-modulus, low to no bleed silicone sealant that cures to a durable, flexible building sealant. Sikasil® WS-290 performs exceptionally well under dynamic conditions due to its ultra-low modulus, high extension/compression, recovery properties and strong adhesion to most building materials. Sikasil® WS-290 accommodates long-term movement of +100–50 % in properly designed joints and is particularly well suited for use in Exterior Insulation Finish Systems (EIFS). Meets the requirements of ASTM C-920, Type S, Grade NS, Class 100/50, Use NT, M, G, A, O; TT-S-00230C, Type II, Class A; TT-S-001543A, Class A; CAN/CGSB-1 9.1 3-M87, AAMA 808.3


USES

- Sealing expansion and control joints in precast concrete panels and metal curtain walls.
- As a weatherseal in glass to glass butt joint glazing.
- As a weatherseal in nonstructural glazing applications, including cap, toe and heel beads.
- Exterior Insulation Finish Systems (EIFS) and numerous other areas requiring a high-performance sealant.

CHARACTERISTICS / ADVANTAGES

- Unaffected by most atmospheric conditions
- Excellent resistance to UV and Ozone exposure
- Non-staining
- Joint movement +100/-50 %
- Excellent adhesion
- One-component
- Excellent gunnability in all temperatures
- Ultra low Modulus

APPROVALS / STANDARDS



PRODUCT INFORMATION

Packaging	10.1 fl.oz. (.300 ml) plastic cartridges, 20 fl.oz. (.592 ml) sausages, 2 gal. pails (7.57 L)
Shelf Life	12 months in original unopened cartridges.
Storage Conditions	Store in unopened containers at temperatures lower than 80 °F (27 °C).

Volatile organic compound (VOC) content 29 g/l

TECHNICAL INFORMATION

Shore A Hardness	12	(7 days at 77 °F (25 °C), 50 % R.H.) (ASTM C-661)	
Tensile Strength	165 psi (1.14 MPa)	(7 days at 77 °F (25 °C), 50 % R.H.) (ASTM D-412)	
Tensile Stress at Specified Elongation	42 psi (0.29 MPa) @ 100 %	(7 days at 77 °F (25 °C), 50 % R.H.) (ASTM D-412)	
Elongation at Break	1000 %	(7 days at 77 °F (25 °C), 50 % R.H.) (ASTM D-412)	
Adhesion in Peel	20–40 pli	(7 days at 77 °F (25 °C), 50 % R.H.) (ASTM C-794)	
Movement Capability	+100 %, -50 %	(7 days at 77 °F (25 °C), 50 % R.H.) (ASTM C-719)	
UV Exposure	Excellent	(7 days at 77 °F (25 °C), 50 % R.H.) (weatherometer)	
Colour Stability	Staining, Color Change Staining on Porous Substrates	none no staining	(7 days at 77 °F (25 °C), 50 % R.H.) (ASTM C-1248)
Service Temperature	-80 °F to 350 °F		

APPLICATION INFORMATION

Coverage

10.1 oz Cartridge: Yield in Linear feet

Width/Depth	1/4"	3/8"	1/2"
1/4"	24.3		
3/8"	16.2	10.8	
1/2"	12.1	8.1	6.1
3/4"	8.1	5.4	4.0
1"			3.0
1.25"			2.4
1.5"			2.0

20 oz Sausage: Yield in Linear feet

Width/Depth	1/4"	3/8"	1/2"
1/4"	48.1		
3/8"	32.1	21.4	
1/2"	24.1	16.0	12.0
3/4"	16.0	10.7	8.0
1"			6.0
1.25"			4.8
1.5"			4.0

1 gallon: Yield in Linear feet

Width/Depth	1/4"	3/8"	1/2"
1/4"	307.9		
3/8"	205.3	136.8	
1/2"	153.9	102.6	77.0
3/4"	102.6	68.4	51.3
1"			38.5
1.25"			30.8
1.5"			25.7

Sag Flow none

Cure Time	Tack Free Time	50 min.	(at 77 °F (25 °C) and
	Cure Time	7-14 days	50 % R.H.)
	Full Adhesion	7-14 days	(ASTM C-679)
<hr/>			
Tack Free Time	50 minutes		
<hr/>			
Tooling Time	30 minutes, (higher temperatures and/or humidity will shorten this time)		
<hr/>			

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

The substrate must be clean, dry, frost free, sound and free of any oils, greases or incompatible sealers, paints or coatings that may interfere with adhesion.

POROUS SUBSTRATES – clean by mechanical methods to expose a sound surface free of contamination and laitance.

NON-POROUS SUBSTRATES – for cleaning non-porous substrates, use two rag wipe method using xylene or an approved commercial solvent. Allow solvent to evaporate prior to sealant application. Sikasil® WS-290 is designed to obtain adhesion without the use of a primer; however, certain substrates may require a primer. Test by applying the sealant and/or primer sealant combination to confirm results and proposed application methods. Refer to Technical Data Sheet for Sikasil Primer 2100 and contact Technical Service for additional information.

APPLICATION METHOD / TOOLS

The depth of the sealant should be 1/2 the width of the joint. The maximum depth is 1/2 inch (13mm) and the minimum is 1/4 inch (6mm). To control joint depth, use closed cell polyethylene, non-gassing polyolefin or open cell polyurethane backer rod. If joint depth does not allow for backer rod, use polyethylene bond breaker tape to prevent three-sided adhesion. Closed cell backer rod should be 25% larger than joint width; do not compress more than 40 %. Open cell should be compressed 40 %. Do not use open cell rod in horizontal on grade joint or with E.I.F.S. When installing during time of large temperature swings such as spring or fall, and in joints designed for movement greater than ± 25 %, be aware of the significant joint movement before cure, may cause aesthetic issues such as ripples in the sealant surface. Performance will not be affected.

Ready to use, apply using professional caulking gun. Do not open product container until preparation work has been completed. Apply sealant using consistent, positive pressure to force sealant into the joint. Tool sealant to create a concave joint shape and maximum adhesion. Dry tooling is recommended. DO NOT use soapy water or other liquids when tooling.

Tooling & Finishing

All joints should be masked to ensure a neat appearance and prevent sealant applied outside the joint. Place

nozzle of the gun into bottom of joint and fill entire joint making complete contact with joint sides. Keep the nozzle in the sealant, continue with a steady flow of sealant preceding the nozzle to avoid air entrapment. Tool the sealant slightly concave using dry-tooling techniques. Do not tool with soap or detergent and water solutions.

LIMITATIONS

- Do not allow sealant to come in contact with solvent during cure.
- Do not allow sealant to come in contact with curing polyurethane sealants during cure.
- Not intended for immersion.
- Sealant may be applied below freezing temperatures if substrates are completely dry, frost free and clean. Contact Technical Service for more information.
- Do not apply when substrate temperatures are below - 20 °F or above 130 °F.
- Not intended for structural glazing.
- Not recommended for horizontal vehicular traffic.
- Do not apply to surfaces that will be painted as sealant surface will not hold paint.
- Do not apply to damp or wet substrates.
- Lower temperature and humidity will extend tack free and cure rates.
- Allow treated wood to age six months before application.
- Brass and copper may be discolored. Test apply prior to application.
- Test sensitive substrates, such as mirror backings, for compatibility before use.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must

read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet
Sikasil® WS-290
March 2019, Version 02.02
020511030000000007

SikasilWS-290-en-US-(03-2019)-2-2.pdf

BUILDING TRUST

