

PRODUCT DATA SHEET

Sikasil® GP-101

GENERAL PURPOSE ACETOXY CURE SILICONE SEALANT

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base	1-component silicone
Color (CQP001-1)	Almond, aluminum, black, cameo white, translucent, transwhite, white
Cure mechanism	Moisture-curing
Cure type	Acetoxy
Density	0.98 kg/l
Application temperature	5 – 40 °C (41 – 104 °F)
Skin time (CQP019-1)	20 minutes ^{a)}
Shore A hardness (CQP023-1 / ISO 7619-1)	15
Tensile strength (ASTM D412)	150 psi
Elongation at break (ASTM D412)	400 %
Service temperature	-40 – 180 °C (-40 – 356 °C)
Shelf life (CQP016-1)	24 months ^{b)}

CQP = Corporate Quality Procedure

^{a)} 23 °C (73 °F) / 50 % r.h.^{b)} Stored below 25 °C (77 °F)

DESCRIPTION

Sikasil® GP-101 is a general purpose, one-component, non-sag, elastomeric, room-temperature vulcanizing (RTV) acetoxy silicone sealant with good adhesion characteristics for general sealing and bonding applications.

PRODUCT BENEFITS

- Listed under NSF/ANSI 51 - Food Equipment Materials (dependent on color)
- Joint movement accommodation ±25 % per ISO 11600
- Excellent UV and heat resistance
- Superior gunning & tooling
- Solvent free

AREAS OF APPLICATION

Sikasil® GP-101 can be used for food equipment and appliance assembly. Other areas of application include general sealing of windows, HVAC, trucks, trailers, and RVs. This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

CURE MECHANISM

Sikasil® GP-101 cures by reaction with atmospheric moisture. At low temperatures, the water content of the air is lower and the curing reaction proceeds more slowly.

METHOD OF APPLICATION

Surface Preparation

Surfaces must be clean, dry and free from grease, oil and dust. Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond.

Application

The optimum temperature for substrate and sealant is between 15 °C (59 °F) and 25 °C (77 °F). Sikasil® GP-101 can be processed with hand, pneumatic or electric driven piston guns. Joints must be properly dimensioned. Joints deeper than 15 mm must be avoided.

Tooling and finishing

Tooling and finishing must be carried out within the skin time of the sealant or adhesive. When tooling freshly applied Sikasil® GP-101 press the adhesive to the joint flanks to get a good wetting of the bonding surface. No tooling agents to be used.

Removal

Uncured Sikasil® GP-101 can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically. Hands and exposed skin have to be washed immediately using hand wipes or a suitable industrial hand cleaner and water. Do not use solvents on skin.

Overpainting

Sikasil® GP-101 cannot be overpainted.

Application Limits

- Sikasil® GP-101 is not suitable for submersible applications.
- Sikasil® GP-101 should not be used on substrates such as marble, concrete, fibrous cement and mortars due to acetic acid.
- Due to staining, Sikasil® GP-101 is not recommended for use on natural stone such as marble, granite, quartzite, etc.
- Sikasil® GP-101 may become discolored if in contact with some organic elastomers such as EPDM, APTK and neoprene.
- Due to corrosion, Sikasil® GP-101 should not be used in contact with metals such as lead, copper, brass or zinc.
- Sikasil® GP-101 is not recommended for structural glazing or use in an aquarium.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets

PACKAGING INFORMATION

Cartridge	295 ml
-----------	--------

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ENVIRONMENTAL, HEALTH AND

SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1- 800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by contacting SIKA's Technical Service Department via email at tsmh@us.sika.com. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product. SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.** Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 201-933-8300.

