



## Section 03 60 00 Grouting

\*\*\*

**SIKA SPECIFICATION NOTE:** *This guide specification includes test methods, materials and installation procedures for SikaGrout®-212, general purpose cementitious grout. SikaGrout®-212 is a one-component, ready to mix, free flowing, non-shrink, cementitious grout with a unique 2-stage shrinkage compensating mechanism. This guide specification should be adapted to suit the needs and conditions of individual projects. It is prepared in CSI Master Format and should be included as a separate section under Division 3 - Concrete.*

\*\*\*

### Part 1 - General

#### 1.01 Summary

This Specification shall be read as a whole by all parties concerned. Each Section may contain more or less the complete Work of any trade. The Contractor is solely responsible to make clear to the Subcontractors the extent of their Work and coordinate overlapping Work.

#### 1.02 System description

This specification describes the grouting of cavities, voids, key ways, etc. with a portland cement, non-shrink, non-metallic grout.

#### 1.03 Related sections

- A. 03 61 00 Cementitious Grouting
- B. 03 62 00 Non-Shrink Grouting
- C. 03 62 13 Non-Metallic Non-Shrink Grouting
- D. 03 01 60 Maintenance of Grouting

#### 1.04 References

The following standards are applicable to this section:

- ASTM C-266 – Time of Set
- ASTM C-939 – Fluidity
- ASTM C-109 – Compressive Strength
- ASTM C-940 - Expansion
- ASTM C-1090 – Shrinkage
- ASTM C-1107 – Standard Specification for Non-shrink Grouts

#### 1.05 Quality Assurance



- A. Manufacturing qualifications: The manufacturer of the specified product shall be ISO 9001 certified and have in existence a recognized ongoing quality assurance program independently audited on a regular basis.
- B. Contractor qualifications: Contractor shall be qualified in the field of grouting with a successful track record of 5 years or more. Contractor shall maintain qualified personnel who have received product training by a manufacturer's representative.
- C. Store and apply materials in accordance with all safety and weather conditions required by manufacturer or as modified by applicable rules and regulations of local, state and federal authorities having jurisdiction. Consult Material Safety Data Sheets for complete handling recommendations.

#### **1.06 Delivery, Storage, and Handling**

- A. All materials must be delivered in original, unopened containers with the manufacturer's name, labels, product identification, and batch numbers. Damaged material must be removed from the site immediately.
- B. Store all materials off the ground and protect from rain, freezing or excessive heat until ready for use.
- C. Condition the specified product as recommended by the manufacturer.

#### **1.07 Job Conditions**

- A. Environmental Conditions: Do not apply material if it is raining or snowing or if such conditions appear to be imminent. Minimum application temperature 45°F (7°C) and rising.
- B. Protection: Precautions should be taken to avoid damage to any surface near the work zone due to mixing and handling of the specified material.

#### **1.08 Submittals**

- A. Submit two copies of manufacturer's literature, to include: Product Data Sheets (PDS), and appropriate Safety Data Sheets (SDS).
- B. Submit copy of Certificate of Approved Contractor status by manufacturer.

#### **1.09 Warranty**

Provide a written warranty from the manufacturer against defects of materials for a period of one (1) year, beginning with date of substantial completion of the project.

## **Part 2 - Products**

### **2.01 Manufacturer**

SikaGrout®-212, as manufactured by Sika® Corporation, is considered to conform to the requirements of this specification.

### **2.02 Materials**

- A. The material shall be a blend of selected portland cements, specially graded aggregates, admixtures for controlling setting time and water reducers for workability.
- B. The material shall be non-combustible both before and after cure
- C. The material shall be supplied in a factory-blended bag

Portland cement grout:

- D. The portland cement grout shall be a non-shrink, non-metallic composition containing a blend of selected portland cements, plasticizing/water-reducing admixtures and shrinkage compensating agents. The shrinkage agents shall compensate for shrinkage in both the plastic and hardened state.
- E. Materials for forming, as required for the designated work, shall be approved by the Engineer.
- F. Curing compound, conforming to ASTM C-309, as required for the designated work, shall be approved by the Engineer.

### **2.03 Performance Criteria**

The grout shall not exhibit bleeding.

The grout shall be segregate.

The grout shall be pumpable through standard grout pumping equipment.

The grout shall not produce a vapor barrier.

The grout shall exhibit positive expansion when tested in accordance to ASTM C-827.

The grout shall conform to United States Army Corps of Engineers Specification CRD C-621.

The grout shall conform to ASTM C-1107.

The material shall be approved by the United States Department of Agriculture.



Typical Properties of the mixed polymer-modified, portland cement mortar:

1	Yield	0.44 ft <sup>3</sup> (0.01 m <sup>3</sup> ) at fluid consistency
2	Color	Gray powder
3	Mixing Ratio	<b>Plastic</b> - 6 pt <b>Flowable</b> – 6.5 pt <b>Fluid</b> – 8.5 pt
4	Application Thickness	Min: 1/2" (12.7 mm) Max: 4" (101.6 mm)
5	Application Temp	< 45 °F (7 °C)
6	Flowability (ASTM C-1437 <sup>1</sup> ASTM C-939 <sup>2</sup> )	<b>Plastic</b> <sup>1</sup> : 100–124 % <b>Flowable</b> <sup>1</sup> : 124–145 % <b>Fluid</b> <sup>2</sup> : 20–40 sec
7	Set time (ASTM C-266) flowable consistency	Initial: 4.0–5.0 h Final: 5.5–6.5 h
8	Compressive Strength (ASTM C-109)	<b>Plastic</b> 1 day - 4,500 psi (31 MPa) 7 days - 6,100 psi (42 MPa) 28 days - 7,500 psi (51.7 MPa) <b>Flowable</b> 1 day - 3,500 psi (24.1 MPa) 7 days - 5,700 psi (39.3 MPa) 28 days - 6,200 psi (42.7 MPa) <b>Fluid</b> 1 day - 2,700 psi (18.6 MPa) 7 days - 5,500 psi (37.9 MPa) 28 days - 5,800 psi (40 MPa)
9	Flexural Strength (ASTM C-293)	<b>Plastic</b> 28 days - 1,400 psi (9.6 MPa) <b>Flowable</b> 28 days - 1,200 psi (8.2 MPa) <b>Fluid</b> 28 days - 1,000 psi (6.8 MPa)
10	Splitting Tensile Strength (ASTM C-496)	<b>Plastic</b> 28 days - 600 psi (4.1 MPa) <b>Flowable</b> 28 days - 575 psi (3.9 MPa) <b>Fluid</b> 28 days - 500 psi (3.4 MPa)
11	Tensile Adhesion Strength (ASTM C-882 modified)	<b>Plastic</b> 28 days - 2,000 psi (13.7 MPa) <b>Flowable</b> 28 days - 1,900 psi (13.1 MPa) <b>Fluid</b> 28 days - 1,900 psi (13.1 MPa)
12	Expansion (ASTM C-1090)	<b>Plastic</b> 28 days +0.021 % <b>Flowable</b> 28 days +0.056 % <b>Fluid</b> 28 days +0.027 %

Note: Tests above were performed with the material and curing conditions @ 71°F – 75°F and 45 - 55% relative humidity.

## Part 3 – Execution

### 3.01 Surface Preparation

Areas to be repaired must be clean, sound, and free of contaminants. All loose and deteriorated concrete shall be removed by mechanical means. Mechanically prepare concrete substrate to obtain a surface profile of CSP 4 or greater (as per ICRI Guidelines) with a new exposed aggregate surface.

### 3.02 Mixing and Application

- A. Mixing of the portland cement grout: Mix manually or mechanically. Manually mix in a wheelbarrow or mortar box. Mechanically mix with a low-speed (400-600 rpm) drill and jiffy paddle or in an appropriate sized mortar mixer. Add an appropriate quantity of water to the mixing container to achieve the desired consistency. DO NOT OVERWATER While mixing the bag of powder is slowly added to the mixer. Mix to a uniform consistency for a minimum of 2 minutes. Mix temperature should be maintained at 70-75F, thus using cold or warm water accordingly.
- B. Placement Procedure:

**Spalls:** Within 15 minutes of mixing, pour the grout into the prepared form. Work in a manner to avoid air entrapment. Vibrate the form as required to achieve flow and compaction. Flowable grout must be confined in either the horizontal or vertical direction, leaving a minimum of exposed surface. After the grout has achieved its final set, remove any forms and trim or shape exposed mortar/concrete to the desired profile, if required.


**Cracks:** Within 15 minutes of mixing pour the grout into prepared crack. Continue pouring until the crack has been completely filled.
- C. Wet cure for a minimum of 3 days or apply a curing compound that conforms to ASTM C-309 as approved by the Engineer.
- D. Adhere to all limitation and cautions for the polymer-modified portland cement coating in the manufacturers printed Product Data Sheet (PDS) and literature.

### 3.02 Cleaning


- A. The uncured polymer-modified portland cement mortar can be cleaned from tools with water. The cured polymer modified portland cement mortar can only be removed mechanically.
- B. Leave finished work and work area in a neat, clean condition without evidence of spillovers onto adjacent areas.

# SikaGrout®-212 Form and Pump

1. Pre-wet surface to SSD.
2. Apply release agent to form or use plastic lined plywood.
3. Run bead of Sikaflex 1a around edge of form to prevent leakage, let cure, then anchor form. Fill with water to check for water tightness. Let drain to no free standing water.
4. Pump SikaGrout-212 with a variable pressure pump. Continue pumping until a 3 to 5 psi increase in normal line pressure is evident then STOP pumping. Form should not deflect.
5. Vibrate form while pumping.
6. Vent to be capped when steady flow is evident.
7. Strip form when appropriate
8. Dry pack anchor holes with SikaGrout-212.



# SikaGrout®-212 Crack Filler



1. Pre-wet surface to SSD.
2. Apply release agent to form or use plastic lined plywood.
3. Run bead of Sikaflex-1a around edge of form to prevent leakage, let cure, then anchor form.
4. Pump SikaGrout-212 with a variable pressure pump. Continue pumping until grout flow is evident at an adjacent port.
5. Cap off original port when steady flow is evident, move to adjacent port and continue pumping procedure until all injectable cracks have been filled.
6. Strip form when appropriate.
7. Dry pack anchor holes with SikaGrout-212.

**Concrete Restoration Systems by Sika Corporation, 201 Polito Avenue, Lyndhurst, NJ 07071**

The preceding specifications are provided by Sika Corporation as a guide for informational purposes only and are not intended to replace sound engineering practice and judgment and should not be relied upon for that purpose. Sika Corporation makes no warranty of any kind, either express or implied, as to the accuracy, completeness or the contents of these guide specifications. Sika Corporation assumes no liability with respect to the provision or use of these guide specifications, nor shall any legal relationship be created by, or arise from, the provision of such specifications. SIKA SHALL NOT BE RESPONSIBLE UNDER ANY LEGAL THEORY TO ANY THIRD PARTY FOR ANY DIRECT OR CONSEQUENTIAL DAMAGES OF ANY KIND ARISING FROM THE USE OF THESE GUIDE SPECIFICATIONS. The specifier, architect, engineer or design professional or contractor for a particular project bears the sole responsibility for the preparation and approval of the specifications and determining their suitability for a particular project or application.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at <http://usa.sika.com/> or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.