

PRODUCT DATA SHEET

Sarnacol®-2175

Spray applied, canister flashing membrane adhesive

PRODUCT DESCRIPTION

Sarnacol® 2175 membrane adhesive is a spray applied, canister adhesive used to bond Sarnafil® or Sikaplan® flashing membrane to approved substrates.

USES

Uniquely formulated to be compatible with Sarnafil and Sikaplan membranes.

AREAS OF APPLICATION

Approved Substrates

- Plywood
- Concrete
- Concrete Block
- Metal
- Polyisocyanurate Insulations
- High Density Polyisocyanurate Roof Boards
- Gypsum Cover Boards
- Certain SBS Modified Bitumen Membranes

CHARACTERISTICS / ADVANTAGES

- Compatible with Sarnafil and Sikaplan membranes
- Self-contained, portable spray system for fast application and minimal cleanup
- Quick drying
- Low VOC

PRODUCT INFORMATION

Chemical Base	Liquid
Packaging	Canister in carton, 40 lbs (18.14 kg), 36 cartons per pallet
Appearance / Color	Blue
Shelf Life	12 months if stored properly in original unopened, sealed and undamaged packaging.
Storage Conditions	Store canisters between 60°F (16°C) and 90°F (32°C). Do not store in direct sunlight. Contents are flammable. Store in accordance with local, state, and federal regulations.
Volatile organic compound (VOC) content	191 g/L 96 g/L with exempt solvents

APPLICATION INFORMATION

Coverage	Typical coverage rate for a canister is 500 – 700 ft ² (46 – 65 m ²) of bonded membrane. Application rate may vary depending on spray pattern, surface roughness and porosity.
----------	---

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

AVAILABILITY/WARRANTY

AVAILABILITY

From Sika Corporation – Roofing Authorized Applicators for use within Sarnafil or Sikaplan systems.

WARRANTY

Upon successful completion of the installed roof by the Sika Authorized Applicator, Sika Corporation will provide a warranty to the Building Owner via the Sika Authorized Applicator.

LIMITATIONS

Precautions should be taken to prevent odors and/or vapors from entering the building/structure, including but not limited to turning off and sealing air intake vents or other means of ingress for odors and/or vapors into the building/structure during product application and cure.

- Do not apply in wet weather or to a wet surface.
- The minimum ambient temperature is 40°F (4°C) and rising.
- The canister temperature must be above 65°F (18°C) during application.
- Do not heat the canister above 100°F (38°C).

- Apply using the Sarnacol 2175 spray gun, spray hose and spray tip.
- Avoid ignition source.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

GENERAL

Apply Sarnacol 2175 in ambient temperatures of 40°F (4°C) and rising provided the canister temperature is above 65°F (18°C) during application. The spray pattern will become inconsistent and begin to spit rather than spray when the adhesive temperature drops below 65°F (18°C).

Utilize power-heated blankets or hot boxes when necessary to keep the canisters warm. Power-heated blankets will keep the canisters warm but are not intended to heat cold canisters. Never use band heaters or any device capable of heating the canisters above 100°F (38°C) as these devices may cause explosion or personal injury.

Always keep the canister in an upright position. The dip

tube inside the canister extends to the bottom of the canister. Attempting to dispense the adhesive when the canister is on its side or upside down will release only the propellant. The loss of propellant will significantly reduce the spray pattern, coverage rates and overall yield.

Protect the membrane and adjacent surfaces from overspray.

ACCESSORIES

The following accessories are sold separately.

Sarnacol 2175 Spray Gun – Part #679513 (includes 2 ft spray wand and spray tip)

Sarnacol 2175 Spray Hose – Part #679516 (12 ft), #679515 (18 ft)

Sarnacol 2175 Spray Tips – Part #679514 (9502E)

Sarnacol 2175 Cleaner – Part #679512

SUBSTRATE PREPARATION

All surfaces must be clean, dry, and free of dirt, grease, oil, or other contaminants or particulates.

APPLICATION

1. Shake the canister to agitate contents that may have settled.
2. Connect the spray hose to the spray gun.
3. Connect the other end of the spray hose to the canister valve outlet. Use caution not to strip threads or overtighten the connection.
4. Close the adjustment wheel behind the spray gun trigger to prevent accidental spray.
5. Open the canister valve to pressurize the spray hose and keep the adhesive in a fluid state. Do not close the canister valve until the canister is empty. If the canister valve is closed before the canister is empty, the adhesive will dry and clog the spray hose and spray gun. If the canister valve must be closed, close the valve and clean the spray hose and spray gun with Sarnacol 2175 Cleaner. Refer to the Sarnacol 2175 Cleaner product data sheet for instructions.
6. Set the canister in an upright position and open the adjustment wheel behind the spray gun trigger. Hold the spray gun approximately 12" (30.5 cm) from and perpendicular (90 degrees) to the substrate. Press the spray gun trigger and spray the adhesive onto the membrane and substrate in a continuous, uniform pattern with a 50% overlap avoiding any globs or puddles.
7. Orient the membrane spray pattern so it is perpendicular (90 degrees) to the substrate spray pattern. Adjust the width of the spray pattern by opening or closing the adjustment wheel behind the spray gun trigger. Porous substrates may require an additional pass of adhesive to provide enough "layup" on the surface to properly bond to the membrane to the substrate.
8. Do not apply the adhesive to the membrane seam areas. Immediately clean any overspray in the lap area with Sarnacol 2175 Cleaner or acetone.
9. Allow the coated surfaces to dry. The adhesive typically dries in 3-5 minutes. The adhesive is dry when there is no wet transfer of adhesive and the adhesive is not tacky. The maximum open time after the adhesive has dried is 30 minutes. After 30 minutes, reapply a light coat of adhesive to the surfaces following Steps 6 through 8 above.
10. Set the membrane to the substrate as soon as the adhesive is dry. The longer the coated surfaces are open after drying, the more pressure is required to achieve adequate bonds. Smooth the membrane with hand pressure to ensure there are no wrinkles or air pockets. Roll the entire membrane with a clean roller applying uniform pressure to achieve maximum contact. Any area that does not receive adequate pressure may yield a false bond.
11. Check the adhesion of the membrane to the substrate by peeling back the edge of the membrane. The adhesive should not release from either surface. An acceptable initial bond will exhibit 'legging' or 'stringing' of adhesive from both surfaces.
12. When the canister is empty, close the canister valve and press the spray gun trigger to relieve pressure from the spray hose. Disconnect the spray hose from the canister and quickly connect it to a new canister. Repeat Steps 5 through 11 above.

CLEAN UP

Clean the spray hose and spray gun with Sarnacol 2175 Cleaner. Refer to the Sarnacol 2175 Cleaner product data sheet for instructions.

Spray tips can be soaked separately in Sarnacol 2175 Cleaner, MEK, MEK Substitute or acetone. Use a small gauge wire or torch clean-out tool to remove clogs.

DISPOSAL OF EMPTY CANISTER

1. When the canister is empty, close the canister valve and press the spray gun trigger to relieve pressure from the spray hose.
2. Disconnect the spray hose from the canister.
3. Place the canister in an upright position and point the canister valve into a suitable waste container. Slowly open the canister valve to exhaust any remaining propellant and adhesive.
4. Mark the canister "empty". Keep the canister valve open and allow it to sit in an upright position for at least one hour to fully exhaust the pressure.
5. Puncture the rupture disc on the side of the canister using a brass punch and hammer.
6. Recycle or dispose the empty canister in accordance with all applicable local, state, and federal regulations.

MAINTENANCE

Standard maintenance of Sarnafil and Sikaplan systems should include regular inspections of flashings, drains and termination sealants at least twice a year and after each storm.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Sarnafil

100 Dan Road
Canton, MA 02021
Phone: +1 800-451-2504
Fax: +1 781-828-5365
usa.sika.com/sarnafil
webmaster.sarnafil@us.sika.com

Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet

Sarnacol®-2175
June 2021, Version 03.01
02094507200000053

Sarnacol-2175-en-US-(06-2021)-3-1.pdf

