

PRODUCT DATA SHEET

Sikadur[®]-32 Hi-Mod

HIGH-MODULUS, HIGH-STRENGTH, EPOXY BONDING/GROUTING ADHESIVE

PRODUCT DESCRIPTION

Sikadur[®]-32 Hi-Mod is a multi-purpose, 2-component, 100 % solids, moisture-tolerant structural epoxy adhesive. It conforms to the current ASTM C-881 Types I, II, and V, Grade 2, Class C and AASHTO M-235 specifications.

USES

Sikadur[®]-32 Hi-Mod may only be used by experienced professionals.

- Bond fresh, plastic concrete to hardened concrete and steel.
- Grout horizontal cracks in structural concrete and wood by gravity feed.
- Machinery and 'robotic' base-plate grout.
- Structural adhesive for concrete, masonry, metal, wood, etc

CHARACTERISTICS / ADVANTAGES

- High-strength bonding/grouting adhesive.
- Tolerant to moisture before, during and after cure.
- Excellent adhesion to most structural materials.
- Convenient easy-to-mix ratio A:B = 1:1 by volume.
- Easy-to-use for bonding/grouting applications.
- Fast initial set; rapid gain to ultimate strengths.
- USDA-certified for use in food plants.

PRODUCT INFORMATION

Chemical Base	100 % epoxy	
Packaging	1, 2 and 4 gal. units	
Color	Concrete gray	
Shelf Life	2 years in original, unopened containers	
Storage Conditions	Store dry at 40–95 °F (4–35 °C). Condition material to 65–75 °F (18–24 °C) before using.	
Viscosity	Approximately 4–5,000 cps.	
Water Absorption	0.21 % (7 days, 24 h immersion)	(ASTM D-570) 73 °F (23 °C) 50 % R.H.

TECHNICAL INFORMATION

Compressive Strength	40 °F*	73 °F*	90 °F*	(ASTM D-695)
	(4 °C)	(23 °C)	(32 °C)	
8 hour	-	140 (1.0)	1,700 (11.7)	
16 hour	-	4,800 (33.1)	7,300 (50.3)	
1 day	30.0 (0.2)	5,700 (39.3)	7,300 (50.3)	
3 day	5,300 (36.6)	11,300 (77.9)	10,400(71.7)	
7 day	9,600 (66.2)	11,800 (81.4)	10,400(71.7)	
14 day	11,900 (82.1)	12,200 (84.1)	10,400(71.7)	
28 day	12,600 (86.9)	12,200 (84.1)	10,500(72.4)	

*Material cured and tested at the temperatures indicated.

Modulus of Elasticity in Compression	2.1 x 10 ⁶ psi (1,449 MPa) (7 days)	(ASTM D-695) 73 °F (23 °C) 50 % R.H.														
Flexural Strength	7,000 psi (48.3 MPa) (14 day)	(ASTM D-790) 73 °F (23 °C) 50 % R.H.														
Modulus of Elasticity in Flexure	6.0 x 10 ⁵ psi (4,800 MPa) (14 day)	(ASTM D-790) 73 °F (23 °C) 50 % R.H.														
Tensile Strength	6,900 psi (48 MPa) (7 days)	(ASTM D-638) 73 °F (23 °C) 50 % R.H.														
Tensile Modulus of Elasticity	5.4 x 10 ⁵ psi (3,726 MPa) (14 days)	(ASTM D-638) 73 °F (23 °C) 50 % R.H.														
Elongation at Break	1.9 % (7 days)	(ASTM D-638) 73 °F (23 °C) 50 % R.H.														
Tensile Adhesion Strength	<table border="1"> <tbody> <tr> <td rowspan="3">2 day (moist cure)</td> <td>Plastic Concrete to Hardened Concrete</td> <td>1,700 psi (11.7 MPa)</td> <td rowspan="6">(ASTM C-882) 73 °F (23 °C) 50 % R.H.</td> </tr> <tr> <td>Hardened Concrete to Hardened Concrete</td> <td>2,000 psi (13.8 MPa)</td> </tr> <tr> <td>Hardened Concrete to Steel</td> <td>1,900 psi (13.1 MPa)</td> </tr> <tr> <td rowspan="3">14 day (moist cure)</td> <td>Plastic Concrete to Hardened Concrete</td> <td>2,200 psi (15.1 MPa)</td> </tr> <tr> <td>Hardened Concrete to Hardened Concrete</td> <td>2,000 psi (13.8 MPa)</td> </tr> <tr> <td>Hardened Concrete to Steel</td> <td>2,000 psi (13.8 MPa)</td> </tr> </tbody> </table>	2 day (moist cure)	Plastic Concrete to Hardened Concrete	1,700 psi (11.7 MPa)	(ASTM C-882) 73 °F (23 °C) 50 % R.H.	Hardened Concrete to Hardened Concrete	2,000 psi (13.8 MPa)	Hardened Concrete to Steel	1,900 psi (13.1 MPa)	14 day (moist cure)	Plastic Concrete to Hardened Concrete	2,200 psi (15.1 MPa)	Hardened Concrete to Hardened Concrete	2,000 psi (13.8 MPa)	Hardened Concrete to Steel	2,000 psi (13.8 MPa)
2 day (moist cure)	Plastic Concrete to Hardened Concrete		1,700 psi (11.7 MPa)	(ASTM C-882) 73 °F (23 °C) 50 % R.H.												
	Hardened Concrete to Hardened Concrete		2,000 psi (13.8 MPa)													
	Hardened Concrete to Steel	1,900 psi (13.1 MPa)														
14 day (moist cure)	Plastic Concrete to Hardened Concrete	2,200 psi (15.1 MPa)														
	Hardened Concrete to Hardened Concrete	2,000 psi (13.8 MPa)														
	Hardened Concrete to Steel	2,000 psi (13.8 MPa)														
Shear Strength	6,200 psi (43 MPa) (14 days)	(ASTM D-732) 73 °F (23 °C) 50 % R.H.														
Heat Deflection Temperature	[fiber stress loading 264 psi (1.8 MPa)] 122 °F (50 °C) (7 days)	(ASTM D-648)														

APPLICATION INFORMATION

Mixing Ratio	Component 'A': Component 'B' = 1:1 by volume
Coverage	Bonding Adhesive: 1 gal. covers approximately 80 ft ² on smooth surface. Base Plate Grout: 1 gal. mixed with 1.5 parts oven-dried aggregate by loose volume yields approximately 420 in ³ of grout. Anchoring Grout: 1 gal. yields 231 in ³ of grout.
Product Temperature	Condition material to 65°-75°F (18°-24°C) before using.
Ambient Air Temperature	Minimum ambient temperature 40°F (4°C).
Substrate Temperature	Minimum substrate temperature 40°F (4°C).
Pot Life	Approximately 30 minutes. (60 gram mass) Approximately 22 minutes. (350 gram mass)
Contact Time	40 °F (4 °C)*: 15–16 h 73 °F (23 °C)*: 2–2.5 h 90 °F (32 °C)*: 1.5–2 h <small>*Material cured and tested at the temperatures indicated.</small>

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Surface must be clean and sound. It may be dry or damp, but free of standing water. Remove dust, laitance, grease, curing compounds, impregnations, waxes and any other contaminants.

SUBSTRATE PREPARATION

Concrete - Should be cleaned and prepared to achieve a laitance and contaminant free, open textured surface by blast cleaning or other equivalent mechanical means.
Steel - Should be cleaned and prepared thoroughly by blast cleaning or other equivalent mechanical means.

MIXING

Pre-mix each component. Proportion equal parts by volume of Component 'A' and Component 'B' into clean pail. Mix thoroughly for 3 minutes with Sika paddle on low-speed (400-600 rpm) drill until blend is a uniform color. Mix only that quantity that can be applied within its pot life.

APPLICATION METHOD / TOOLS

To bond fresh concrete to hardened concrete - Apply by brush, roller, broom or spray. Place fresh concrete while Sikadur® 32, Hi-Mod, is still tacky. If coating becomes glossy and loses tackiness, remove any surface contaminants then recoat with additional Sikadur® 32 Hi-Mod, and proceed.

To grout baseplates - Add up to 1 1/2 parts of oven-dried aggregate to 1 part of mixed Sikadur® 32, Hi-Mod, by volume. Place grout under baseplate. Avoid contact with the underside of the plate. A 1/4 to 3/8 in. (6 to 10 mm) space should remain between the top of the grout and the bottom of the plate.

Maximum thickness of grout per lift is 1.5 in. (38 mm) If multiple lifts are needed, allow preceding layer to cool to

touch before applying additional layer. The remaining 1/4 to 3/8 in. (6 to 10 mm) space should be filled with neat Sikadur® 32 Hi-Mod. Pour a sufficient quantity of neat epoxy to allow the level to rise slightly higher than the underside of the bearing plate.

To gravity feed cracks - Pour neat material into vee-notched crack. Continue placement until completely filled.

Seal underside of slab prior to filling if cracks reflect through.

LIMITATIONS

- For spray applications, consult Technical Service at 800-933-7452.
- Use only oven-dry aggregate.
- Material is a vapor barrier after cure.
- For applications on exterior, on-grade substrates, consult Technical Services at 800-933-7452.
- Do not apply over wet, glistening surface.
- Not an aesthetic product. Color may alter due to variations in lighting and/or UV exposure.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LOCAL RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the cur-

rent actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

KEEP CONTAINER TIGHTLY CLOSED •KEEP OUT OF REACH OF CHILDREN •NOT FOR INTERNAL CONSUMPTION •FOR INDUSTRIAL USE ONLY •FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.** Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 201-933-8300.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet
Sikadur®-32 Hi-Mod
October 2018, Version 01.01
020204030010000129

Sikadur-32Hi-Mod-en-US-(10-2018)-1-1.pdf

BUILDING TRUST

