



# PRODUCT DATA SHEET

## SCOFIELD® Cure Seal 350

### SOLVENT-BASED NON-YELLOWING, CURING, AND SEALING COMPOUND

#### PRODUCT DESCRIPTION

SCOFIELD® Cure Seal 350 is a solvent-based non-yellowing, curing, and sealing compound for newly poured and existing concrete surfaces. SCOFIELD® Cure Seal 350 is formulated for use in regions that require 350 g/L VOC. The product is formulated for curing and sealing uncolored concrete, integrally colored concrete, color hardened (shake-on) concrete, stamped or stenciled concrete, and cementitious overlays. It is recommended for use with CHROMIX® Admixtures for Color-Conditioned® Concrete, SCOFIELD® Integral Color SG, LITHOCHROME® Color Hardener, LITHOCHROME® Chemstain® Classic, and SCOFIELD® Texturetop®. It is suitable for residential or commercial projects, exterior hardscapes, and vertical surfaces.

SCOFIELD® Cure Seal 350 visually enhances the concrete color, protects the surface from dirt and staining, and minimizes the effects of de-icing salts and exposure to gas or oil. It is well suited for application to cured concrete to prevent absorption or penetration of many fats, oils, greases, aliphatic solvents, salts, acids, and other chemicals. By preventing penetration of these compounds, SCOFIELD® Cure Seal 350 provides good economical protection for exterior concrete surfaces, thereby reducing maintenance costs. As a curing compound, it improves the surface strength, abrasion resistance, and durability of the concrete, and reduces the potential for plastic cracking. It forms a moisture barrier that prevents free lime in the concrete from migrating and reacting at the surface, forming a dust residue. Curing with SCOFIELD® Cure Seal 350 also provides interim construction protection from most oils, greases, chemical spills, and from the adhesion of mortar splashes. Final cleanup costs are reduced and the resulting concrete surface appearance is greatly

enhanced. SCOFIELD® Cure Seal 350 can also be applied to old concrete, cementitious terrazzo, and cementitious brick to dust proof and impart stain and chemical resistance.

#### USES

Formulated for curing and sealing uncolored concrete, integrally colored concrete, color hardened (shake-on) concrete, stamped or stenciled concrete, and cementitious overlays.

#### CHARACTERISTICS / ADVANTAGES

SCOFIELD® Cure Seal 350 visually enhances the concrete color, protects the surface from dirt and staining, and minimizes the effects of de-icing salts and exposure to gas or oil.

#### APPROVALS / STANDARDS

SCOFIELD® Cure Seal 350 is a Methacrylate Acrylic copolymer specifically designed to meet the moisture retention properties of AASHTO M 148, ASTM C309, ASTM C1315, when applied at the recommended coverage rate. It is a clear liquid (25 % solids by weight), which dries to a gloss, breathable, UV resistant film. SCOFIELD® Cure Seal 350 complies with most VOC (350 g/L) requirements and other Federal and State Air Quality Regulations. The longevity of SCOFIELD® Cure Seal 350 depends upon the dried film thickness, exposure, and use conditions. Clear sealers will scratch and scuff, and will require maintenance. Treated surfaces are readily recoated with adequate cleaning.

## PRODUCT INFORMATION

<b>Packaging</b>	1-gallon (3.8L) cans or 5-gallon (18.9L) pails.
<b>Shelf Life</b>	Two years from date of manufacture in original, unopened container.
<b>Storage Conditions</b>	Store in well ventilated area, away from heat sources.

## APPLICATION INFORMATION

<b>Coverage</b>	<p>Coverage rates vary with surface texture and porosity, ambient and surface temperatures and method of application. The following coverage rates are approximate for broom finish concrete surfaces:</p> <p>Curing: 300 ft<sup>2</sup>/gal (7.4 m<sup>2</sup>/L) Sealing: 300-400 ft<sup>2</sup>/gal (7.4-9.8 m<sup>2</sup>/L)</p> <p>Avoid excessive build-up, particularly in the depressed textures and grout joints of stamped or stenciled concrete, hand tooled or saw cut joints. Thicker applications may lead to discoloration, peeling, and diminished sealer performance. Wipe up or brush out excessive material before the film becomes tacky.</p>
<b>Waiting / Recoat Times</b>	<p>Drying times will vary depending upon wet film thickness, surface texture and porosity, ambient and surface temperatures, humidity, and if the product is being used as a cure coat or a seal coat. At 70 °F, approximate dry times: Tack free: 1 hour Light foot traffic: 6 hours Light car traffic: 24 hours Normal car traffic: 72 hours.</p>

## APPLICATION INSTRUCTIONS

### APPLICATION

SCOFIELD® Cure Seal 350 may be applied using a roller, airless sprayer, or hand pump industrial sprayer made for solvent based sealer and capable of delivering moderately viscous liquids in thin even layers. If roller is to be used, apply only enough material so that it may be rolled prior to the sealer becoming tacky. Do not attempt to roll the material once it has become tacky. Also if using a roller, a non-shed solvent resistant roller with 1/4"–1/2" nap length is recommended. The nap length of the roller will depend on the surface porosity and texture of the concrete. Best results are obtained when product is applied at ambient and substrate temperatures are between 50–85 °F, (10–29.4 °C). Do not apply at or below 50 °F (10 °C) or when such temperatures are expected within 72 hours following application. Do not apply if there are concerns with the quality of the color or finish of the concrete, until those concerns are adequately addressed. When using a sprayer, apply material with a fan pattern nozzle. Spray equipment should be clean and in good working condition. Sprayer seals must be solvent resistant. SCOFIELD® Cure Seal 350 should be applied in two thin even coats for best results. Care must be taken to protect adjacent areas from over spray.

### New Concrete

Apply SCOFIELD® Cure Seal 350 as a curing agent immediately following final finishing and after the slab is

firm enough to walk on without damage. Do not apply if any moisture is present on the surface. Avoid runs or puddles and over application. To achieve maximum sealing and dustproofing benefits, a second application should be made at least two weeks after the cure coat application. Surfaces to be retreated should be dry and clean. Apply in a continuous wet surface film. Application of product over excessively smooth, hard-troweled surfaces may result in adhesion loss.

### Colored Stamped or Stenciled Concrete

After concrete has been stamped using a liquid or powder release agent allow the concrete to cure for a minimum of 24 hours, before the washing procedure begins. Thoroughly remove the residual release powder or liquid release by washing and scrubbing. After cleaning and rinsing, allow the concrete to dry for a minimum of 24 hours before beginning the sealing process. The concrete must be thoroughly dry before applying SCOFIELD® Cure Seal 350. Read the LITHOCHROME® Antiquing Release and the LITHOTEX® Liquid Release Technical Data Sheets before applying products. All information is available for download online at [www.scofield.com](http://www.scofield.com).

Before application of sealer the Moisture Vapor Emission Rate (MVER) of the concrete or cementitious topping must be measured and be less than 5 pounds per 1000 square feet per 24 hours (2.27 kg/92.9 m<sup>2</sup> per 24 hours). Promptly clean application equipment with xylene following use. Handle and dispose of cleaning residue properly.

### Existing Concrete

Adequately remove accumulations of grease, oil residue, incompatible curing, or sealing compound residue and other substances that would diminish adhesion. Wash surfaces thoroughly. Allow surface and joints to adequately dry before applying SCOFIELD® Cure Seal 350. Very rough, porous and deeply textured surfaces may require multiple applications to ensure the formation of a protective film, without pinholes or holidays. Before application of sealer the Moisture Vapor Emission Rate (MVER) of the concrete or cementitious topping must be measured and be less than 5 pounds per 1000 square feet per 24 hours (2.27 kg/92.9 m<sup>2</sup> / 24 hours). Promptly clean application equipment with xylene following use. Handle and dispose of cleaning residue properly.

### No Gloss Finish

SCOFIELD® Cure Seal 350 can be modified in the field to reduce the surface shine of the dried film with SCOFIELD® Matte Finish Additive. It is a solvent-based silica paste that is added directly to the sealer. Shelf life for SCOFIELD® Matte Finish Additive is 1 year, when stored in original, unopened containers, in dry storage, between 60–80 °F. Do not use material that has been frozen. Add the contents of the one-quart (0.95 L) container to 5 gallons (18.93 L) of sealer. Do not thin or alter with any chemical. Mix thoroughly with a drill mounted mixer. Do not introduce air bubbles into sealer by excessive high speed mixing. Once SCOFIELD® Matte Finish Additive is added to the sealer; remix periodically during the application and before each use of the mixed products.

## MAINTENANCE

Periodically inspect cured and sealed surfaces for wear or damage. All concrete curing and sealing compounds will eventually exhibit the effects of weathering and traffic. For maximum coating life and performance, wipe up all chemical solvent or petroleum spills as soon as possible. Remove abrasive debris by sweeping or vacuuming. Do not drag, drop or place sharp edges on sealed surfaces. Periodic washings with mild detergents will help maintain surface luster. Do not use solvent or acid based cleaning materials for general cleaning. Hot car tires or turning tires while car is standing may damage the sealer. Surfaces that will be subjected to car traffic, de-icing salts or chemical exposure, must receive minimally, two applications of SCOFIELD® Cure Seal 350. Prior to recoating, the surface and joints must be clean, dry, free from cleaning product residue, other contamination, or loose materials, which will affect the adhesion of SCOFIELD® Cure Seal 350. When recoating, a slip resistant additive must be added to the sealer.

### Quality Control

Cast a job site sample at least 21 days prior to the installation for approval of color and finish. Utilize all materials, tools, and techniques from the actual job in

the mock-up. Consistent batching, pouring, finishing, curing, sealing, and preparation techniques, will ensure the uniformity of architectural concrete. Verify adequate wet and dry slip resistance. Discuss maintenance requirements. Site visits by Scofield personnel are for making technical recommendations only and not for supervising or providing quality control. Maintenance requirements should also be discussed.

## LIMITATIONS

For exterior use only. Do not use on concrete slabs with inadequately drained sub-grade and/or surfaces subject to hydrostatic water pressures. Do not use in swimming pools, fountains or ponds. Do not use on surfaces that will have direct food contact. Do not use for recoating or in conjunction with other floor sealers, treatments, bond breakers, or adhesives without prior test to determine compatibility and adhesion. Do not use to fill or repair cracks in the substrate. If SCOFIELD® Cure Seal 350 is stored in temperatures below 30 °F it will become thick and unusable. Usability can be restored by taking material to warmer temperatures, usually above 60 °F.

Warning: Treated surfaces may be slippery during application prior to drying, and when wet with water or liquids after drying. Concrete should be textured sufficiently to eliminate potential slipping hazards. In addition, use a non-slip additive with the SCOFIELD® Cure Seal 350. Test and confirm that the treated surface is adequately slip resistant prior to opening installation to any traffic.

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## OTHER RESTRICTIONS

See Legal Disclaimer.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION



- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA’s Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

**Sika Corporation**  
201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)

**Sika Mexicana S.A. de C.V.**  
Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



Product Data Sheet  
SCOFIELD® Cure Seal 350  
October 2018, Version 01.01  
020815110020000032

SCOFIELDCureSeal350-en-US-(10-2018)-1-1.pdf

