



Division 3- Concrete
Section 03930 - Concrete Rehabilitation

Part 1 - General

1.01 Summary

This specification describes the patching of interior vertical and overhead surfaces with an epoxy resin adhesive binder.

1.02 Quality Assurance

- A. Manufacturing qualifications: The manufacturer of the specified product shall be ISO 9001/9002 certified and have in existence a recognized ongoing quality assurance program independently audited on a regular basis.
- B. Contractor qualifications: Contractor shall be qualified in the field of concrete repair and protection with a successful track record of 5 years or more. Contractor shall maintain qualified personnel who have received product training by a manufacturer's representative.
- C. Install materials in accordance with all safety and weather conditions required by the manufacturer, or as modified by applicable rules and regulations of local, state and federal authorities having jurisdiction. Consult Material Safety Data Sheets for complete handling recommendations.

1.03 Delivery, Storage, and Handling

- A. All materials must be delivered in original, unopened containers with the manufacturer's name, labels, product identification, and batch numbers. Damaged material must be removed from the site immediately.
- B. Store all materials off the ground and protect from rain, freezing or excessive heat until ready for use.
- C. Condition the specified product as recommended by the manufacturer.

1.04 Job Conditions

- A. Environmental Conditions: Do not apply material if it is raining or snowing or if such conditions appear to be imminent. Minimum application temperature 40°F (5°C) and rising.
- B. Protection: Precautions should be taken to avoid damage to any surface near the work zone due to mixing and handling of the specified product.

1.05 Submittals

- A. Submit two copies of manufacturer's literature, to include: Product Data Sheets, and appropriate Material Safety Data Sheets (MSDS).

1.06 Warranty

- A. Provide a written warranty from the manufacturer against defects of materials for a period of one (1) year, beginning with date of substantial completion of the project.

Part 2 : Products

2.01 Manufacturers

- A. Sikadur 31, Hi-Mod Gel, as manufactured by Sika Corporation, 1682 Marion Williamsport Road, Marion, Ohio 43302, is considered to conform to the requirements of this specification.

2.02 Materials

- A. Epoxy resin adhesive binder:
 - 1. Component “A” shall be a modified epoxy resin of the epichlorohydrin bisphenol A type containing suitable viscosity control agents and pigments. It shall not contain butyl glycidyl ether.
 - 2. Component “B” shall be primarily a reaction product of a selected amine blend with an epoxy resin of the epichlorohydrin bisphenol A type containing suitable viscosity control agents, pigments and accelerators.
 - 3. The ratio of Component “A”: Component “B” shall be 1:1 by volume.
- B. Aggregate for the epoxy resin mortar shall be an oven-dried, 20-40 gradation sand, as approved by the Engineer.

2.03 Performance Criteria

- A. Properties of the mixed epoxy resin adhesive:
 - 1. Pot Life: 60 minutes (500 gram mass) @73F
 - 2. Tack-Free Time to Touch (30 mil thickness): 1.5 – 2.5 hours
 - 3. Consistency: non-sag paste
 - 4. Color: Concrete gray
- B. Properties of the mixed epoxy resin adhesive:
 - 1. Compressive Properties (ASTM D-695) at 28 days
 - a. Compressive Strength: 16,000 psi (110.3 MPa)
 - b. Compressive Modulus: 795,000 psi (5,485 MPa)
 - 2. Tensile Properties (ASTM D-638) at 7 days
 - a. Tensile Strength: 3,300 psi (22.7 MPa)
 - b. Elongation at Break: 0.9%
 - 3. Flexural Properties (ASTM D-790) at 14 days
 - a. Flexural Strength (Modulus of Rupture): 6,100 psi (42 MPa)
 - b. Tangent Modulus of Elasticity in Bending: 1.67×10^6 psi (11,520 MPa)
 - 4. Shear Strength (ASTM D-732) at 14 days: 4,600 psi (31.7 MPa)
 - 5. Total Water Absorption (ASTM D-570) at 7 days: 0.79% (2 hour boil)
 - 6. Bond Strength (ASTM C-882) Hardened Concrete to Hardened Concrete
 - a. 14 day (moist cure): 2,900 psi (20 MPa)
 - 7. Deflection Temperature (ASTM D-648) at 7 days: 135F (fiber stress loading = 264 psi)
 - 8. The epoxy resin adhesive binder shall be approved by the United States Department of Agriculture.

Note: Tests above were performed with material and curing conditions at 73F & 45-55% relative humidity.

Part 3 – Execution

3.01 Mixing and Application


- A. Mixing the epoxy resin adhesive binder: Premix each component. Proportional 2 parts Component “A” to 1 part Component “B” by volume into a clean, dry mixing pail. Mix thoroughly for 3 minutes min. with a jiffy paddle on a low-speed (400-600 rpm) drill. Mix only that quantity of material that can be used within its pot life (25-45 minutes at 73F).
- B. Mixing the epoxy resin mortar: Slowly add 1 part by loose volume of an oven-dried sand to 1 part by volume of the mixed epoxy resin adhesive binder. Continue mixing with the drill and paddle until the sand is uniformly blended.
- C. Placement Procedure: Work the epoxy resin mortar against the side walls of the prepared area, slowly working to the center and finally filling the whole cavity to excess. Strike off and level with a screed. Smooth with a finishing trowel. Occasionally wipe the trowel with a rag dampened with water.
- D. Adhere to all limitations and cautions for the epoxy resin adhesive in the manufacturers current printed literature.

3.02 Cleaning

- A. The uncured epoxy resin adhesive can be cleaned from tools with an approved solvent. The cured epoxy resin adhesive can only be removed mechanically.
- B. Leave finished work and work area in a neat, clean condition without evidence of spillovers onto adjacent areas.

SC-041 Sikadur® 31, Hi-Mod Gel Crack Filler (Vertical / Overhead)

1. Prime prepared substrate with neat Sikadur 31, Hi-Mod Gel epoxy resin adhesive binder.
2. While primer is still tacky fill cavity with Sikadur 31, Hi-Mod Gel epoxy resin mortar. Strike off and level, finishing with a trowel.
3. Seal cured epoxy resin mortar with neat epoxy resin adhesive binder to provide additional moisture and chemical protection.



Note: Maximum application thickness of epoxy resin mortar on exterior substrates not to exceed 1 ½" per lift.

The preceding specifications are provided by Sika Corporation as a guide for informational purposes only and are not intended to replace sound engineering practice and judgment and should not be relied upon for that purpose. **SIKA CORPORATION MAKES NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS OR THE CONTENTS OF THESE GUIDE SPECIFICATIONS.** Sika Corporation assumes no liability with respect to the provision or use of these guide specifications, nor shall any legal relationship be created by, or arise from, the provision of such specifications **SIKA SHALL NOT BE RESPONSIBLE UNDER ANY LEGAL THEORY TO ANY THIRD PARTY FOR ANY DIRECT OR CONSEQUENTIAL DAMAGES OF ANY KIND ARISING FROM THE USE OF THESE GUIDE**

SPECIFICATIONS. The specifier, architect, engineer or design professional or contractor for a particular project bears the sole responsibility for the preparation and approval of the specifications and determining their suitability for a particular project or application.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available at www.sikaconstruction.com or by calling (201) 933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instructions for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use.