

PRODUCT DATA SHEET

Sikafloor®-959 SC

A lithium silicate densifier modified to add water and stain repellent properties to bare, densified, or polished concrete surfaces.

PRODUCT DESCRIPTION

Sikafloor® -959 SC is a reactive lithium silicate densifier modified to add water and stain repellent properties to concrete and other cementitious surfaces. It can be used as a standalone product, or as a cost effective next stage surface treatment that adds water and stain resistant properties to previously densified or polished cementitious surfaces. It is VOC compliant, improves abrasion and scratch resistance, and is suitable for interior or exterior applications. It is not a coating, remains permeable to moisture vapors, and will not yellow, crack, peel, or delaminate from surfaces.

USES

Use full strength without dilution to add water, stain, and abrasion resistance to cementitious surfaces of:

- Interior or exterior floors
- Stairs and walkways
- Terrazzo
- Ground and polished floors
- Cementitious overlays
- Countertops
- Below grade basements

CHARACTERISTICS / ADVANTAGES

- Adds water and stain resistance.
- Low odor, non-yellowing water based formulation.
- Breathable non-film forming surface treatment.
- Bonds directly to cement and aggregate silicates.
- Effectively locks in concrete dyes.
- Hardens and improves scratch resistance.
- Deeply penetrates, and quickly reacts.
- Shortens concrete polishing times.
- UV light stable and weather resistant.
- Cures to a non-toxic, non-flammable surface.
- Apply by brush, roller, spray or mop.

PRODUCT INFORMATION

Chemical Base	0 Voc, Lithium Silicate with proprietary water repellent.
Packaging	5-gallon (18.9 L) pail
Appearance / Color	Clear
Shelf Life	24 months in original unopened container under proper storage conditions. 30 days after opening.

APPLICATION INFORMATION

Coverage	200–400 ft ² /gal (4.9–9.8 m ² /L)		
Cure Time	Ambient & Substrate Temperature	Relative humidity	Time
	70°F (21°C)	50 %	1 hours
*Application rate of 400 sq. ft. per gallon (9.8 m ² /L)			
Waiting / Recoat Times	Dry to touch		

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

Concrete substrate should be at least at 7 days and preferably 28 days old. Concrete surfaces must be dry and clean of all prior sealers, curing compounds oils or other foreign materials that might prevent penetration. If used as first stage densifier or dye lock for concrete polish work, grind to the desired aggregate exposure ending with 80 to 200 grit tools. Use brooms or vacuums to remove all grinding dust, loose concrete laitance, and powders, or the densifier may permanently adhere them to the surface.

Jobsite Test Sections

Verify and approve suitability and appearance by making jobsite test sections prior to general application. Each individual concrete color, finishing technique, densifier, and sealer combination should be verified. Test sections must be of adequate size to be representative and be produced by the same workers who will apply product to the larger job. Test completed systems for wet and dry slip resistance to ensure they are safe. Do not proceed with products, techniques, or finishing systems that do not meet required safety specifications or site owner approval.

APPLICATION

Sikafloor®-959 SC should be used full strength without dilution. Although successful application can be performed with topical applications, the use of brooms, sponges, or mops to work material into substrate pores have proven to produce superior results.

Mixing

Mix until uniform before using.

Coverage

Coverage will depend upon method of application, surface porosity, age, moisture, absorption characteristics and the texture of the concrete. Coverage on flat finished concrete is typically 200–400 ft²/gal (4.9–9.8 m²/L). Old or soft concrete will require more material. Slabs ground to expose hard non absorptive aggregates will take less material.

Equipment

Apply Sikafloor®-959 SC by brush, roller, sponge, mop, or pump-spray application. Use rotary floor scrubbers equipped with brushes or pads to assist with large jobs. Always wear protective clothing and equipment proper for the method of application.

Spray applicator Guidelines

Pump Garden Sprayer: Use conical tip and apply with circular motion. Mask all areas not to be coated to safeguard against splashes, overspray, and runoff from application. Wear all required safety equipment. Take care not to allow tape adhesive to interfere with surfaces to be treated. Surface wet with material will be slippery until dry.

Distribute product with a pump garden sprayer to fully saturate the surface. Surfaces should remain wet 5 to 10 minutes. Work material into the surface with a broom, mop, or sponge to ensure product penetrates into substrate pores and microcracks. Take care not to create lap marks as they cannot be removed once the product has dried. If too much material has been applied, and it is puddled after 30 minutes, dilution and removal with a wet vacuum is recommended.

Recoat Time

When the first application is dry to touch, a second coat can be applied to maximize densification properties. If used as a polishing aid, wet polishing can begin when dry to touch.

Dry Time

Will depend upon the selected coverage rate, penetration into the substrate, and weather conditions. At 70°F (21°C) and 50 % relative humidity with an application rate of 400 sq. ft. per gallon (9.8 m²/L), surfaces should be dry and walkable and ready for the next stage of polishing or rinsing in 1 hour. If surface will not be polished further, or they will be sealed with coating, wash surfaces at this stage with fresh water to remove excess densifier. when completely dry, surface can be returned to service. if sealing wait 24 hours to allow the densifier to cure.

CLEANING OF TOOLS

Clean equipment with warm water and detergent immediately after application.

LIMITATIONS

Sikafloor®- 959 SC is not a membrane forming curing compound and does not conform to ASTM C 309 requirements. It is not a substitute for proper curing procedures.

If residual Sikafloor® -959 SC is allowed to dry on the concrete surface it will leave unsightly deposits that are difficult to remove. The appearance of residue on the concrete surface after completion indicates that the excess Sikafloor® -959 SC was not removed. This residue can only be removed by mechanical means.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet

Sikafloor®-959 SC
February 2020, Version 01.03
020815110010000020

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sikafloor-959SC-en-US-(02-2020)-1-3.pdf

