

## PRODUCT DATA SHEET

# Sarnatherm CG tapered

Rigid closed cell polyisocyanurate insulation board with coated glass facers

### PRODUCT DESCRIPTION

Sarnatherm CG tapered is a sloped, rigid closed cell polyisocyanurate insulation board with coated glass facers, and is suitable for use in new construction and re-roofing with Sarnafil® or Sikaplan® membranes.

### USES

Wherever insulation is required within a conventional roof assembly to achieve specified thermal resistance.

### AREAS OF APPLICATION

- New Roofs
- Recover Roofs
- Mechanically Attached Systems
- Adhered Systems

### CHARACTERISTICS / ADVANTAGES

- Manufactured with no CFCs or HCFCs
- Virtually no GWP (Global Warming Potential)
- Zero ODP (Ozone Depletion Potential)
- Recognized as resistant to mold growth
- Compatible with Sarnafil and Sikaplan membranes
- Improved coverage rates in adhered systems

### APPROVALS / STANDARDS

- ASTM C 1289 Type II, Class 2, Grade 2 (20 psi)
- ASTM C 1289 Type II, Class 2, Grade 3 (25 psi)
- UL 1256, 790, 263
- FM 4450, 4470
- Miami-Dade County
- State of Florida

## PRODUCT INFORMATION

|   |  |                  |                            |
|---|--|------------------|----------------------------|
| <b>Chemical Base</b>  | Polyisocyanurate foam core with coated glass facers  |                  |                            |
| <b>Packaging</b>  | <ul style="list-style-type: none"> <li>▪ 4 ft x 4 ft (1.2 m x 1.2 m)</li> <li>▪ Various Thicknesses</li> </ul>   |                  |                            |
| <b>Shelf Life</b>   | N/A  |                  |                            |
| <b>Storage Conditions</b>   | <p>Factory-applied packaging is intended only for protection during transit. When stored outdoors or on the job site, the insulation should be stacked on pallets at least 4" (102 mm) above ground level and completely covered with a weatherproof covering such as a tarpaulin. The temporary factory-applied packaging should be slit or removed to prevent accumulation of condensation. Refer to PIMA Technical Bulletin 109: <i>Storage and Handling Recommendations for Polyiso Roof Insulation</i>.</p> |                  |                            |
| <b>Thickness</b>  | <b>Thickness</b>   | <b>Slope</b>     | <b>Average LTTR Value*</b> |
|   | 0.5 – 1.0" (12 – 25 mm)  | 1/8" per ft (1%) | 4.3                        |
|   | 1.0 – 1.5" (25 – 38 mm)  | 1/8" per ft (1%) | 7.1                        |
|   | 1.5 – 2.0" (38 – 50 mm)  | 1/8" per ft (1%) | 10.0                       |
|   | 2.0 – 2.5" (50 – 63 mm)  | 1/8" per ft (1%) | 12.9                       |
|   | 0.5 – 1.5" (12 – 38 mm)  | 1/4" per ft (2%) | 5.7                        |
|   | 1.5 – 2.5" (38 – 63 mm)  | 1/4" per ft (2%) | 11.4                       |
|   | 0.5 – 2.5" (12 – 63 mm)  | 1/2" per ft (4%) | 8.6                        |
|   | * LTTR (long term thermal resistance) values are based on ASTM C 1289. Test samples were third-party selected and tested by an accredited material testing laboratory. The LTTR results were reviewed by FM Global and certified by the PIMA Quality Mark Program.   |                  |                            |
| <b>Compressive Strength</b>   | 20 psi (138 kPa)<br>25 psi (172 kPa)   | (ASTM D-1621)    |                            |
| <b>Dimensional Stability</b>  | < 2%   | (ASTM D-2126)    |                            |
| <b>Reaction to Fire</b>   | Flame Spread: 25 – 60*<br>Smoke Development: 50 – 170*   | (ASTM E-84)      |                            |
| * Numerical ratings are not intended to reflect performance under actual fire conditions. Flame spread index of ≤ 75 and smoke development ≤ 450 meet code requirements for foam plastic roof insulation. Codes exempt foam plastic insulation when used in FM 4450 or UL 1256. |  |                  |                            |
| <b>Permeability to Water Vapor</b>  | < 4 perm (229 ng/(Pa·s·m <sup>2</sup> ))   | (ASTM E-96)      |                            |
| <b>Water Absorption</b>   | < 1.5%   | (ASTM C-209)     |                            |
| <b>Service Temperature</b>  | -100 to 250°F (-73 to 121°C)   |                  |                            |

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## AVAILABILITY/WARRANTY

### AVAILABILITY

From Sika Corporation – Roofing Authorized Applicators for use within Sarnafil or Sikaplan systems.

## WARRANTY

Upon successful completion of the installed roof by the Sika Authorized Applicator, Sika Corporation will provide a warranty to the Building Owner via the Sika Authorized Applicator.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using

any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## APPLICATION INSTRUCTIONS

Sarnatherm CG tapered is installed by a Sika Authorized Applicator. Sarnatherm CG tapered may be installed by mechanical-attachment to the roof deck with Sarnafasteners and Sarnaplates, by attachment with Sarnacol Board Adhesive, or by hot asphalt depending on project requirements and specifications. Roof insulation which has become wet or damaged should be removed and replaced with solid, dry insulation. Contact Sika Corporation – Roofing Technical Department regarding alternative methods of attachment.

## MAINTENANCE

Standard maintenance of Sarnafil or Sikaplan systems should include regular inspections of flashings, drains, and termination sealants at least twice a year and after each storm.

## OTHER RESTRICTIONS

See Legal Disclaimer.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA’s Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

### Sika Corporation

201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)

### Sika Sarnafil

100 Dan Road  
Canton, MA 02021  
Phone: +1 800-451-2504  
Fax: +1 781-828-5365  
[usa.sika.com/sarnafil](http://usa.sika.com/sarnafil)  
[webmaster.sarnafil@us.sika.com](mailto:webmaster.sarnafil@us.sika.com)

### Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



### Product Data Sheet

Sarnatherm CG tapered  
April 2021, Version 01.01  
020935012000000010

SarnathermCGtapered-en-US-(04-2021)-1-1.pdf

