

PRODUCT DATA SHEET

SikaWrap® Hex-106 G

BI-DIRECTIONAL GLASS FIBER FABRIC FOR STRUCTURAL STRENGTHENING

PRODUCT DESCRIPTION

SikaWrap® Hex-106 G is a bi-directional (0/90) E-glass fiber fabric. Material is field laminated using Sikadur® 330 or Sikadur® Hex 300 epoxy to form a glass fiber reinforced polymer (GFRP) used to strengthen structural elements.

USES

SikaWrap® Hex-106 G may only be used by experienced professionals.

Load increases

Seismic strengthening of:

- Columns
- Masonry walls

Damage to structural parts

Temporary strengthening

Change in structural system

Design or construction defects

CHARACTERISTICS / ADVANTAGES

- Used for shear, confinement or flexural strengthening
- Flexible, can be wrapped around complex shapes
- Light weight
- Non-corrosive
- Acid resistant
- Low aesthetic impact

APPROVALS / STANDARDS

- Approved by ICC ESR-3288
- IBC 2015 Compliance

PRODUCT INFORMATION

Fiber Type	0 °/90 ° (bi-directional)
Packaging	Rolls: 50 in. (1.3 m) x 450 ft. (137 m)
Shelf Life	10 years in original packaging
Storage Conditions	Store dry at 40–95 °F (4–35 °C)
Dry Fibre Density	0.092 lb./in ³ (2.5 g/cm ³)
Dry Fibre Thickness	0.0025 in. (0.064 mm) each fiber direction
Area Density	9.6 osy (325 gsm) total
Dry Fibre Tensile Strength	330 ksi (2,276 MPa)

Dry Fibre Modulus of Elasticity in Tension 10.5 msi (72.4 GPa)

Dry Fibre Elongation at Break 4.00 %

TECHNICAL INFORMATION

Nominal Ply Thickness	Average Ultimate Value	Design Value	
	-	-	0.007 in. (0.18 mm) each fiber direction
Tensile Strength	Average Ultimate Value	Design Value	(ASTM D-3039)
	76.7 ksi (529 MPa)	65.6 ksi (452 MPa)*	73 °F (23 °C) 50 % R.H.
	* Average ultimate value minus 3 standard deviations		
Tensile Modulus	Average Ultimate Value	Design Value	(ASTM D-3039)
	-	4.24 msi (29.2 GPa)(E _f)	73 °F (23 °C) 50 % R.H.
	* Average ultimate value minus 3 standard deviations		
Tensile % Elongation	Average Ultimate Value	Design Value	(ASTM D-3039)
	1.81 %	1.45 %*	73 °F (23 °C) 50 % R.H.
	* Average ultimate value minus 3 standard deviations		
Tensile Stiffness	Average Ultimate Value	Design Value	(ASTM D-7565)
	-	29.7 kips/in./ply (E _f *A)	73 °F (23 °C) 50 % R.H.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Surface must be clean and sound. It may be dry or damp, but free of standing water and frost. Remove dust, laitance, grease, curing compounds, impregnations, waxes, foreign particles, disintegrated materials, and other bond inhibiting materials from the surface. Consult Sikadur® Hex 300 and Sikadur® 330 technical data sheets for additional information on surface preparation. Existing uneven surfaces must be filled with an appropriate repair mortar. The adhesive strength of the concrete must be verified following surface preparation by random pull-off testing (ASTM D4541) at the discretion of the engineer. Minimum tensile strength, 200 psi (1.4 MPa) with concrete substrate failure.

Preparation Work: Concrete - Blast clean, shotblast or use other approved mechanical means to provide an open roughened texture. In certain applications and at the engineer's discretion, the intimate contact between the substrate and the fabric may be determined to be non-critical. In these cases, a thorough cleaning of the substrate using low pressure sand or water blasting is sufficient.

Mixing

Consult Sikadur® 330 or Sikadur® Hex 300 technical data sheets for information on epoxy resins.

APPLICATION METHOD / TOOLS

SikaWrap® Hex-106 G can be applied using wet or dry lay-up methods.

Dry Lay-Up: Apply the mixed Sikadur® 330 epoxy resin directly onto the substrate at a rate of 40–50 ft²/gal. (32–40 mils), depending on the surface profile. Carefully place the fabric into the resin with gloved hands and smooth out any irregularities or air pockets using a plastic laminating roller. Allow the resin to squeeze out between the rovings of the fabric. If more than one layer of fabric is required apply additional Sikadur® 330 at a rate of 100ft²/gal. (16 mils) and repeat as above. Apply a final coat of Sikadur® 330 to the exposed surface at a rate of 160ft²/gal. (10 mils).

Wet Lay-Up: Seal the prepared concrete surface using Sikadur® Hex 300. Material may be applied by spray, brush or roller. SikaWrap® Hex-106 G can be impregnated using Sikadur® Hex 300 epoxy. For best results, the impregnation process should be accomplished using an automated fabric saturating device. Once saturated, apply fabric to the sealed concrete surface and smooth out any irregularities or air pockets using a plastic laminating roller. If required,

apply additional layers of fabric while epoxy on previous layer is still tacky. Coat the exposed surface of final fabric layer using Sikagard® 670W or Sikagard® 62. For overhead and vertical applications, prime concrete with Sikadur® 330 to improve tack. Installation of SikaWrap® products should be performed only by specially trained approved contractors.

Cutting SikaWrap

Fabric can be cut to appropriate length by using a commercial quality heavy duty scissor. Since dull or worn cutting implements can damage, weaken or fray the fiber their use should be avoided. Consult MSDS for proper handling procedures.

LIMITATIONS

- Design calculations must be made and certified by an independent licensed professional engineer.
- System is a vapor barrier. Concrete should not be encapsulated in areas of freeze/thaw.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

- Design calculations must be made and certified by an independent licensed professional engineer.
- System is a vapor barrier. Concrete should not be encapsulated in areas of freeze/thaw.

LEGAL DISCLAIMER

- **KEEP CONTAINER TIGHTLY CLOSED**
- **KEEP OUT OF REACH OF CHILDREN**
- **NOT FOR INTERNAL CONSUMPTION**
- **FOR INDUSTRIAL USE ONLY**
- **FOR PROFESSIONAL USE ONLY**

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA’s Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.



Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet
SikaWrap® Hex-106 G
November 2018, Version 01.01
020206020020000005

SikaWrapHex-106G-en-US-(11-2018)-1-1.pdf

