

# PRODUCT DATA SHEET

## SikaRepair<sup>®</sup> SHB

ONE COMPONENT, CEMENTITIOUS REPAIR MORTAR WITH SUPERIOR HIGH BUILD PROPERTIES THAT MAY BE HAND APPLIED OR WET-SPRAYED

### PRODUCT DESCRIPTION

SikaRepair<sup>®</sup> SHB is a one-component, cementitious ready to use repair mortar. It is a multi-purpose mortar which can be applied by trowel or low pressure wet spray process. The incorporation of low density aggregates allows high build applications on vertical and overhead surfaces. SikaLatex<sup>®</sup> R or SikaLatex<sup>®</sup> may be used instead of water for a two component, polymer-modified repair mortar.

### USES

- Fast repairs to overhead and vertical concrete on mortar surfaces on grade, above and below grade
- As a repair material for building facades, parking structures, industrial plants, bridges, etc.

### CHARACTERISTICS / ADVANTAGES

- Time/labor-saving material; application up to 3" (76 mm) on vertical surfaces in one layer
- Application by hand or low pressure wet spray method
- Easy to use; just add water
- High bond strength ensures excellent adhesion
- Good, early and ultimate strength
- Increased freeze/thaw durability and resistance to deicing salts
- Easy to clean
- Suitable for exterior and interior applications

### PRODUCT INFORMATION

<b>Packaging</b>	SikaRepair <sup>®</sup> SHB: 50 lb. (22.7 kg) bag SikaLatex <sup>®</sup> (R): 1 gal. (3.8 L) plastic jug and 5 gal. (19 L) pail
<b>Appearance / Color</b>	Gray powder
<b>Shelf Life</b>	12 months from date of production if stored properly in original, unopened and undamaged sealed packaging
<b>Storage Conditions</b>	Store dry at 40–95 °F (4–35 °C). Protect from moisture. If damp, discard material

## TECHNICAL INFORMATION

Compressive Strength		Water	SikaLatex® R	(ASTM C-109) 73 °F (23 °C) 50 % R.H.
	1 day		2,500 psi (17.2MPa)	
28 days		5,000 psi (34.5 MPa)	5,000 psi (34.5 MPa)	

  

Flexural Strength		Water	SikaLatex® R	(ASTM C-293) 73 °F (23 °C) 50 % R.H.
	28 days		800 psi (5.5 MPa)	

  

Slant Shear Strength		Water	SikaLatex® R	(ASTM C-882 modified)*
	28 days		1,000 psi (6.9 MPa)	

\* Mortar scrubbed into substrate at 73 °F (23 °C) and 50 % R.H.

## APPLICATION INFORMATION

Mixing Ratio	3/4 - 1 gal. (2.8 - 3.8 L) of liquid			
Fresh Mortar Density	106 lbs./ft <sup>3</sup> (1.70 kg/l)	(ASTM C-138)		
Coverage	0.55 ft <sup>3</sup> (0.02 m <sup>3</sup> ) per bag (Coverage figures do not include allowance for surface profile and porosity or material waste)			
Layer Thickness		Min.	Max. overhead	Max. vertical
	Water	1/4" (6 mm)	1.5" (38 mm)	3" (75 mm)
SikaLatex® R	1/8" (3 mm)	1.5" (38 mm)	3" (75 mm)	
Product Temperature	65–75 °F (18–24 °C)			
Ambient Air Temperature	> 45 °F (7 °C)			
Substrate Temperature	> 45 °F (7 °C)			
Pot Life	~ 30 minutes As the temperature will affect the pot life, application temperature: ▪ Above 73 °F (23 °C) will reduce the pot life and workability ▪ Below 73 °F (23 °C) will extend the pot life and workability			
Set Time	2–3 hours	(ASTM C-266)		

# APPLICATION INSTRUCTIONS

## SURFACE PREPARATION

### Surface preparation

- Surface must be clean and sound. Remove all deteriorated concrete, dirt, oil, grease, and other bond-inhibiting materials from the area to be repaired.
- Preparation work should be done by high pressure water blast, scabber or other appropriate mechanical means to obtain an exposed aggregate surface profile of  $\pm 1/16"$  (1.6 mm) (CSP-5).
- To ensure optimum repair results, the effectiveness of decontamination and preparation should be assessed by a pull-off test.
- Saw cutting of edges is preferred and a dovetail is recommended.
- Substrate should be Saturated Surface Dry (SSD) with clean water prior to application. No standing water should remain during application.

### Priming

- **Reinforcing steel:** Steel reinforcement should be thoroughly prepared by mechanical cleaning to remove all traces of rust. Where corrosion has occurred due to the presence of chlorides, the steel should be high pressure washed with clean water after mechanical cleaning. For priming of reinforcing steel use Sika® Armatec® 110 EpoCem (consult PDS).
- **Concrete Substrate:** Prime the prepared substrate with a brush or sprayed applied coat of Sika® Armatec® 110 EpoCem (consult PDS). Alternately, a scrub coat of SikaRepair® SHB can be applied prior to placement of the mortar. The repair mortar has to be applied into the wet scrub coat before it dries.

## MIXING

- **With water:** Start with 3/4 gal. (2.8 L) of water added to the mixing vessel. Add 1 bag of SikaRepair® SHB while continuing to mix with a low-speed drill (400-600 rpm) and mixing paddle or in an appropriate mortar mixer. Add up to another 1/4 gal (1 L) of water to achieve desired consistency. Do not over-water.
- **With SikaLatex® R:** Pour 3/4 gal. (2.8 L) of SikaLatex® R into the mixing container. Slowly add powder, mix and adjust as above.
- **With diluted SikaLatex® R:** SikaLatex® R may be diluted up to 5:1 (water: SikaLatex® R) for projects requiring minimal polymer modification. Pour 3/4 gal. (2.8 L) of the mixture into the mixing container. Slowly add powder, mix and adjust as above.

## APPLICATION

### By hand

- The mixed SikaRepair® SHB must be worked well into the primed substrate, filling all pores and voids. Compact well. Force material against edge of repair working towards the center. Thoroughly compact the mortar around exposed reinforcement.
- After filling repair, consolidate, then screed.
- Finish with steel, wood, plastic floats, or damp sponges, depending on the desired surface texture.
- Where multiple lifts are required, score top surface on each lift to produce a roughened substrate for next lift. Allow preceding lift to harden before applying fresh material. SSD of the lift with clean water. If previous layers are over 48 hours old, mechanically prepare the substrate and dampen.

### By machine

- Apply SikaRepair® SHB mortar by low or high pressure wet spray.
- Shoot perpendicular (90°) to the surface. This minimizes rebound, creates the smoothest pattern (reduces 'bumps') and properly encases the rebars.
- The velocity of the material is sufficient if, at a distance of 18 to 24" (457 to 609 mm), the material pattern flattens out on contact with the surface and the rebars are encased.
- After applying the material, allow it to stiffen for about 10 minutes before removing bumpy areas with a trowel.
- Before applying the next layer, allow the material to reach initial set. This will take anywhere from 45 minutes to several hours, depending on mix consistency, mix and ambient temperature, wind conditions and humidity.
- Begin and finish a given patch on the same day.

## CURING TREATMENT

- As per ACI recommendations for Portland cement concrete, curing is required.
- Moist cure with wet burlap and polyethylene, a fine mist of water or a water based\* compatible curing compound.
- Curing compounds adversely affect the adhesion of following lifts of mortar, leveling mortar or protective coatings.
- Moist curing should commence immediately after finishing. Protect freshly applied mortar from direct sunlight, wind, rain and frost.

\* Pretesting of curing compound is recommended.

## LIMITATIONS

- Do not use solvent based curing compounds
- Not a vapor barrier
- As with all cement based materials, avoid contact with aluminum to prevent adverse chemical reaction and possible product failure. Insulate potential areas of contact by coating aluminum bars, rails, posts etc. with an appropriate epoxy such as Sikadur® Hi-Mod 32

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## OTHER RESTRICTIONS

See Legal Disclaimer.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

0 g/L

(EPA Method 24)

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

**Sika Corporation**  
201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)

**Sika Mexicana S.A. de C.V.**  
Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



Product Data Sheet  
SikaRepair® SHB  
June 2018, Version 01.02  
020302020010000017

SikaRepairSHB-en-US-(06-2018)-1-2.pdf

**BUILDING TRUST**

