

PRODUCT DATA SHEET

Westec TPER

CHEMICALLY RESISTANT WATERSTOP

PRODUCT DESCRIPTION

Thermoplastic Elastomeric Rubber Waterstop for joint waterproofing of secondary containment structures.

USES

Ethanol/Biodiesel
 Petrochemical Manufacturing
 Refineries
 Pulp and Paper Mills
 Land, Air and Seaports
 Pipeline
 Pharmaceutical Plants

CHARACTERISTICS / ADVANTAGES

Embedded in concrete, across and/or along the joint, waterstops form a watertight diaphragm that prevents the passage of liquid through the joint.
 Suitable for contact with a wide range of chemicals including oils, fuels, acids, bases, and numerous solvents.
 Meets NSF/ANSI Standard 61.

PRODUCT INFORMATION

Packaging	Varies
Shelf Life	N/A
Storage Conditions	N/A

TECHNICAL INFORMATION

Shore A Hardness	85	(ASTM D2240)
Tensile Strength	2000 psi	(ASTM D638)
Tensile Modulus of Elasticity	1000 psi	(ASTM D638)
Elongation	450%	(ASTM D638)
Chemical Resistance	Resistant to a wide range of chemicals. Please refer to the Westec® Chemical Resistance Chart available at usa.sika.com for commonly used chemicals or contact the waterproofing engineering department for any chemicals not shown.	

APPLICATION INSTRUCTIONS

Westec® Envirostop® TPER Waterstop must be installed prior to concrete placement to ensure proper positioning and concrete consolidation around the waterstop. All transitions, intersections, and splices should be heat welded to maintain continuity. Factory Made Fabrications are recommended for all intersections and changes of direction. Specific installation requirements will vary depending on the style of profile, please refer to Sika's TPER/PE Waterstop Installation Guide and TPER/PE Waterstop Splicing Guide available at usa.sika.com.

APPLICATION METHOD / TOOLS

All transitions, intersections, and splices must be heat welded using a Sika® Greenstreak® Splicing Iron in compliance with the instructions shown in Sika's TPER/PE Splicing Guidelines found at usa.sika.com.

LIMITATIONS

The size, shape, and style of waterstop should be based on specific application needs. Please consult a Sika Engineer at 800-325-9504 for assistance with profile selection.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and

instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet
Westec TPER
August 2019, Version 01.01
020703100300000107

WestecTPER-en-US-(08-2019)-1-1.pdf

