



## PRODUCT DATA SHEET

# SikaColor-25 G Medium Red

---

FREE FLOWING PIGMENT GRANULES DESIGNED TO PERMANENTLY COLOR CONCRETE AND OTHER CEMENTITIOUS MATERIALS.

---

### DESCRIPTION

SikaColor® granules are free-flowing concentrated pigment granules designed to permanently color concrete and other cementitious materials. They can be poured directly into concrete mixes, conveyed by gravity feed or pneumatic equipment, or predispensed into pulpable bags that can later be added directly to the concrete mix as a single unit.

### USES

SikaColor® granules can be used to color cast-in-place, precast, concrete floor slabs, walls, steps, sidewalks, curbs, columns, arches, blocks, pavers, and other decorative objects.

### CHARACTERISTICS / ADVANTAGES

SikaColor® granules add color that is weather resistant, UV Stable, and lightfast. It contains no materials that initiate, accelerate, or promote the corrosion of steel, coated metal, plastic, or rubber concrete reinforcements. SikaColor® granules will not migrate from standing water, and can safely color concrete fountains, pools, water features, or concrete that will be polished and encounter damp or wet environments.

### APPROVALS / CERTIFICATES

All pigments used conform to the requirements of ASTM C 979 Pigments for Integrally Colored Concrete.

## PRODUCT INFORMATION

---

<b>Composition</b>	Synthetic iron oxide granule pigments.
<b>Packaging</b>	Bulk bags designed for use with a SikaColor® Granular Dispensing System are available in four standard base colors: SikaColor®-10 G Black SikaColor®-20 G Light Red SikaColor®-25 G Medium Red SikaColor®-30 G Yellow Hundreds of ready to use colors are available from distributors in pulpable toss-in bags and plastic pails. These are typically packaged so one unit colors one yard of concrete.
<b>Appearance / Colour</b>	Over 700 tested color formulas are available for immediate packaging with the SikaColor® Granular Dispensing System. These include colors depicted on Sika Decorative Concrete brands Butterfield Color® and Scofield® color charts, as well as hundreds of colors common to the industry. Visit <a href="http://www.usa.sika.com">www.usa.sika.com</a> for your nearest point of distribution.
<b>Shelf life</b>	SikaColor®-25 G Medium Red granules have a 24 month shelf life from date of manufacture.
<b>Storage conditions</b>	Keep dry, moisture free, and below 175 °F (80 °C).

---

## TECHNICAL INFORMATION

---

<b>Concreting Guidance</b>	SikaColor® granules are designed to have minimal effect on concrete plastic and hardened properties, and to minimally interact with other concrete admixtures. Additional water, about 10 % of the SikaColor® granules used, may be needed to compensate for water absorbed by the granules. This amount of water will be less if water reducing admixtures are part of the mix design. As all chemical admixture interactions cannot be predicted, always test final mix designs with actual materials to be used, and perform a jobsite test section as described later in this Product Data Sheet.
----------------------------	---

---

## APPLICATION INFORMATION

---

<b>Recommended Dosage</b>	Color selection will determine the ratio of base colors needed, and color saturation, and intensity will determine the amount of granules required. Typical dosages range between 0.2 to 10.0 pounds of granules per 94
---------------------------	---

**PRODUCT DATA SHEET**  
SikaColor-25 G Medium Red  
May 2020, Version 01.01  
021405071000000096



pound sack of cement. If supplementary cementitious materials such as fly ash or blast-furnace slag are used in the mix, their weight must be added to the weight of the cement when determining the correct dosage.

---

**Dispensing**

SikaColor® granules can be introduced at any point in the concrete mixing process, as long as enough mixing and time is given for the color to reach an unchanging uniform appearance. Typically, this will take at least 10 minutes and 130 drum revolutions at optimal mixing speed. Automated delivery systems can be set to introduce granules early in the batching process to minimize dusting. Care must be taken to not allow disintegrating bags or granules to become hung up on mixing vanes or collect in spaces where the mix has limited motion.

---

**Restrictions**

Do not use with chloride based accelerators.

---

## APPLICATION INSTRUCTIONS

### Factors Influencing Final Color & Appearance

Colors shown on Sika Decorative Concrete brands Butterfield Color® and Scofield® color charts represent formulations using medium gray cement. The final color and appearance obtained on the jobsite will be influenced by concrete composition, surface finishing technique, timing, and curing compound/sealer selection.

Concrete composition variations that can impact color include cement type and color, aggregate selection, and the use of pozzolans such as slag or fly ash. Differences in sealer or curing compound type, such as water or solvent-based, or if no sealer is used, can also influence final appearance. Finishing techniques will influence final concrete appearance.

Different tools such as wood floats, magnesium trowels, hard steel trowels, brooms, and edging tools, will each influence color, surface texture, sealer penetration, and final cured concrete appearance differently. Do not change tool types once work has begun. Changes in water content and water-to-cement ratio, both in the mix and on the concrete surface during finishing, can influence the final surface color. Mix designs that develop excessive bleed water can float non-uniform cement/pigment ratios, and cause uneven or weak coloring. Once mix designs are established, do not add water to alter concrete plastic properties. Do not add water to loosen partially cured loads. Do not use “watering” sprinklers as colored concrete cures, or use wet brooms and tools while finishing. Any of these will likely result in inconsistent concrete color.

#### PRODUCT DATA SHEET

SikaColor-25 G Medium Red

May 2020, Version 01.01

021405071000000096

**BUILDING TRUST**



### Placement and Finishing Tips

As freshly placed concrete cures, its color will vary with differences in surface moisture. Concrete curing in shaded areas or in the center of large slabs will surface dry slower than those exposed to sunlight or closer to form edges. This can cause color variations that will often fade with time. Avoid high salt aggregates that can cause efflorescence that can make color irregular. These visual differences can be long lasting, and raise questions about the quality of the concrete placement. Always evaluate composition and finishing techniques as described below.

### Reinforcing Fiber Interactions

If high air content is experienced with competitor reinforcing fibers, pre-wet the fibers by tumbling in the mixer three minutes with water and colorant before batching concrete into the mixer.

### Jobsite Test Sections

Prior to large scale production, the concrete or cementitious mix design for each color to be produced must be made. Conduct small scale testing to demonstrate concrete from the mix design meets all slump, flow, air content, compressive strength, and any other required concrete specifications. Prior to general jobsite use, representative Jobsite Test Section(s) or “Mock- Ups” must be produced and approved for each individual concrete color mix design, surface finish/texture, and for each curing compound/sealer combination that will be created. Use Jobsite Test Sections to verify entire system suit-

ability including frame/mold and foundation preparation methods, surface concrete specification compliance, finishing techniques, safety procedures, and achieved performance of the fresh and fully cured concrete. When applicable, test completed systems for wet and dry slip resistance. Evaluate polishing or coating application techniques, final color, and visual appearance. Do not proceed with products, techniques, or finishing systems that do not meet required specifications or meet with site owner approval. Selected Jobsite Test Sections should be in close proximity to the larger job area, and made from the same concrete mix design that will be used on the larger project. Test sections should be sized to be representative of the finished project, and be produced by the same workers who will perform the project installation.

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product

#### PRODUCT DATA SHEET

SikaColor-25 G Medium Red

May 2020, Version 01.01

021405071000000096

may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

## ECOLOGY, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## LEGAL NOTES

- **KEEP CONTAINER TIGHTLY CLOSED**
- **KEEP OUT OF REACH OF CHILDREN**
- **NOT FOR INTERNAL CONSUMPTION**
- **FOR INDUSTRIAL USE ONLY**
- **FOR PROFESSIONAL USE ONLY**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any

legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

