

PRODUCT DATA SHEET

PAREX® DPR Acrylic Finish

Factory-mixed, 100% acrylic polymer finish coat

PRODUCT DESCRIPTION

100% acrylic polymer finishes with advanced technology to improve long-term performance and dirt pick-up resistance. Integrally colored with high quality pigments.

USES

PAREX® DPR Acrylic Finish provides enhanced protection for an aesthetically pleasing surface color and texture for Parex systems, poured concrete or unit masonry, conventional stucco, properly prepared insulating concrete forms and interior veneer plaster or gypsum wallboard (primer required over interior surfaces).

CHARACTERISTICS / ADVANTAGES

- 100% Acrylic polymer chemistry creating long-term durability and weather resistance.
- Integral color reducing maintenance and the need for recoating.
- Repels water and resists wind-driven rain.
- Seals existing, non-moving hairline cracks. Doesn't blister, peel or flake

PRODUCT INFORMATION

Packaging	5 gallon pail (19 liter pail)
Color	Available in a wide variety of standard and custom colors.
Shelf Life	Two (2) years when properly stored in original container.
Storage Conditions	▪ Protect materials during transportation to avoid physical damage. Store in a cool, dry place protected from freezing, extreme heat and direct sun. Store at no less than 40°F (4°C) ▪ Do not stack pallets.
Grain size distribution	▪ DPR 530 Swirl Fine ▪ DPR 533 Sand Smooth ▪ DPR 534 Sand Fine ▪ DPR 535 Sand Coarse

TECHNICAL INFORMATION

Test Results

TEST	METHOD	CRITERIA	RESULT
VOC	ASTM D 3960 (based in part on EPA method 24)	Report Value	0.22-0.31 lbs/gal (26-37 g/l) less water and exempt solvents.
Surface Burning Characteristics	ASTM E 84	Report Value	Flame Spread < 25 Smoke Development < 450 (Class A)
Water Vapor Transmission	ASTM E96 Method B	Report Value	Finish with Parex 121 Dry Basecoat/Parex 355 Standard Mesh: 15-19 Perms (varies based on texture) Finish with Parex 121 Dry Base Coat/Parex 355 Standard Mesh: 19-22 Perms (varies based on texture)
Water Resistance of Coating in 100% R.H.	ASTM D2247	No deleterious effects after 14 days exposure	Pass
Salt Fog Resistance	ASTM B117	No deleterious effects after 300 hours	Pass
Mildew Resistance	Mil. Std. 810B Method 508	fungus growth after 28 days	Pass
Chemical Resistance	Lab Test	Determined by spot testing the sample surface with turpentine, mineral spirits, and 10% Lab Test hydrochloric acid for 4 hours	Turpentine = slight softening Mineral spirits = slight softening 10% Hydrochloric acid = slight softening
Abrasion Resistance	ASTM D968	No deleterious effects after 528 quarts (500 liters) ASTM D958	Finish not worn through after 725 qt. (686L) of falling sand
Accelerated Weathering	ASTM G23 ASTM G53	No deleterious effects after 2000 hrs No deleterious effects after 7500 hrs	Pass
Tensile Bond	ASTM C292.22134	15 psi minimum	Pass over acceptable substrates

APPLICATION INFORMATION

Coverage

DPR 530 Swirl Fine: 130 to 140 ft² (12 to 13 m²)
DPR 533 Sand Smooth: Smooth 182-187 ft² (17 m²) at two (2) coats.
DPR 533 Sand Smooth: Skip Trowel 150-160 ft² (17 m²)
DPR 534 Sand Fine: 145 to 155 ft² (13.5 - 14.4 m²).
DPR 535 Sand Coarse: 105 to 115 ft² (9.8 - 10.7 m²).

* Coverage rates vary depending on porosity of substrates and application techniques.

Ambient Air Temperature

- Protect from temperatures less than 40°F (4.5°C) for a minimum of 24 hours and until dry.
- When temperatures less than 40°F (4.5°C) prevail, provide supplementary heat during installation and drying period for at least 24 hours after installation and until dry.
- Do not apply in ambient temperature above 100°F (38°C) or surface temperature above 120°F (49°C).

Cure Time

- Finish will be dry within 24 hours. Drying time is dependent on humidity, air temperature, sun exposure, surface conditions and finish thickness. Lower temperature, higher humidity and application in shaded areas will extend drying time.
- Protect finish from rain or other precipitation and temperatures less than 40°F (4.5°C) for a minimum of 24 hours and until dry.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

USES

1. Appearance of Swirl Fine Finish might vary if floated by different mechanics.
2. Not for use on damp surfaces, below-grade applications or on surfaces subject to water immersion.
3. Do not apply materials to frozen surfaces.

4. Efflorescence of Portland cement based substrates such as concrete, masonry units and stucco may cause staining or discoloration on the surface of applied finish. Efflorescence is neither caused nor prevented by Parex finish.
5. The use of dark colors with light reflective values (LRV) less than 20% is not recommended with EIFS that incorporate expanded polystyrene (EPS). EPS has a sustained service temperature limitation of approximately 165°F (74°C).
6. Samples of Parex Finishes are available for color approval only. Samples for job approval must be made in the field by the applicator and approved prior to ordering.
7. Do not exceed 10 oz of water per 5 gallon pail. Excess water will affect texture appearance and product

Product Data Sheet

PAREX® DPR Acrylic Finish

November 2025, Version 03.01

021810101000000147

BUILDING TRUST



- performance.
8. Finish tint base is not intended for use untinted.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Substrates must be clean, dry, sound and free of loose material, releasing agents, paint, efflorescence, contaminants and other coatings. Use of SikaWall-15 Tinted Primer can improve color uniformity by minimizing substrate read-through in light colors.

- Concrete: allow to cure a minimum of 28 days prior to application of primer or finish.
- Unit Masonry: allow to cure prior to application of primer or finish. When needed, apply a leveling coat of Parex 121 Dry Basecoat to provide a smooth surface and minimize the likelihood of mortar joint read-through prior to application of finish.
- Stucco: allow to cure a minimum of 6 days prior to application of primer or finish.

Note: Primer is for color uniformity, not for adhesion assistance.

MIXING

Thoroughly mix the factory prepared finish with a paddle and low speed drill to a uniform workable consistency. A small amount of clean potable water may be added to adjust workability. Do not exceed 10 oz. of water per 5-gallon pail.

- Additives are not permitted.
- Close container when not in use.
- Clean tools with soap and water immediately after use. Dried material can only be removed mechanically.

APPLICATION

1. Apply finish directly to the substrate (or primed substrate) with a clean, stainless steel trowel. Apply and level finish during the same operation to minimum obtainable thickness consistent with uniform coverage.
2. Maintain a wet edge on finish by applying and texturing continually over the wall surface. Work finish to corners, joints or other natural breaks and do not allow material to set up within an uninterrupted wall area.
3. Float finish to achieve final texture.

Note: DPR Sand Smooth Finish

For smooth application, allow the first coat of Sand Smooth finish to dry prior to applying a second coat. 2 coats are required for a smooth texture.

For free-formed application including stipple and skiptrowel, maximum thickness not to exceed 1/8" (3.2mm).

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of Sika products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/about-us/terms-conditions-of-sale.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet

PAREX® DPR Acrylic Finish
November 2025, Version 03.01
02181010100000147

PAREXDPRAcrylicFinish-en-US-(11-2025)-3-1.pdf

