



SURFACE COATS

ROOM & HIGH TEMPERATURE

EPOXY SURFACE COATS - ROOM TEMPERATURE

Product	Hardener	Tg (°F)	Mixed Ratio	Pot Life (min/g)	Color	Shore Hardness	Description & Applications
ES-218	ES-218 H	114	100/14	22/230	White	83 D	Sandable system for durable high quality surface reproductions; Ideal for taking laminating duplicates
TCC-352	TCC-352 H	180*	100/15	20/100	Lt. Gray	89 D	Wear-resistant system for durable surface reproductions; Ideal for checking and trimming fixtures

EPOXY SURFACE COATS - HIGH TEMPERATURE

Product	Hardener	Tg (°F)	Mixed Ratio	Pot Life (min/g)	Color	Shore Hardness	Description & Applications
S11	S11 H	200	100/16	15/232	Lt. Blue	88 D	System for Plastic-Faced Plaster (PFP) and general applications, including vacuum forming molds and nesting fixtures
SP-707	SP-707 H	220	100/15	23/230	Gray	90 D	Aluminum-filled system used for laminated vacuum form, drape form, RIM, RTM, and injection molds
ES-221	ES-221 H	230	100/13	22/226	Black or White	90 D	Polishable system for duplicating of clay models, PFP molds, and high temperature tools requiring a gloss finish
ES-224	ES-224 H	264	100/9	60/327	Gray	90 D	Abrasion-resistant system used for laminated vacuum form, drape form, RIM, RTM, and intermediate high temperature production tools
ESG-215 Series	ESG-215 H	268	100/14	43/240	Black	90 D	Graphite-filled repair paste used for surface repairs of high temperature epoxy composite molds
	ESG-215-T H	371	100/15	43/240	Black	90 D	
ES-215 Series	ES-215-1 H	301	100/18	16/240	Black	89 D	Graphite-filled system used for high temperature composite molds and autoclave tooling
	ES-215-2 H	307	100/22	83/240	Black	88 D	
	ES-215-IHG	382	100/17	200/280	Black	89 D	

POLYESTER SURFACE COATS - HIGH TEMPERATURE

Product	Hardener	Tg (°F)	Mixed Ratio	Viscosity Mixed (cps)	Pot Life (min/g)	Shore Hardness	Description & Applications
APG 1750 S	MEKP	400*	100/2	Thixotropic	22/102	87 D	Styrene-free system most commonly used in high temperature tools for epoxy infusion, cultured marble molds, thermoforming molds, FRP molds, and RTM mold repair

* Peak Use Temperature

Our most current General Sales Conditions shall apply.
Please consult the Data Sheet prior to any use and processing.

SIKA ADVANCED RESINS CUSTOMER SERVICE
30800 Stephenson Highway (248) 588 2270
Madison Heights, MI 48071 Advanced.Resins@us.sika.com
(248) 577 0020
www.SikaAdvancedResins.us

BUILDING TRUST

