

## PRODUCT DATA SHEET

# Sikaflex®-201 US

Long open time polyurethane sealant

**TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)**

|  |   |
|--|---|
| Chemical base                          | 1-component polyurethane  |
| Color (CQP001-1)                       | White, aluminum gray, tan, capitol tan, MB bronze, black                        |
| Cure mechanism                         | Moisture-curing   |
| Density (uncured)                      | 1.5 kg/l (12.5 lb/gal)  |
| Non-sag properties                     | Good  |
| Application temperature                | 5 – 40 °C (41 – 104 °F)   |
| Skin time (CQP019-1)                   | 4 hours <sup>A</sup>  |
| Curing speed (CQP049-1)                | (see diagram 1)   |
| Shore A hardness (CQP023-1 / ISO 48-4) | 45  |
| Tensile strength (ASTM D412)           | 1.3 MPa (190 psi)   |
| Elongation at break (ASTM D412)        | 550 %   |
| Service temperature (CQP513-1)         | -40 – 90 °C (-40 – 194 °F)  |
| Shelf life                             | cartridge / unipack 12 months <sup>B</sup><br>pail / drum 6 months <sup>B</sup> |

CQP = Corporate Quality Procedure

<sup>A</sup>) 23 °C (73 °F) / 50 % r.h.<sup>B</sup>) storage below 25 °C (77 °F)
**DESCRIPTION**

Sikaflex®-201 US is a multi-purpose 1-component polyurethane sealant which cures on exposure to atmospheric moisture suitable for making permanent flexible and elastic seals. It is designed with a long open time for applications that require additional working time.

**PRODUCT BENEFITS**

- Bonds well to a wide variety of substrates
- Can be sanded and painted
- Meets the requirements of AAMA 803.3 Type I and AAMA 808.3
- Listed under NSF/ANSI/CAN 61 – Drinking Water System Components (aluminum gray, capitol tan, black, and white)
- Listed under NSF – Proprietary Substances and Nonfood Compounds (aluminum gray, black, and white)

**AREAS OF APPLICATION**

Sikaflex®-201 US provides a longer working time and permanent elastic seal. It is suitable for sealing joints, seams and gaps in many applications including HVAC, metal buildings, tanks and grain bins, non-vehicular window perimeters and many other industrial applications. Suitable substrate materials are metals, metal primers and paint coatings (2-component systems), ceramic materials and plastics. Seek manufacturer's advice and perform tests on original substrates before using Sikaflex®-201 US on materials prone to stress cracking. This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

**PRODUCT DATA SHEET**

Sikaflex®-201 US

Version 04.01 (04 - 2023), en\_US  
012001202010001000

Nonfood Compounds  
Program Listed (R2)  
(NF1 22443, NF1 22721, NF1 22720)

## CURE MECHANISM

Sikaflex®-201 US cures by reaction with atmospheric moisture. At low temperatures the water content of the air is generally lower and the curing reaction proceeds somewhat slower (see diagram 1).




Diagram 1: Curing speed for Sikaflex®-201 US

## CHEMICAL RESISTANCE

Sikaflex®-201 US is generally resistant to fresh water, seawater, diluted acids and diluted caustic solutions; temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, glycolic alcohol, concentrated mineral acids and caustic solutions or solvents.

## METHOD OF APPLICATION

### Surface Preparation

Surfaces must be clean, dry and free from grease, oil and dust.

Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond. Suggestions for surface preparation may be found on the current edition of the appropriate Sika® Pre-Treatment Chart. Consider that these suggestions are based on experience and have in any case to be verified by tests on original substrates.

### Application

Sikaflex®-201 US can be processed between 5 °C and 40 °C (41 °F and 104 °F) but changes in reactivity and application properties have to be considered. The optimum temperature for substrate and process material is between 15 °C and 25 °C (41 °F and 77 °F).

Sikaflex®-201 US can be processed with hand, pneumatic or electric driven piston guns as well as pump equipment. For advice on selecting and setting up a suitable pump system, contact the System Engineering Department of Sika Industry.

## Tooling and finishing

Tooling and finishing must be carried out within the skin time of the product. It is recommended using Sika® Slick. Other finishing agents must be tested for suitability and compatibility prior the use.

## Removal

Uncured Sikaflex®-201 US may be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically.

Hands and exposed skin have to be washed immediately using a suitable industrial hand cleaner and water.

Do not use solvents on skin.

## Overpainting

Sikaflex®-201 US can be painted after formation of a skin. If the paint requires a baking process, best performance is achieved by allowing the sealant to fully cure first. 1C-PUR and 2C-acrylic based paints are usually suitable. All paints have to be tested by carrying preliminary trials under manufacturing conditions.

The elasticity of paints is usually lower than that of sealants. This could lead to cracking of the paint in the joint area.

## FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets
- Sika Pre-treatment Chart
  - For 1-component Polyurethane
- General Guideline
  - Bonding and Sealing with 1-component Sikaflex®

## PACKAGING INFORMATION

|           |              |
|-----------|--------------|
| Cartridge | 300 ml       |
| Unipack   | 600 ml       |
| Pail      | 4.5 gal (US) |
| Drum      | 50 gal (US)  |

## BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## LEGAL DISCLAIMER

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by contacting SIKA's Technical Service Department via email at [tsmh@us.sika.com](mailto:tsmh@us.sika.com). Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.** Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling +1 800-933-7452.

## PRODUCT DATA SHEET

Sikaflex®-201 US  
Version 04.01 (04 - 2023), en\_US  
012001202010001000

## Sika Corporation

30800 Stephenson Highway  
Madison Heights, MI 48071  
U.S.A.  
Telephone: +1 248-577-0020  
Email: [tsmh@us.sika.com](mailto:tsmh@us.sika.com)  
[www.sikausa.com](http://www.sikausa.com)

