

PRODUCT DATA SHEET

Sikafloor®-2570 WB

Water Based Epoxy Primer/Sealer For High Performance Floor Finishes

PRODUCT DESCRIPTION

Sikafloor®-2570 WB is a water-based, low VOC, two part epoxy resin primer

USES

Sikafloor®-2570 WB may only be used by experienced professionals.

Sikafloor®-2570 WB is designed as a primer for Sikafloor epoxy and urethane coatings, as well as for broadcast and troweled systems. When used as a primer Sikafloor®-2570 WB can be considered where $\leq 6\%$ moisture content by mass (pbw – part by weight) is measured on concrete substrate with Tramex® CME/CMExpert type concrete moisture meter.

CHARACTERISTICS / ADVANTAGES

- Water based, low VOC's
- Excellent penetration and adhesion
- Easy application
- Reduced recoat times

PRODUCT INFORMATION

Packaging	Component A: 2.5 US gal. (9.46 L) Component B: 2.5 US gal. (9.46 L) Components A+B: 5.0 US gal. (18.92 L) (Ready to mix unit)
Appearance / Color	White transparent after mixing
Shelf Life	24 months in original unopened container under proper storage conditions
Storage Conditions	Store dry between 40 °F and 90 °F (4–32 °C). Do not allow to freeze
Solid content by volume	~ 51.5 % 73°F (23°C) and 50% R.H: Properties tested at
Volatile organic compound (VOC) content	28 g/L (A+B Combined)

APPLICATION INFORMATION

Coverage 160–530 ft² / US gal (3.9–4.9 m² / L) at 3–10 mils (0.08–0.25 mm) wet film thickness.

Pot Life	Material Temperature	Time
	50 °F (23 °C)	~ 1 hour
	68 °F (20 °C)	~ 40 minutes
	86 °F (30 °C)	~ 25 minutes

Pot life is not visible, product remains liquid after exceeding pot life. Application after pot life limit may result in adhesion failure. Do not apply after pot life limit.

Waiting / Recoat Times Before applying second coat Sikafloor®-2570 WB on Sikafloor®-2570 WB allow:

Ambient & Substrate Temperature	Minimum	Maximum
50 °F (10 °C)	4 hours	72 hours
68 °F (20 °C)	2 hours	48 hours
86 °F (30 °C)	1 hour	24 hours

Before applying Sikafloor® Epoxy or Polyurethane on Sikafloor®-2570 WB allow:

Ambient & Substrate Temperature	Minimum	Maximum
50 °F (10 °C)	24 hours	72 hours
68 °F (20 °C)	8 hours	48 hours
86 °F (30 °C)	6 hours	24 hours

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

Surface must be clean, sound and dry. Remove dust, laitance, grease, curing compounds, bond inhibiting impregnations, waxes and any other contaminants. All projections, rough spots, etc. should be removed to achieve a level surface prior to the application.

Concrete - Should be cleaned and prepared to achieve a laitance-free and contaminant-free, open textured surface by shot blasting or equivalent mechanical means (CSP-3 to CSP-4 as per ICRI guidelines). Sweep and vacuum any remaining dirt and dust with a wet/dry vacuum. Removing residual dust will help ensure a tenacious bond between the primer and substrate. Whenever “shot-blasting” is utilized, be careful to leave concrete with a uniform texture. “Over-blasting” will result in reduced coverage rates of the primer and/or subsequent topcoats. The “shotblast” pattern may show through the last coat, known as “tracking”. The compressive strength of the concrete substrate should be at least 3,500 psi (24 MPa) at 28 days and at least 215 psi (1.5 MPa) in tension at the time of application. For other substrates, please contact Sikafloor Technical Services.

MIXING

Mixing Ratio - 1 : 1 by volume.

For bulk packaging, when not mixing full units, each

component must be pre-mixed separately to ensure product uniformity.

Primer

Premix each component separately. Empty Component B (Hardener) in the correct mix ratio into Component A (Resin). Mix the combined components for at least 3 minutes using a low speed drill (300–450 rpm) and Exomixer or Jiffy type paddle suited to the volume of the mixing container to minimize entrapped air. Be careful not to introduce any air bubbles while mixing. Make sure the contents are completely mixed to avoid any weak or partially cured spots in the coating. During the mixing operation, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once to ensure complete mixing.

Do not mix more material than can be applied within the working time limits (i.e. Pot Life) at the actual field temperature.

APPLICATION

Primer/Sealer:

Apply primer by squeegee at the rate of 160–320 ft² / US gal. (3.9–7.8 m² / L) at 5–10 mils (0.13–0.25 mm) wet film thickness (w.f.t.) and back-roll with pressure. Coverage will vary depending on the porosity of the prepared floor. Product has a limited pot life, see Typical Data. Do not apply by dipping roller into mixing container. Pour a bead of product in the form of a ribbon on the surface to be coated, then spread with squeegee and back roll. Ensure that the coating is pore-

free and pinhole-free and provides uniform and complete coverage over the entire concrete substrate. If necessary, apply an additional coat to ensure the coating is pore-free and pinhole-free and provides uniform and complete coverage over the entire concrete substrate.

LIMITATIONS

Notes on Limitations:

Prior to application, measure and confirm Substrate Moisture Content, Ambient Relative Humidity, Ambient and Surface Temperature and Dew Point. During installation, confirm and record above values at least once every 3 hours, or more frequently whenever conditions change (e.g. Ambient Temperature rise/fall, Relative Humidity increase/decrease, etc.).

Substrate Moisture Content: Moisture content of concrete substrate must be $\leq 6\%$ by mass (pbw – part by weight) as measured with a Tramex® CME/CMExpert type concrete moisture meter on mechanically prepared surface according to this product data sheet (preparation to CSP-3 to CSP-4 as per ICRI guidelines). ASTM F2170 testing is not a substitute for measuring substrate moisture content. Use a Tramex® CME/CMExpert type concrete moisture meter as described above.

Material Temperature: Precondition material for at least 24 hours between 65 °F and 75 °F (18–24 °C)

Ambient Temperature: Minimum/Maximum 50/85 °F (10/30 °C)

Substrate Temperature: Minimum/Maximum 50/85 °F (10/30 °C). Substrate temperature must be at least 5 °F (3 °C) above measured Dew Point. Mixing and Application must adhere to Material, Ambient and Substrate temperatures listed above or a decrease in product workability and slower cure rates will occur.

Ambient Relative Humidity: Maximum ambient humidity 85 % (during application and curing)

Dew Point: Beware of condensation!

The substrate must be at least 5 °F (3 °C) above the Dew Point to reduce the risk of condensation, which may lead to adhesion failure or “blushing” on the floor finish. Be aware that the substrate temperature may be lower than the ambient temperature.

Mixing: Do not hand mix Sikafloor® materials. Mechanically mix only. Do not thin this product. Addition of thinners (e.g. water, solvent, etc.) will slow cure and reduce ultimate properties of this product. Use of thinners will void any applicable Sika warranty. Improper mixing procedure or incorrect mixing ratio may result in moisture sensitivity, whitening, slow cure, soft spots, and other defects.

- Do not apply while ambient and substrate temperatures are rising, as pinholes may occur.
- Ensure there is no vapor drive at the time of

application. Refer to ASTM D4263, may be used for a visual indication of vapor drive.

- Will discolor over time when exposed to sunlight (UV) and under certain artificial lighting conditions. Use of clear UV resistant top coat may not prevent discoloration of underlying coatings
- Do not apply Sikafloor® to concrete substrate containing aggregates susceptible to ASR (Alkali Silica Reaction) due to risk of natural alkali redistribution below the Sikafloor® product after application. If concrete substrate has or is suspected to have ASR (Alkali Silica Reaction) present, do not proceed. Consult with design professional prior to use.
- Any aggregate used with Sikafloor® systems must be non-reactive and oven-dried.

- This product is not designed for negative side waterproofing.
- Use of unvented heaters and certain heat sources may result in defects (e.g. blushing, whitening, debonding, etc.).
- Beware of air flow and changes in air flow. Introduction of dust, debris, and particles, etc. may result in surface imperfections and other defects.
- For professional use only by experienced applicators.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet
Sikafloor®-2570 WB
August 2018, Version 01.01
020811010010000011

Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sikafloor-2570WB-en-US-(08-2018)-1-1.pdf

