

PRODUCT DATA SHEET

SikaLatex[®]

Water resistant bonding agent and mortar admixture

PRODUCT DESCRIPTION

SikaLatex[®] is an acrylic-polymer latex that is used as admixture for cementitious bonding bridges and high quality site-mix mortars.

USES

SikaLatex[®] is used as bonding agent and site-mix mortar admixture for the following applications:

- Grouts and screeds
- Patch repair mortars
- Masonry mortars
- Renders
- Tile adhesives
- Stucco and terrazzo

CHARACTERISTICS / ADVANTAGES

- Increased adhesion
- Reduced shrinkage and cracking
- Increased abrasion resistance
- Reduced permeability
- Improved workability
- User friendly
- Suitable on most common construction substrates
- An admixture in mortar and concrete to improve adhesion, and achieve a denser surface
- Increases resistance to freeze/thaw cycling

APPROVALS / STANDARDS

USDA certifiable for incidental food contact

PRODUCT INFORMATION

Packaging	<ul style="list-style-type: none"> ▪ 1 gal (3.8 L) jug, 4/case ▪ 5 gal (19 L) pail ▪ 55 gal (208 L) drum
Appearance / Color	Milky-white liquid
Shelf Life	24 months from date of production if stored properly in original, unopened and undamaged sealed packaging
Storage Conditions	Store dry at 40–95 °F (4–35 °C). Protect from moisture. If frozen, discard material Condition material to 65–75 °F (18–24 °C) before using
Density	62.4 lb./ft ³ (~1.0 kg/l) (ASTM C-138)

TECHNICAL INFORMATION

Tensile Adhesion Strength

	7 days
Slurry, scrub coat*	950 psi (6.6 MPa)
Primer	1,200 psi (8.2 MPa)

(ASTM C-882
Modified)

Slurry, scrub coat: 2 parts sand, 1 part cement

APPLICATION INFORMATION

Recommended Dosage	Admixture	No dilution
	Primer for acrylic coatings	SikaLatex® : Water = 1 : 1
	Bonding agent	1 part cement, 2 parts sand, undiluted SikaLatex®*

* Creamy paint consistency, maximum 4 gal/bag

Coverage	Primer for acrylic coatings only
	<ul style="list-style-type: none">▪ Estimated coverage on a CSP-3 prepared surface is 300 ft²/gal▪ Very porous concrete may require a second coat

Ambient Air Temperature	40–86 °F (4–30 °C)
--------------------------------	--------------------

Substrate Temperature	40–86 °F (4–30 °C)
------------------------------	--------------------

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

- The substrate shall be thoroughly clean, sound, free from dust, loose material, surface contamination and materials which reduce bond or prevent suction or wetting by cementitious materials.
- De-laminated, weak, damaged and deteriorated substrate shall be removed by suitable means before application.
- Rust, scale, dust and other loose and deleterious materials which reduces bond or contributes to corrosion shall be removed.

MIXING

- Mix SikaLatex® with the correct amount of water to produce a gauging solution.
- Pour part of the gauging solution into a suitable mixing container.
- While mixing slowly, add the mortar mix to the gauging solution and mix thoroughly until a smooth, uniform and lump-free mix is achieved.
- Within the mixing time add additional gauging solution to adjust to the desired consistency.

APPLICATION METHOD / TOOLS

Primer for acrylic coatings only

- Apply diluted SikaLatex® to prepared concrete substrate (CSP-3) using brushes, rollers, soft brooms, or spray.
- SikaLatex® must be tack-free (film formation) prior to coating.
- SikaLatex® may be applied up to 24 hours ahead providing the area is kept dry and clean.

Bonding Agent

- Brush slurry into area to be resurfaced with stiff-bristled broom or scrub brush.
- Be sure entire surface and all edges are coated.
- Apply topping immediately over scrub coat before the bonding slurry dries.

Admixture

- Immediately trowel SikaLatex® mortar or concrete mixes applied in areas to be patched.
- Do not over-finish.
- As soon as finish will resist damage, cure with damp burlap and/or white pigmented polyethylene film.
- Curing should continue for 24 hours.
- Pre-testing is recommended

LIMITATIONS

- Never use pure SikaLatex® or SikaLatex®-water mix directly onto the substrate as bonding agent, always add cement and sand to the mix.
- Non-reemulsifiable.
- Does not produce a vapor barrier.
- Toppings must be applied immediately over SikaLatex® bonding grout.
- Do not apply solvents or solvent-based curing compounds to SikaLatex® mortar/ concrete.
- Do not use air-entraining cements when used as an admixture.
- Do not use for overlays.
- As with all cement based materials, avoid contact with aluminum to prevent adverse chemical reaction and possible product failure. Insulate potential areas of contact by coating aluminum bars, rails, posts etc. with an appropriate epoxy such as Sikadur® Hi-Mod 32.

BASIS OF PRODUCT DATA

Product Data Sheet

SikaLatex®

May 2018, Version 01.01

020301010010000001

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

10 g/l

(EPA method 24)

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet

SikaLatex®
May 2018, Version 01.01
020301010010000001

SikaLatex-en-US-(05-2018)-1-1.pdf

