

## PRODUCT DATA SHEET

# Sikaplan® Adhered-60 Feltback EnergySmart

Sikaplan Adhered Roof Membrane is a PVC thermoplastic membrane

### PRODUCT DESCRIPTION

Sikaplan® Adhered-60 Feltback EnergySmart EnergySmart Roof Membrane is a highly reflective, PVC thermoplastic membrane produced with an integral fiberglass mat reinforcement and a recycled felt backing.

### USES

Sikaplan Adhered is adhered to approved substrates.

### AREAS OF APPLICATION

- Adhered roof systems
- Adhered roof flashings
- New construction and reroofing

### CHARACTERISTICS / ADVANTAGES



- Highly reflective
- Excellent dimensional stability
- Factory applied lacquer coating to reduce dirt pick up
- Hot-air welded seams for long-term performance

### APPROVALS / STANDARDS

- FM Global
- Underwriters Laboratories
- Underwriters Laboratories of Canada
- ICC Code Compliance – ES 1157
- Miami-Dade County
- Florida Building Code
- ENERGY STAR®
- California Title 24
- LEED / Green Globes

#### Product Data Sheet

Sikaplan® Adhered-60 Feltback EnergySmart

December 2020, Version 05.01

020905051150153002

## PRODUCT INFORMATION

<b>Chemical Base</b>	Thermoplastic PVC membrane containing ultraviolet light stabilizers, flame retardant and fiberglass reinforcement with a unique lacquer coating on the top surface.	
<b>Recycled Content</b>	9% Pre-consumer, 1% Post-consumer	
<b>Reinforcing Material</b>	Fiberglass	
<b>Packaging</b>	<b>60 mil (1.5 mm) Membrane</b> 10 ft x 100 ft (3 m x 30 m) roll, 388 lbs (176 kg) per roll, 9 rolls per pallet	
<b>Appearance / Color</b>	<ul style="list-style-type: none"> <li>▪ Top: White, Reflective Gray, and Tan</li> <li>▪ Bottom: Gray</li> </ul>	
<b>Shelf Life</b>	N/A	
<b>Storage Conditions</b>	Store rolls on pallets and fully protected from the weather with clean canvas tarpaulins. Unvented polyethylene tarpaulins are not accepted due to the accumulation of moisture beneath the tarpaulin in certain weather conditions that may affect the ease of membrane weldability.	
<b>Overall Thickness</b>	60 mil (1.5 mm), nominal 45 mil	(ASTM D-751) (ASTM Type II D-4434 Spec. Requirement)
<b>Thickness Above Scrim</b>	24 mil 16 mil	(ASTM D-7635) (ASTM Type II D-4434 Spec. Requirement)
<b>Felt Weight</b>	9 oz/yd <sup>2</sup>	

## TECHNICAL INFORMATION

<b>Resistance to Static Puncture</b>	Pass 33 lbf (15 kg)	(ASTM D-5602) (ASTM Type II D-4434 Spec. Requirement)
<b>Resistance to Dynamic Puncture</b>	Pass 7.3 ft-lbf (10 J)	(ASTM D-5635) (ASTM Type II D-4434 Spec. Requirement)
<b>Tensile Strength</b>	64 lbf (285 N) 55 lbf (245 N)	(ASTM D-751) (ASTM Type II D-4434 Spec. Requirement)
<b>Elongation at Break</b>	250 & 220% MD & CMD <sup>1</sup> 250 & 220% MD & CMD <sup>1</sup>	(ASTM D-751) (ASTM Type II D-4434 Spec. Requirement)
	<sup>1</sup> MD = Machine Direction, CMD = Cross Machine Direction.	
<b>Linear Dimensional Change</b>	-0.02% 0.1%	(ASTM D-1204) (ASTM Type II D-4434 Spec. Requirement)
<b>Tear Strength</b>	15 lbf (67 N) 10 lbf (45 N)	(ASTM D-751) (ASTM Type II D-4434 Spec. Requirement)
<b>Seam Strength</b>	Pass 75% of original <sup>2</sup>	(ASTM D-751) (ASTM Type II D-4434 Spec. Requirement)
	<sup>2</sup> Failure occurs through membrane rupture not seam failure.	
<b>Low Temperature Bend</b>	Pass Pass -40°F (-40°C)	(ASTM D-2136) (ASTM Type II D-4434 Spec. Requirement)

<b>Retention of Properties after Heat Ageing</b>	Tensile Strength, % of original: Pass	(ASTM D-3045)	
	Elongation, % of original: Pass	(ASTM D-751)	
	Tensile Strength, % of original: 90	(ASTM Type II D-4434 Spec. Requirement)	
	Elongation, % of original: 90		
<b>UV Exposure</b>	10,000 hours	(ASTM G-154)	
	5,000 hours	(ASTM Type II D-4434 Spec. Requirement)	
	Cracking (7x magnification)	None	
	Discoloration (by observation)	Negligible	
	Crazing (7x magnification)	None	
<b>Weight Change after Immersion in Water</b>	2.4%	(ASTM D-570)	
	± 3.0%	(ASTM Type II D-4434 Spec. Requirement)	
<b>Solar Reflectance</b>	<b>EnergySmart Colors</b>	<b>Initial Solar Reflectance<sup>1</sup></b>	<b>3-Year Solar Reflectance<sup>1</sup></b>
	EnergySmart White	0.85	0.73
	EnergySmart Reflective Gray	0.73	0.66
	EnergySmart Tan	0.72	0.65
	<sup>1</sup> Solar Reflectance testing according to ASTM C-1549.		
<b>Thermal Emittance</b>	<b>EnergySmart Colors</b>	<b>Initial Thermal Emittance<sup>1</sup></b>	<b>3-Year Thermal Emittance<sup>1</sup></b>
	EnergySmart White	0.89	0.89
	EnergySmart Reflective Gray	0.89	0.88
	EnergySmart Tan	0.89	0.88
	<sup>1</sup> Thermal Emittance testing according to ASTM C-1371, Slide Method.		
<b>Solar Reflectance Index</b>	<b>EnergySmart Colors</b>	<b>Initial Solar Reflectance Index<sup>1</sup></b>	<b>3-Year Solar Reflectance Index<sup>1</sup></b>
	EnergySmart White	107	90
	EnergySmart Reflective Gray	90	80
	EnergySmart Tan	88	78
	<sup>1</sup> Solar Reflectance Index calculated according to ASTM E-1980.		

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## AVAILABILITY/WARRANTY

### AVAILABILITY

From Sika Corporation – Roofing Authorized Applicators when used within Sikaplan roofing systems.

### WARRANTY

Upon successful completion of the installed roof by the Sika Authorized Applicator, Sika Corporation will provide

a warranty to the Building Owner via the Sika Authorized Applicator.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## APPLICATION INSTRUCTIONS

### APPLICATION

Sikaplan Adhered is installed after proper preparation of the approved substrate. The membrane is unrolled into approved Sikaplan or Sarnacol adhesive in accordance with Sika's technical requirements and then pressed into place with a minimum 100 lb (45 kg) steel roller. Sikaplan Adhered seams are heat-welded together by trained operators using hot-air welding equipment. Different Sarnacol adhesives require different application methods. Please consult Sika's Specifications or Applicator Handbook for detailed installation procedures.

### MAINTENANCE

Standard maintenance of Sikaplan systems should include regular inspections of flashings, drains, and termination sealants at least twice a year and after each storm.

### OTHER RESTRICTIONS

See Legal Disclaimer.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

#### Sika Corporation

201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)

#### Sika Sarnafil

100 Dan Road  
Canton, MA 02021  
Phone: +1 800-451-2504  
Fax: +1 781-828-5365  
[usa.sika.com/sarnafil](http://usa.sika.com/sarnafil)  
[webmaster.sarnafil@us.sika.com](mailto:webmaster.sarnafil@us.sika.com)

#### Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



#### Product Data Sheet

Sikaplan® Adhered-60 Feltback EnergySmart  
December 2020, Version 05.01  
020905051150153002

SikaplanAdhered-60FeltbackEnergySmart-en-US-(12-2020)-5-1.pdf

