



PRODUCT DATA SHEET

SikaShot® NS

Machine-applied, pre-packaged, ready-to-use, non-accelerated, portland cement mortar

PRODUCT DESCRIPTION

SikaShot® NS is a pre-packaged ready-to-use, portland cement mortar formulated for application by pneumatic gun. SikaShot® NS is placed with dry process shotcrete equipment.

USES

- Use on grade, above, and below grade on concrete and mortar.
- Use on horizontal, vertical, and overhead surfaces.
- As a structural repair material for vertical, horizontal, and overhead surfaces on parking structures, industrial plants, walkways, bridges, tunnels, dams, ramps, etc.

CHARACTERISTICS / ADVANTAGES

- Consistent physical properties
- Gunned pneumatically, no hand application
- Simple-to-use, labor-saving system
- Easily applied to clean, sound substrate
- High compressive strength
- No added chlorides

PRODUCT INFORMATION

Packaging	55 lb (25 kg) bag
Appearance / Color	Concrete gray
Shelf Life	12 months from date of production if stored properly in original, unopened and undamaged sealed packaging.
Storage Conditions	Store dry at 40–95 °F (4–35 °C) Protect from moisture. If damp, discard material. Condition material to 65–75 °F (18–24 °C) before using.

TECHNICAL INFORMATION

Compressive Strength	<u>1 day</u>	<u>>3000 psi (20.7 MPa)</u>	(ASTM C-109)
	<u>2 day</u>	<u>5,000 psi (34.5 MPa)</u>	
	<u>7 day</u>	<u>6,000 psi (41.4 MPa)</u>	
	<u>28 day</u>	<u>7,000 psi (48.3 MPa)</u>	
Flexural Strength	<u>7 day</u>	<u>800 psi (5.5 MPa)</u>	(ASTM C-293)
	<u>28 day</u>	<u>1,200 psi (8.2 MPa)</u>	
Tensile Strength	<u>7 day</u>	<u>600 psi (4.1 MPa)</u>	(ASTM C-496)
	<u>28 day</u>	<u>750 psi (5.2 MPa)</u>	

APPLICATION INFORMATION

Coverage	<u>Overhead</u>	<u>0.45 ft³/bag</u>
	<u>Horizontal</u>	<u>0.48 ft³/bag</u>
Coverage figures do not include allowance for surface profile and porosity or material waste. Yield in service will vary according to amount of water utilized in the shotcreting process. Estimating should be based on prior experience or actual field evaluation.		
Layer Thickness	Minimum 1/4" (6.4 mm)	
Ambient Air Temperature	> 45 °F (7 °C)	
Substrate Temperature	> 45 °F (7 °C)	

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

- Surface must be clean and sound.
- Remove all deteriorated concrete, dirt, oil, grease, and other bond-inhibiting materials from the area to be repaired.
- Be sure repair area is not less than 1/4" (6.4 mm) in depth.
- Preparation work should be done by scabbler or other appropriate mechanical means to obtain an exposed aggregate surface profile of CSP-6.
- Follow this with a high-pressure water blast to remove all loose materials.
- For better adhesion, substrate should be Saturated Surface Dry (SSD) with clean water prior to application. No standing water should remain during application.

MIXING

- Set up dry-process shotcrete equipment.
- Add SikaShot® NS powder directly into gun.
- Water is to be added at nozzle.

APPLICATION

- At time of application, surfaces should be Saturated Surface Dry (SSD) with no glistening water.
- Apply SikaShot® NS mortar by dry spray process or trowelling for repairing vertical or overhead surfaces.

- Apply SikaShot® NS in accordance with ACI 506-R85, "Guide to Shotcrete". Important factors to observe during shotcreting are nozzle distance (2-6 ft.), angle to substrate (90°), and consistency of mortar.
- This minimizes rebound, creates the smoothest pattern (reduces 'bumps') and properly encases the rebars. The velocity of the material is sufficient if, at a distance of 18 to 24" (4.5-6 m), the material pattern flattens out on contact with the surface and the rebars are encased.
- Immediately after application and before set, mortar consistency should be plastic, like a firm jelly.
- After applying the shotcrete, allow it to stiffen for about 10 minutes before removing bumpy areas with a trowel.
- Before applying the next layer, allow the material to reach initial set. This will take anywhere from 2-4 hours, depending on mix consistency, mix and ambient temperature, wind conditions and humidity.
- Begin and finish a given patch on the same day.
- A natural gun finish may be used. If a gun-finish is too rough, special finishes may be applied. Approximately 5-10 min. after initial set, excess material should be sliced off with a sharp-edged cutting screed. The surface may then be finished to your requirements: broomed for a rough texture, wood-floated for a granular texture, steel-trowelled for a smooth finish.

CURING TREATMENT

- As per ACI recommendations for Portland cement concrete, curing is required.
- Moist cure with wet burlap and polyethylene, a fine mist of water or a water based* compatible curing compound meeting ASTM C-309.
- Curing compounds adversely affect the adhesion of following lifts of mortar, leveling mortar or protective coatings.
- Moist curing should commence immediately after finishing.
- Protect freshly applied mortar from direct sunlight, wind, rain and frost.
- To prevent from freezing, cover with insulating material.

* Pretesting of curing compound is recommended.

LIMITATIONS

- Use only in dry-process shotcreting.
- Color may vary depending on manufacturing location.
- Protect newly applied mortar from rain. If necessary to prevent from freezing, cover with insulating materials.
- For material pre-dampening recommendations, consult Technical Service.
- Not a vapor barrier.
- As with all cement based materials, avoid contact with aluminum to prevent adverse chemical reaction and possible product failure. Insulate potential areas of contact by coating aluminum bars, rails, posts etc. with an appropriate epoxy such as Sikadur 32 Hi-Mod.
- All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet

SikaShot® NS
October 2018, Version 01.01
020302030200000007

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

SikaShotNS-en-US-(10-2018)-1-1.pdf

