

PRODUCT DATA SHEET

Sikalastic® Recoat Primer

TWO-COMPONENT, HIGH SOLIDS, AROMATIC, POLYURETHANE PRIMER

PRODUCT DESCRIPTION

Sikalastic® Recoat Primer is a two component, high solids, liquid applied primer.
Optional: Sikalastic® 700 ACL Accelerator.

USES

- Partially completed new urethane coating systems
- Recover of existing urethane coating systems
- Repair of existing urethane coating systems

CHARACTERISTICS / ADVANTAGES

- High Solids
- Fast Re-Coat Time
- Low Odor
- Low Viscosity

PRODUCT INFORMATION

Packaging	10 gal. Kit, Comp. A-5 gal., Comp. B-5 gal. 4 gal. Kit , 2 X 1 gal. Comp.A, 2 X 1 gal. Comp.B
Shelf Life	12 months in original, unopened containers
Storage Conditions	Store dry at 60–95 °F (15–35 °C). Condition material to 65–85 °F (18–30 °C) before using.
Appearance / Color	Green Gray
Solid content by mass	97.8 % (ASTM D-2697)
Solid content by volume	97.7 % (ASTM D-2697)
Viscosity	Parts A & B Combined: 500 +/- 100 cps

APPLICATION INFORMATION

Coverage	300 sf/gal.
Layer Thickness	5 +/- 1 mils (Dry Film Thickness per Coat)
Substrate Temperature	Sikalastic® Recoat Primer without Sikalastic® 700 ACL Accelerator Min. Application Temperature: 40 °F, and at least 3 °F above the dew point
	Sikalastic® Recoat Primer with Sikalastic® 700 ACL Accelerator Min. Application Temperature: 40 °F, and at least 3 °F above the dew point
Pot Life	Sikalastic® Recoat Primer without Sikalastic® 700 ACL Accelerator
	45 minutes at 40 °F (4 °C), 50 % R.H.
	25 minutes at 75 °F (24 °C), 50 % R.H.
	20 minutes at 90 °F (32 °C), 50 % R.H.
	Sikalastic® Recoat Primer with Sikalastic® 700 ACL Accelerator
	45 minutes at 40 °F (4 °C), 50 % R.H.
25 minutes at 75 °F (24 °C), 50 % R.H.	
20 minutes at 90 °F (32 °C), 50 % R.H.	

Cure Time	Sikalastic® Recoat Primer without Sikalastic® 700 ACL Accelerator
	Allow Sikalastic® Recoat Primer to become tack free before applying the coating. Approximate tack free time is 2-4 hours at 75°F and 50% relative humidity. If the primer has been allowed to remain tack free for more than 12 hours , it is necessary to solvent wipe surface with solvent and reprime the surface. Recommended surface temperature should be greater than 50°F and at least 5°F above the dew point.
	Sikalastic® Recoat Primer with Sikalastic® 700 ACL Accelerator
	Allow Sikalastic® Recoat Primer to become tack free before applying the coating. Approximate tack free time is 1-2 hours at 75°F and 50% relative humidity. If the primer has been allowed to remain tack free for more than 6 hours , it is necessary to solvent wipe surface with solvent and reprime the surface. Recommended surface temperature should be greater than 50°F and at least 5°F above the dew point.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LIMITATIONS

- To avoid dew point conditions during application relative humidity must be no more than 95 % and substrate temperature must be at least 5 °F (3 °C) above measured dew point temperature.
- Minimum ambient and substrate temperature during application and curing of material is 40 °F (4 °C); maximum is 90 °F. Frequent monitoring of ambient and substrate temperature should always be done when applying polyurethane coatings. Note that low temperatures and low humidity will slow down the cure, and high temperatures and high humidity will accelerate it.
- Do not store materials outdoors exposed to sunlight for prolonged periods.
- Do not thin with solvents.
- Precautions should be taken to prevent odors and/or vapors from entering the building/structure, including but not limited to turning off and sealing air intake

vents or other means of ingress for odors and for vapors into the building/structure during product application and cure.

- Do not apply to a porous or damp surface where moisture vapor transmission will occur during application and cure.
- Substrate must be dry prior to application. Do not apply to a frosted, wet or damp surface.
- Do not proceed if rain is eminent within 8–12 hours of application. Allow sufficient time for the substrate to dry after rain or inclement weather as there is the potential for bonding problems.
- When applying over existing coatings compatibility and adhesion testing is recommended.
- Do not subject to continuous immersion.
- Sikalastic® Recoat Primer is not UV stable and must be top coated.
- Sikalastic® Recoat Primer must be kept clean and overcoated within 12 hours, or within 6 hours if Sikalastic® ACL accelerator is used. If this overcoat window is exceeded, contact Sika for recommendations.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

Existing coating surface must be clean, dry and sound with an open texture. Remove dust, grease, bond inhibiting impregnations, waxes, and any other contaminants. All loose and flaking coating, projections, rough spots, etc. should be dressed off to achieve a well-bonded, level surface prior to the application. Mechanically abrade the existing coating as required to obtain an open, textured surface profile. Solvent wipe as allowed by state and local regulations, allow to flash before proceeding.

MIXING

Premix Part A and Part B components using a mechanical mixer (Jiffy) at slow speed to obtain uniform color, making sure to scrape the solids from the bottom and sides of the pail. Pour part B into Part A slowly and while mixing scrape the side of the container, Mix the combined material thoroughly until a homogenous mixture and uniform color is obtained (typically 3 minutes). When mixing use care not to entrap air into the mixture.

Sikalastic® Recoat Primer can be applied with or without Sikalastic® 700 ACL as an accelerator. In the event that Sikalastic® 700 ACL is used, add two quarts Sikalastic® 700 ACL into 10 gallons of mixed primer. Mix the combined material thoroughly until a homogenous mixture and uniform color is obtained (typically 3 minutes). When mixing use care not to entrap air into the mixture

APPLICATION

Apply at the recommended coverage rate, typically 1 gallon per 300 sf, using a phenolic resin core roller. Coverage rate will depend on surface roughness and porosity. Reference Typical Data section for curing and recoat guidelines.

Removal

Remove liquid primer immediately with dry cloth. Once cured, primer can only be removed by mechanical means.

Over Painting

Sikalastic® Recoat Primer without Sikalastic® 700 ACL should be recoated within 12 hours once tack free. Sikalastic® Recoat Primer with Sikalastic® 700 ACL should be recoated within 6 hours once tack free.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA’s Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or

replacement of this product exclusive of any labor costs.
NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet

Sikalastic® Recoat Primer
June 2023, Version 01.02
020812060020000034

SikalasticRecoatPrimer-en-US-(06-2023)-1-2.pdf

