

# Sikadur 31<sup>®</sup>, SBA Normal Set

## Segmental Bridge Adhesive, Normal Set

High-modulus, high-strength, moisture tolerant, epoxy paste adhesive

<b>Description</b>	Sikadur 31, SBA is a unique high-modulus 2- component, moisture-tolerant, solvent-free, epoxy resin system available in three application temperature ranges. A unique high-modulus, structural adhesive for bonding hardened concrete to hardened concrete for segmental bridge construction. The mixed material has the consistency of paste and is a concrete gray color. It conforms to the current ASTM C-881, Type VI requirements, and ASBI guidelines.
<b>Where to Use</b>	<ul style="list-style-type: none"> <li>■ Structural bonding of post-tensioned precast concrete bridge segments.</li> <li>■ Sealing joints between concrete segments.</li> <li>■ For use in segment-by-segment erection.</li> <li>■ Supplied in three temperature grades to meet project requirements. (For cold weather conditions, refer to separate technical data sheet on Sikadur 31, SBA [20°-45°F].)</li> </ul>
<b>Advantages</b>	<ul style="list-style-type: none"> <li>■ Moisture tolerant before, during and after cure.</li> <li>■ High-modulus, high-strength, structural paste adhesive.</li> <li>■ Range of curing times to meet assembly and strength gain requirements.</li> <li>■ Easy to apply, non-sag paste for vertical applications.</li> <li>■ Excellent adhesion to concrete, steel and most construction materials.</li> <li>■ Convenient easy to mix ratios. A:B=2:1 by volume.</li> <li>■ Color-coded components to ensure proper mixing control.</li> </ul>
<b>Coverage</b>	Approximately 12 sq. ft./gal. or 36 sq. ft./3 gal. unit.
<b>Packaging</b>	3 gal. units.

### Typical Data (Material and curing conditions @ 73°F (23°C) and 50% R.H.)

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

<b>Shelf Life</b>	2 years in original, unopened containers.		
<b>Storage Conditions</b>	Store dry at 40°-95°F (4°-35°C). <b>Condition material to 70°-75°F (21°-24°C) before using.</b>		
<b>Color</b>	Concrete gray		
<b>Consistency</b>	Non-sag paste		
<b>Product name</b>	<b>Temp. Range</b>	<b>Mix Ratio, A:B by volume</b>	
Normal Set (40°-60°F)	40°-60°F (4°-15°C)	2:1	
Normal Set (55°-95°F)	55°-95°F (13°-35°C)	2:1	
Normal Set (80°-115°F)	80°-115°F (27°-46°C)	2:1	

Property	ASTM C881 Spec.	SBA NS 40°- 60°F	SBA NS 55°- 95°F	SBA NS 80°-115°F
Pot life, 1 gal., min (ASTM C881)		~ 60	~ 60	~ 60
Compressive Strength, psi (ASTM D695)				
24 hr	2000	2000	2000	2000
48 hr	6000	6000	6000	6000
Open Time (ASTM C881), Hours	1	1	1	1
Contact Strength after open time, 2 day, psi	1000	1000	1000	1000
Bond strength, 2 day, psi (ASTM C882)	1000	1000	1000	1000
Heat deflection Temp., °F (ASTM D648)	≥120	≥120	≥120	≥120

Construction



**PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.**

## How to Use

<b>Surface Preparation</b>	Surface must be clean and sound. It may be dry or damp, but free of standing water and frost. Remove dust, laitance, grease, curing compounds, impregnations, waxes, foreign particles, disintegrated materials and any other contaminants.
<b>Mixing</b>	<b>Pre-mix each component.</b> Wear chemical resistant gloves and safety goggles. Mix all of Part 'A' with all of Part 'B'. Mix thoroughly for a minimum of 3 minutes with a low-speed (400-600 rpm) drill fitted with a mixing Sika paddle until a uniform gray color is achieved. Scrape down the sides of the mixing pail and ensure there are no streaks of unmixed epoxy before applying. Mix only that quantity which can be used within its pot life.
<b>Application</b>	Apply the neat mixed Sikadur 31, SBA to the concrete surface using a trowel, spatula or glove protected hand; work into surface, especially if it is damp. Spread to a thickness of 1/8" (3 mm) to one face or 1/16" (1.5 mm) on both faces, depending upon project requirements. Segments must be post-tensioned within the open time of the epoxy.
<b>Removal</b>	Ventilate area. Confine spill. Collect with absorbent material, flush area with water. Dispose of in accordance with current, applicable local, state and federal regulations. Uncured material can be removed with approved solvent. Follow solvent manufacturer's instructions for use and warnings. Cured material (when combined with component 'B') can only be removed mechanically.
<b>Limitations</b>	<ul style="list-style-type: none"> <li>■ Do not thin Sikadur 31, SBA. Solvents will prevent proper cure.</li> <li>■ Use correct temperature range material for prevailing conditions.</li> <li>■ Use correct setting material (normal or slow) depending on method of erection.</li> <li>■ Not for use as an adhesive for fresh, plastic portland cement concrete or mortar.</li> <li>■ Lower temperatures will prolong cure time. Higher temperatures will rapidly accelerate cure time.</li> <li>■ Use of product outside of designated temperature range is not recommended.</li> <li>■ Not an aesthetic product. Color may alter due to variations in lighting and/or UV exposure.</li> </ul>

**PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.**

KEEP CONTAINER TIGHTLY CLOSED. KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. FOR PROFESSIONAL USE ONLY.

For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheet before using the product. In case of emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at <http://usa.sika.com/> or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. SALE OF SIKA PRODUCTS ARE SUBJECT SIKA'S TERMS AND CONDITIONS OF SALE AVAILABLE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING 201-933-8800.

Visit our website at [usa.sika.com](http://usa.sika.com)

1-800-933-SIKA NATIONWIDE

**Regional Information and Sales Centers.** For the location of your nearest Sika sales office, contact your regional center.

**Sika Corporation**  
201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: 800-933-7452  
Fax: 201-933-6225

**Sika Canada Inc.**  
601 Delmar Avenue  
Pointe Claire  
Quebec H9R 4A9  
Phone: 514-697-2610  
Fax: 514-694-2792

**Sika Mexicana S.A. de C.V.**  
Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



Sika, SikaRepair, and SikaLatex are registered trademarks. Printed in Canada.

