

Pebbletex Vulcan NC - Section 07 24 19

Water-drainage polymer-based EIFS incorporating mineral wool insulation, vertical drainage channels and an air/water-resistive barrier

INTRODUCTION

This specification has been assembled to enable the design professional to select or delete sections to suit the project requirements and is intended to be used in conjunction with LaHabra [®] typical details, product bulletins, technical bulletins, etc.

DESIGN RESPONSIBILITY

It is the responsibility of both the specifier and the purchaser to determine if a product is suitable for its intended use. The designer selected by the purchaser shall be responsible for all decisions pertaining to design, detail, structural capability, attachment details, shop drawings and the like. The LaHabra® brand of Sika Corporation US (herein referred to as "Sika") has prepared guidelines in the form of specifications, typical application details, and product bulletins to facilitate the design process only. Sika is not liable for any errors or omissions in design, detail, structural capability, attachment details, shop drawings or the like, whether based upon the information provided by Sika or otherwise, or for any changes which the purchasers, specifiers, designers or their appointed representatives may make to Sika published comments.

Designing and Detailing a Pebbletex Vulcan NC Wall System

General: The system shall be installed in strict accordance with current recommended published details and product specifications from the system's manufacturer.

A. Wind Load

- 1. Maximum deflection not to exceed L/240 under positive or negative design loads.
- 2. Design for wind load in conformance with local code requirements.

B. Substrate Systems

- 1. Acceptable substrates are: PermaBase® Cement Board and other cement-boards conforming with ASTM C1325 (Type A-exterior); poured concrete/unit masonry; ASTM C1177 type sheathings, including, Weather Defense™ Platinum sheathing, GreenGlass® sheathing, eXP™ sheathing, GlasRoc® sheathing, Securock™ glass-mat sheathing, and DensGlass® exterior sheathing DensElement (sheathing only); gypsum sheathing (ASTM C79/C1396); Huber Zip (sheathing only) Exposure I or exterior plywood (Grade C/D or better); or Exposure I OSB; fire treated wood sheathing: Pyro-Guard® and Dricon® plywood and FlameBlock® OSB.
- 2. Painted and otherwise coated surfaces of brick, unit masonry, stucco and concrete shall be inspected and prepared as approved by Sika before application. The applicator shall verify that the proposed substrate is acceptable prior to the Pebbletex Vulcan NC Wall System installation.
- 3. The substrate systems shall be engineered with regard to structural performance by others.

C. Moisture Control

- 1. Prevent the accumulation of water behind the EIFS, either by condensation or leakage through the wall construction, in the design and detailing of the wall assembly.
 - a. Provide flashing to direct water to the exterior where it is likely to penetrate components in the wall assembly, including, above window and door heads, beneath window and door sills, at roof/wall intersections, decks, abutments of lower walls with higher walls, above projecting features, and at the base of the wall and anywhere else required by local code.
 - b. Air Leakage Prevention: Provide continuity of air barrier system at foundation, roof, windows, doors and other penetrations through the system with connecting and compatible air barrier components to minimize condensation and leakage caused by air movement.
 - c. Vapor Diffusion and Condensation: Perform a dew point analysis of the wall assembly to determine the potential for accumulation of moisture in the wall assembly as a result of water vapor diffusion and condensation. Adjust insulation thickness and/or other wall assembly components accordingly to minimize the risk of condensation. Avoid the use of vapor retarders on the interior side of the wall in warm, humid climates.
- D. Impact Resistance: Provide ultra-high impact resistance to a minimum height of 6' (1.8m) above



finished grade at all areas accessible to pedestrian traffic and other areas exposed to abnormal stress or potential impact. Indicate the areas with impact resistance requirements other than "Standard" on contract drawings.

E. System Joints

- 1. Typical locations for system expansion joints are at building expansion joints, at prefabricated panel joints, floor lines of wood frame construction or where slip tracks are used in steel frame construction, where substrates change and where structural movement is anticipated. It is the sole responsibility of the project design team, including the architect, engineer, etc., to ultimately determine specific expansion joint placement, width and design. Detail specific locations in construction drawings.
- 2. Sealant joints are required at all penetrations through the Pebbletex Vulcan NC Wall System (windows, doors, etc.)
- 3. Specify compatible closed cell backer rod and acceptable sealant that has been evaluated in accordance with ASTM C1382, "Test Method for Determining Tensile Adhesion Properties of Sealants When Used in Exterior Insulation and Finish System (EIFS) Joints," and that meets minimum 50% elongation after conditioning.
- 4. The system must be properly terminated (back wrapped a min. of 2", properly sealed, flashed) at all penetrations, lighting fixtures, electrical outlets, hose bibs, dryer vents, etc.
- **F. Grade Condition:** The Pebbletex Vulcan NC Wall System is not intended for use below grade or on surfaces subject to continuous or intermittent immersion in water or hydrostatic pressure. Ensure a minimum 6" (152 mm) clearance above grade or as required by code, a minimum 1" (25 mm) clearance above finished grade (sidewalk/concrete flatwork).

G. Trim, Projecting Architectural Features

- (NOTE TO SPECIFIER: Installation of the LaHabra outside the slope guidelines referenced in this specification may still qualify for a standard warranty; however, low sloping EIFS conditions are subject to extreme heat, increased maintenance and premature deterioration of the system shall be expected and any deleterious effects caused by the lack of slope will not be the responsibility of Sika. LaHabra wall systems are designed and tested to be applied to vertical surfaces. The design professional has the option to build according to his/her project needs. The design professional must also consider geography, climate, building orientation, wall orientation and adjacent building components when designing with EIFS. The slope guidelines referenced below are provided to assist the owner and/or design professional. Final design of any building is the responsibility of the design professional.)
- 1. Minimum slope for all projections shall be 1:2 (27°) with a maximum length of 12" (30.5 cm) [6" in 12" (e.g. 15 cm in 30.5 cm)]. Increase slope for northern climates to prevent accumulation of ice/snow on the surface.
- 2. Mineral wool feature bands are applied over the base layer of mineral wool insulation and attached with LaHabra EIFS adhesive and Wind-Lock ULP-302 plates and fasteners, into supporting structure. Reinforced base coat shall be applied continuously across the feature band. Thickness of the bands will be limited by available fastener lengths.
- 3. Other features with more complicated profiles such as cornices are typically manufactured from EPS insulation these shapes must be pre-wrapped with LaHabra base coat and reinforcing mesh. Cornice features are limited to 12" (305 mm) thickness and attached with LaHabra EIFS adhesive to the mineral wool insulation. Supplemental mechanical attachment may be required based on the shape configuration, verify availability of fasteners for adequate fastening prior to start of work. Ensure reinforced base coat is applied in a continuous manner from mineral wool onto feature.

H. Coordination with other trades

- 1. Evaluate adjacent materials such as windows, doors, etc. for conformance to manufacturer's details. Adjacent trades shall provide scaled shop drawings for review.
- 2. Air seals at any joints/gaps between adjoining components (penetrations, etc.) are of primary importance to maintain continuity of an air barrier system and must be considered by the design professional in the overall wall assembly design. Install air seals between the primary air/water-resistive barrier and other wall components (penetrations, etc.) in order to maintain continuity of an air barrier system.
- Provide site grading such that Pebbletex Vulcan NC Wall System terminates a minimum of 6" (152

- mm) above grade or as required by code.
- 4. Provide protection of rough openings in accordance with LaHabra Finestop air/water-resistive barrier product bulletin and published details before installing windows, doors, and other penetrations through the wall.
- 5. Install copings and sealant immediately after installation of the Pebbletex Vulcan NC Wall System and when LaHabra coatings are completely dry.

TECHNICAL INFORMATION

Consult Sika Facades' Technical Services Department for specific recommendations concerning all other applications. Consult the LaHabra website, usa.sika.com/lahabra, for additional information about products, systems and for updated literature.

PART 1 GENERAL

NOTE TO SPECIFIER: Items in blue/underlined indicate a system option or choice of options. Throughout the specification, delete those which are not required or utilized.

1.01 SECTION INCLUDES

- A. Refer to all drawings and other sections of this specification to determine the type and extent of work therein affecting the work of this section, whether or not such work is specifically mentioned herein.
- B. Pebbletex Vulcan NC Wall System: Composite wall Exterior Insulation and Finish System consisting of air/water-resistive barrier, adhesive, mineral wool insulation, base coat, reinforcing mesh, and finish coat (except insulation, all materials must be produced by Sika).
- C. LaHabra products are listed in this specification to establish a standard of quality. Any substitutions to this specification shall be submitted to and receive approval from the Architect at least 10 days before bidding. Proof of equality shall be borne by the submitter.
- D. The system type shall be LaHabra Pebbletex Vulcan NC Wall System as manufactured by Sika Corporation US, Lyndhurst, NJ.

1.02 RELATED SECTIONS

- A. Section 03 00 00 Concrete substrate
- B. Section 04 00 00 Masonry substrate
- C. Section 05 40 00 Cold-formed metal framing
- D. Section 06 16 00 Sheathing
- E. Section 06 11 00 Wood framing
- F. Section 07 27 00 Air barriers
- G. Section 07 62 00 Sheet Metal Flashing and Trim
- H. Section 07 65 00 Flexible flashing
- I. Section 07 90 00 Joint protection
- J. Section 08 00 00 Openings
- K. Section 09 22 00 Supports for plaster and gypsum board
- L. Section 09 22 16 Non-structural metal framing
- M. Section 09 29 00 Gypsum board

1.03 DEFINITIONS

- A. Exterior Insulation and Finish System: Exterior assembly comprised of adhesive, rigid insulation, base coat, reinforcing mesh, and finish coat.
- B. Class PB Systems: A class of EIFS where the base coat varies in thickness depending upon the number of layers or thickness of reinforcing mesh. The reinforcing material is glass fiber mesh, which is embedded into the base coat at the time of installation. The base coat shall be applied to achieve reinforcing mesh embedment with no reinforcing mesh color visible, nominal thickness of 1/16" (1.6 mm). Protective finish coats, of various thicknesses, in a variety of textures and colors, are applied over the base coat.
- C. Water-Drainage EIFS: A wall cladding design with an exterior surface for primary weather protection and aesthetics, which incorporates an inner secondary air/water-resistive barrier to accommodate incidental moisture and direct it to the exterior.

1.04 SUBMITTALS

- A. Submit under provisions of Section [01 33 00]
- B. Code Compliance: Provide manufacturer's applicable code compliance report.
- C. Samples: Submit [two] [x] [millimeter] [inch] size samples of Pebbletex Vulcan NC Wall System illustrating finish coat color and texture range.
- D. Certificate: System manufacturer's approval of applicator.
- E. Sealant: Sealant manufacturer's certificate of compliance with ASTM C1382.
- F. System manufacturer's current specifications, typical details, system overview and related product literature which indicate preparation required, storage, installation techniques, jointing requirements and finishing techniques.

1.05 QUALITY ASSURANCE

- A. Manufacturer: More than 10 years in the EIFS industry, with more than 1000 completed EIFS projects.
- B. Applicator: Approved by Sika Facades in performing work of this section.
- C. Regulatory Requirements: Conform to applicable code requirements for EIFS.
- D. Field Samples
 - 1. Provide under provisions of Section [01 43 36] [01 43 39].
 - 2. Construct one field sample panel for each color and texture, [x] [meters] [feet] in size of system materials illustrating method of attachment, surface finish color and texture.
 - 3. Prepare each sample panel using the same tools and techniques to be used for the actual application.
 - 4. Locate sample panel where directed.
 - 5. Accepted sample panel [may] [may not] remain as part of the work.
 - 6. Field samples shall be comprised of all wall assembly components including substrate, air/water-resistive barrier, insulation board, base coat, reinforcing mesh, primer (if specified), finish coat, and typical sealant/flashing conditions.

E. Testing:

1. General Air/Water-Resistive Barrier Minimum Performance:

TEST	METHOD	CRITERIA	RESULTS
Water-resistive barrier coatings used under EIFS	ASTM E2570		Meets all performance requirements
Air Leakage of Air Barrier Assemblies	ASTM E2357	0.04 cfm/ft² @ 1.57 psf (0.2 l/ (s.m²) @75 Pa)	0.0001 cfm/ft ² @ 1.57 psf (0.0007 l/s.m ² @ 75 Pa) positive / post conditioning 0.0003 cfm/ft ² @1.57 psf (0.0014 l/s.m ² @ 75 Pa) negative / post conditioning
Air Permeance of Building Materials	ASTM E2178	0.004 cfm/ft² @ 1.57 psf (0.02 l/ (s.m²) @75 Pa)	0.00098 cfm/ft² @ 1.57 psf (0.0049 l/s.m² @ 75 Pa)
Rate of Air Leakage	ASTM E283		0.0185 l/s·m² @ 75 Pa (0.0037 cfm/ft² @ 1.57 psf)
Water Vapor Transmission	ASTM E96	Report value	Finestop RA - 18 Perms (grains/Hr. in Hg. ft²) @ 10 mils wet film thickness Finestop RS 18 Perms (grains/Hr. in Hg. ft²) @ 12 mils wet film thickness Finestop RA/RS - 14 Perms (grains/Hr. in Hg. ft²) @ 20 mils wet film thickness Finestop VB - 0.09 Perms (grains/Hr. in Hg. ft²) @ 26 mils wet film thickness
Pull-Off Strength of Coatings	ASTM D4541	Min. 110 kPa (15.9 psi) or substrate failure	Pass - Tested over exterior gypsum sheathing, ASTM C1177 glass-mat sheathing, cement board, OSB, plywood; PVC and galvanized flashing
Nail Sealability (without Sheathing Fabric)	ASTM D1970	No water penetration at galvanized roofing nail penetration under 127 mm (5") head of water after 3 days at 4° C (40° F)	Pass
Surface Burning	ASTM E84	Flame Spread < 25 Smoke Development < 450	Meets Class A: Flame spread =15 Smoke developed = 95

2. Air/Water-Resistive Barrier ICC-ES AC-212:

TEST	METHOD	CRITERIA	RESULTS
Sequential Testing: 1. Structural 2. Racking 3. Restrained Environmental Conditioning 4. Water Penetration	1. ASTM E 1233 Procedure A 2. ASTM E 72 3. ICC-ES AC-212 4. ASTM E 331	No cracking at joints or interface of flashing No water penetration after 15 min @ 137 Pa (2.86 psf)	Pass - Tested over OSB and gypsum sheathing No water penetration after 90 min @ 299 Pa (6.24 psf)
Sequential Testing: 1. UV Light Exposure 2. Accelerated Aging 3. Hydrostatic Pressure Test	1. ICC-ES AC-212 2. ICC-ES AC-212 3. AATCC 127- 1985	No cracking or bond failure to substrate No water penetration after 21.7 in (550 mm) water for 5 hours	Pass
Freeze-Thaw	ASTM E 2485 (Method B)	No sign of deleterious effects after 10 cycles	Pass - Tested over exterior gypsum sheathing, ASTM C1177 glass-mat sheathing, cement board, OSB, plywood
Water Resistance	ASTM D 2247	No deleterious effects after 14- day exposure	Pass - Tested over exterior gypsum sheathing, ASTM C1177 glass-mat sheathing, cement board, OSB, plywood
Tensile Bond	ASTM C 297	Minimum 103 kPa (15 psi)	Pass - Tested over exterior gypsum sheathing, ASTM C1177 glass-mat sheathing, cement board, OSB, plywood, CMU; PVC and galvanized flashing
Tensile Bond (after freeze- thaw)	ASTM C 297	Minimum 103 kPa (15 psi) avg; no failure after 10 cycles freeze-thaw	Pass

3. Air/Water-Resistance Barrier ICC-ES AC 148:

TEST	METHOD	CRITERIA	RESULTS
Sequential Testing: 1. UV Light Exposure	1. ICC-ES AC 148 2. ICC-ES AC 148	No cracking or bond failure to substrate	Pass
Accelerated Aging Hydrostatic Pressure Test	3. AATCC 127- 1985	No water penetration after 21.7 in (550 mm) water for 5 hours	
Peel Adhesion	ASTM D 3330 Method F	After UV Exposure After Accelerated Aging After Elevated Temperature Exposure After Water Immersion	Pass - tested over ASTM C1177 glass-mat sheathing, OSB, plywood, PVC and uncoated aluminum
Nail Sealability after Thermal Cycling	ASTM D 1970 (Modified), AAMA 711	No water penetration at galvanized roofing nail penetration under 31 mm (1.2") head of water after 24 hours at 4° C (40° F)	Pass
Tensile Strength after UV Exposure	ASTM D 5034, AAMA 711	Minimum 0.5 N/mm (2.9 lbs./in)	Pass
Cold Temperature Pliability	ASTM D 1970, AAMA 711	No cracking after bending around a 25 mm (1") mandrel after 2-hour exposure to -18° C (0° F)	Pass
Resistance to Peeling	AAMA 711	No signs of distress or failure after 24 hours of exposure at room temperature, 50° C (122° F), 65° C (149° F), 80° C (176° F)	Pass

4. Pebbletex Vulcan NC Wall System and Component Performance:

TEST	METHOD	CRITERIA	RESULTS
EIFS and EIFS with	ASTM E2568 and		Meets all performance requirements
Drainage	ICC-ES AC 235		
Drainage Efficiency	ASTM E2273	90% Minimum	Pass - 92%
Transverse Wind-load	ASTM E330	Steel stud framing (18 gauge x 3	Average ultimate loads ¹ :
		5/8") 16"o.c., 1/2" gypsum	- 115 psf (5506 Pa)
		sheathing, 4" Sheathing Fabric	+ 176 psf (8426 Pa)
		over sheathing joints, Finestop	
		RA/RS/VB, LaHabra Adhesive,	
		mineral wool insulation board (9	
		fasteners per board), LaHabra	
		Base Coat, LaHabra Standard	
		Mesh 4 and LaHabra Finish.	
Transverse Wind-load	ASTM E330	Wood assembly (2" x 4") 16"o.c.,	Average ultimate loads ¹ :

		7/16" Exposure 1 OSB, 4"	- 194 psf (9288 Pa)
		Sheathing Fabric over sheathing	+ 142 psf (6798 Pa)
		joints, Finestop RA/RS/VB,	+ 142 psi (0790 Fa)
		LaHabra Adhesive, mineral wool	
		insulation board (9 fasteners per	
		board), LaHabra Base Coat,	
		LaHabra Standard Mesh 4,	
		LaHabra Finish.	
Tensile Bond	ASTM	Minimum 15 psi (103 kPa)	Pass
	C297/E2134		
Water Penetration	ASTM E 331	No water penetration after 15	Pass, no water penetration for both durations
		minutes @ 2.86 psf (137 Pa)	and pressures
		Additional testing performed for 2	
		hours @ 6.24 psf (299 Pa)	
Fire Endurance	ASTM E119	Maintain fire resistance of existing	Does not detract from the existing fire rating of
		rated assembly	base wall construction
Radiant Heat Exposure	NFPA 268	Not Applicable, based on previous testing with foam plastic insulation and the	
		substitution of noncombustible mine	ral wool insulation
Intermediate Scale Multi-	NFPA 285 / UBC	Not Applicable, based on previous testing with foam plastic insulation and the	
Story Fire Test	Standard 26-9	substitution of noncombustible mineral wool insulation	
Surface Burning	ASTM E84 / UL	Flame spread < 25	All components of the system meet Class A
· ·	723	Smoke developed < 450	performance (FS < 25; SD < 450)
Abrasion Resistance	ASTM D968	No Cracking or loss of film integrity	Finish Coat not worn through after 686 liters of
		at 528 gt. (500L) of sand	falling sand
Accelerated Weathering	ASTM G 155	No deleterious effects after 2000	Pass
ŭ .		hours, viewed under 5x	
		magnification.	
Accelerated Weathering	ASTM G 154	No deleterious effects after 2000	Pass - No deleterious effects after 7500
(Lamina)	(formerly G53)	hours.	hours.
Freeze-Thaw	ASTM É2485	No deleterious effects after 10	Pass
		cycles, viewed under 5 x	
		magnification	
Mildew Resistance	Mil Std 810B	No fungus growth after 28 days	Pass
	Method 508		
Salt Fog Resistance	ASTM B117	No deleterious effects after 300	Pass
-9	=	hours	
Water Resistance of	ASTM D 2247	No deleterious effects after 14	Pass
Coating in 100% R.H.	= ==	days exposure	
		1 / 1/2	

¹ No failure in the LaHabra materials; failure in framing and/or sheathing connections

5. Reinforcing Mesh Testing and Impact Resistance over Mineral Wool Insulation

TEST	METHOD	CRITERIA	RESULTS
Alkali Resistance of Reinforcing Mesh	ASTM E 2098	Greater than 120 pli (21 dN/CM) retained tensile strength	Pass (all mesh)
STANDARD MESH 4	ASTM E2486 (formerly EIMA 101.86)	25-49 inch-lbs. (2.8-5.6 j)	Pass
INTERMEDIATE 6	ASTM E2486 (formerly EIMA 101.86)	50-89 inch-lbs. (5.7-10.1 j)	Pass
INTERMEDIATE 12	ASTM E2486 (formerly EIMA 101.86)	50-89 inch-lbs. (5.7-10.1 j)	Pass
INTERMEDIATE 12 & STANDARD MESH 4	ASTM E2486 (formerly EIMA 101.86)	90-150 inch-lbs. (10.2-17.0 j)	Pass
STRONG 15 & STANDARD MESH 4	ASTM E2486 (formerly EIMA 101.86)	150 inch-lbs. (17 j)	Pass
ULTA HIGH 20 & STANDARD MESH 4	ASTM E2486 (formerly EIMA 101.86)	150 inch-lbs. (17 j)	Pass

- **1.06 DELIVERY, STORAGE AND HANDLING**A. Deliver, store and handle products under provisions of Section [01 65 00] [01 66 00] [].
- B. Deliver Sika materials in original unopened packages with manufacturer's labels intact.

- C. Protect Sika materials during transportation and installation to avoid physical damage.
- D. Store Sika materials in a cool, dry place protected from freezing. Store at no less than 40°F/4°C (50°F/10°C GRANITE AND STONE finish).
- E. Store MAXFLASH at a minimum of 40F. In cold weather, keep containers at room temperature for at least 24 hours before using.
- F. Store insulation boards flat and protected from direct sunlight and extreme heat.
- G. Store Reinforcing Mesh, SHEATHING FABRIC and FLASH SEAL NP flexible flashing in a cool, dry place protected from exposure to moisture.

1.07 PROJECT/SITE CONDITIONS

- A. Do not apply Sika material in ambient temperatures below 40°F/4°C (50°F/10°C for GRANITE AND STONE Finish). Provide properly vented, supplementary heat during installation and drying period when temperatures less than 40°F/4°C (50°F/10°C for GRANITE AND STONE Finish) prevail. Do not apply in ambient temperature above 100°F (38°C) or surface temperature above 120°F (49°C).
- B. Do not apply materials to frozen surfaces.
- C. Maintain ambient temperature at or above 40°F/4°C (50°F/10°C for GRANITE AND STONE Finish) during and at least 24 hours after material installation and until dry.
- D. Under average conditions [70 °F (21 °C), 50% Relative Humidity] finish will be dry within 24 hours. Drying time is dependent on humidity, air temperature, sun exposure, surface conditions and finish thickness. Lower temperature, higher humidity and application in shaded areas will extend drying time. Protect finish from rain or other precipitation and temperatures less than 40°F (4°C) for a minimum of 24 hours or until dry.

1.08 SEQUENCING AND SCHEDULING

- A. Coordinate and schedule installation of Pebbletex Vulcan NC Wall System with related work of other sections.
- B. Coordinate and schedule installation of trim, flashing, and joint sealers to prevent water infiltration behind the system.

1.09 WARRANTY

- A. Provide Sika standard warranty for Pebbletex Vulcan NC Wall System installations under provisions of Section [01 70 00].
- B. Comply with Sika Facades project review requirements and notification procedures to assure qualification for warranty.

PART 2 PRODUCTS 2.01 MANUFACTURERS

A. LaHabra Pebbletex Vulcan NC Wall System (Class PB System) manufactured by Sika Corporation US.

2.02 MATERIALS

NOTE TO SPECIFIER: Items in blue/underlined indicate a system option or choice of options. Throughout the specification, delete those which are not required or utilized. Contact Sika Facades' Technical Service Department for further assistance.

A. Air/Water-Resistive Barrier Components:

- 1. Air/Water-Resistive Barrier: (Required, Select a, b or c)
 - a. FINESTOP R: A one-component fluid-applied vapor permeable air/water-resistive barrier.
 - b. FINESTOP RS: A one-component fluid-applied vapor permeable air/water-resistive barrier for use with airless spray equipment.
 - c. FINESTOP VB: A one-component fluid-applied vapor impermeable air/water-resistive barrier.
- 2. Rough Opening and Joint Treatment: (Required, Select a or b)
 - <u>a. SIKAWALL SHEATHING FABRIC: A spun-bonded non-woven reinforced polyester web for use with Finestop fluid applied air/weather-resistive barriers.</u>
 - <u>b.</u> <u>SIKAWALL MAXFLASH: A one-component elastomeric material for use as a flexible flashing membrane.</u>

- SIKAWALL FLASH SEAL NP Transitional Membrane / Expansion Joint Flashing: A 32-mil thick self-adhering and self-sealing composite membrane of polyester fabric and butyl adhesive. Compatible with Finestop liquid air/weather resistive barriers.
- B. Adhesives/Base Coats: (Required, Select One or More)
 - 1. A/BC Base Coat: A 100% acrylic base coat, field-mixed with Portland cement. It has a creamy texture that is easily spread.
 - 2. A/BC 1-STEP Base Coat: A dry-mix polymer adhesive and base coat containing Portland cement and requiring only water for mixing.
 - 3. <u>FINEGUARD Base Coat: A 100% acrylic-based, water-resistant base coat, field-mixed with Portland cement.</u>
 - 4. <u>FINEBUILD Base Coat: A 100% acrylic, fiber-reinforced base coat, adhesive and leveler that is</u> field-mixed with Portland cement.
- NOTE TO SPECIFIER: Portland cement is not required if A/BC 1-STEP Base Coat is specified.
- C. Portland cement: Conform to ASTM C150, Type I, IL (ASTM C595), II, or I/II, grey or white; fresh and free of lumps.
- **D. Water:** Clean and potable without foreign matter.
- E. Noncombustible Mineral Wool Insulation Board: (Required, Select One or More)
 - 1. ROCKWOOL: ASTM C612 Type IVA; non-combustible per ASTM E136; Flame Spread 0, Smoke Developed ≤ 15 per ASTM E84; R-value @ 75°F (24°C) = 4.0 per inch; Size: 2' x 4' (0.6 m x 1.22 m). Length, width and thickness: tolerance of plus or minus ½" (12.7 mm) length, ¼" (6.4 mm) width and 1/8" (3.2 mm) thickness.
 - a. Frontrock™ DD (Dual Density):

ASTM C165 – Compressive Strength: 522 psf (25 kPa) @ 10% compression Minimum Thickness 2.5" | Maximum Thickness 4" |

¹Thickness as indicated on drawings

b. Frontrock™ Mono Density:

ASTM C165 – Compressive Strength: 940 psf (45 kPa) @ 10% compression

Minimum Thickness 1.5" Maximum Thickness 4" 1

¹Thickness as indicated on drawings

- Mineral Wool, ASTM C612 Type IVA; minimum compressive strength of 522 psf (25 kPa) @ 10% compression per ASTM C165; Flame Spread <25, Smoke Developed < 450 per ASTM E84; Non-combustible per ASTM E136; R-value @ 75°F (24°C) = 4.0 per inch. Thickness as indicated on drawings [minimum 1.5" (38 mm), maximum 4" (101mm)]. Size: 2' x 4' (0.6 m x 1.22 m). Length, width and thickness: tolerance of plus or minus ½" (12.7 mm) length, ¼" (6.4 mm) width and 1/8" (3.2 mm) thickness. Consult Sika Facades' Technical Services Department on other insulation types before application.
- **F. Mechanical Fasteners:** ULP-302 by Wind-Lock Corp high density plastic washers, 1 ¾ inches (44 mm) in diameter, used in combination with corrosion resistant screws that are suitable for the substrate.
 - Steel: minimum 3/8" (10mm) and 3 thread penetration of steel with threads engaged with steel.
 - Wood: minimum 3/4" (19mm) into wood framing.
 - Masonry: minimum 1" (25mm).
- **G. Reinforcing Mesh:** Balanced, open-weave glass, fiber reinforcing mesh, twisted multi-end strands treated for compatibility with LaHabra Base Coats. (*Required, Select One or More*)
 - 1. LAHABRA STANDARD MESH 4: Standard weight, 4 oz.
 - 2. SIKAWALL INTERMEDIATE 6: Medium weight, 6 oz.
 - 3. SIKAWALL INTERMEDIATE 12: Intermediate weight, 12 oz.
 - 4. <u>SIKAWALL STRONG 15: Heavy weight, 15 oz. used only in combination with STANDARD MESH 4</u> or INTERMEDIATE 6.
 - 5. <u>SIKAWALL ULTRA HI 20: Heavy weight, 20 oz. used only in combination with STANDARD MESH 4 or INTERMEDIATE 6.</u>
 - 6. <u>SIKAWALL CORNER MESH: Intermediate weight, pre-marked for easy bending, for reinforcing at</u> exterior corners.
- H. <u>SIKAWALL COLOR ADVANCE Coating (Optional)</u>: A 100% acrylic-based coating. It is designed for spray, roller or brush-application over EIFS, for use in sealant joints over reinforced base coat or over

- finish coat with minimum change in finish texture or sheen.
- I. <u>SIKAWALL TINTED PRIMER (Optional)</u>: A 100% acrylic-based primer that helps alleviate shadowing and enhances performance of the LaHabra wall systems. Color to closely match the selected LaHabra Finish Coat color.
- J. Finish Coat: (Required, Select One or More Finishes and Textures)

NOTE: Use of smooth/fine finish textures is not advised, however if desired to achieve design requirements, a large-scale mock-up is recommended.

- 1. <u>PEBBLEREX Finish: 100% acrylic polymer finishes with advanced technology to improve long-term performance and dirt pick-up resistance; air cured, compatible with base coat; LaHabra finish color [] as selected; finish texture:</u>
 - a. <u>NATURAL SWIRL: Has a medium "worm-holed" appearance which is achieved by the random aggregate sizes in the Finish. The "worm-holed" look can be circular, random, vertical or horizontal.</u>
 - b. LIMESTONE: Utilizes uniformly sized aggregates for a uniform, fine texture.
 - c. FINETEX: Can achieve a wide variety of free-formed, textured appearances, including stipple and skip-trowel.
 - d. MOJAVE: Provides a uniform, "pebble" appearance.
- 2. <u>PEBBLETEX TERSUS Finish: Modified acrylic-based finish with water repellent properties,</u> compatible with base coat; LaHabra Finish color [] as selected; finish texture:
 - a. NATURAL SWIRL: Has a medium "worm-holed" appearance which is achieved by the random aggregate sizes in the Finish. The "worm-holed" look can be circular, random, vertical or horizontal.
 - b. LIMESTONE: Utilizes uniformly sized aggregates for a uniform, fine texture.
 - c. <u>FINETEX</u>: Can achieve a wide variety of free-formed, textured appearances, including stipple and skip-trowel.
 - d. MOJAVE: Provides a uniform, "pebble" appearance.
- 3. Specialty Finishes: 100% acrylic polymer finishes that can be hand-troweled to simulate stone or create a time-honored, mottled tone-on-tone look that achieves a soft and weathered patina over time.
 - a. SIKAWALL ENCAUSTO VERONA: Utilizes uniformly sized aggregate to achieve a free-formed, flat texture. It can be used to achieve a mottled look and unlimited tone on tone designs by combining multiple colors.
 - b. <u>SIKAWALL METALLIC</u>: Has a pearlescent appearance. It utilizes uniformly sized aggregates for a uniform fine texture.
 - c. <u>SIKAWALL GRANITE AND STONE: Is a factory-mixed, reflective stone finish consisting of colored aggregate and large black mica flakes in a 100% acrylic transparent binder that provides a classic granite or marble-like textured finished appearance.</u>
- 4. SIKAWALL CHROMA Finish: 100% acrylic polymer-based finish with integrated high performance colorants for superior fade resistance, compatible with base coat; LaHabra Finish color [] as selected; finish texture:
 - a. F1.0: Utilizes uniformly sized aggregates for a uniformly fine texture.
 - b. M1.5: Provides a uniform "pebble" appearance.
 - c. R1.5: Has a medium "worm-holed" appearance which is achieved by the random aggregate sizes in the Finish. The "worm-holed" look can be circular, random, vertical or horizontal.

2.03 ACCESSORIES

A. Window/Door Drip Edge: Rigid polyvinyl chloride (PVC), UV resistant for exterior use, with a drip edge, as furnished by Plastic Components, Inc. or equal. PVC accessories shall conform to ASTM D1784 and D4216; Sheet metal flashing conforming to ASTM A653

PART 3 EXECUTION

3.01 EXAMINATION

- A. Site Conditions: Verify project site conditions under provisions of Section [01 00 00].
- B. Walls:
 - 1. Substrates:

- a. Acceptable substrates are: PermaBase® Cement Board and other cement-boards conforming with ASTM C1325 (Type A-exterior); poured concrete/unit masonry; ASTM C1177 type sheathings, including, Weather Defense™ Platinum sheathing, GreenGlass® sheathing, eXP™ sheathing, GlasRoc® sheathing, Securock™ glass-mat sheathing, and DensGlass® exterior sheathing DensElement (sheathing only); gypsum sheathing (ASTM C79/C1396); Huber Zip (sheathing only) Exposure I or exterior plywood (Grade C/D or better); or Exposure I OSB; fire treated wood sheathing: Pyro-Guard® and Dricon® plywood and FlameBlock® OSB. Consult the Sika Facades' Technical Services Department for all other applications.
- b. Wall sheathing must be securely fastened per applicable building code and sheathing manufacturer's requirements.
- c. Examine surfaces to receive Pebbletex Vulcan NC Wall System and verify that substrate and adjacent materials are dry, clean, sound, and free of releasing agents, paint, or other residue or coatings. Verify substrate is flat, free of fins or planar irregularities greater than 1/4" in 10' (6.4 mm in 3 m).

2. Flashings:

- a. All flashings are by others and must be installed in accordance with specific manufacturer's requirements. Where appropriate, end-dams must be provided.
- b. Openings must be flashed prior to window/door, HVAC, etc. installation. Refer LaHabra Finestop published product data sheet and details for further information Windows and openings shall be flashed according to design and Building Code Requirements.
- c. Individual windows that are ganged to make multiple units require continuous head flashing and the joints between the units must be fully sealed.
- 3. Roof: Verify that all roof flashings have been installed in accordance with the guidelines set by the Asphalt Roofing Manufacturers Association (ARMA).
- 4. Kick-out flashing: Kick-out flashing must be installed leak-proof and angled (min 100°) to allow for proper drainage and water diversion.
- 5. Do not proceed until all unsatisfactory conditions have been corrected.

3.02 PREPARATION

- **A.** Protect all surrounding areas and surfaces from damage and staining during application of Pebbletex Vulcan NC Wall System materials.
- **B. Finish:** Protect finished work at end of each day to prevent water penetration.
- C. Substrate preparation: Prepare substrates in accordance with LaHabra instructions.

3.03 MIXING

General: No additives are permitted unless specified in product mixing instructions. Close containers when not in use. Prepare in a container that is clean and free of foreign substances. Do not use a container which has contained or been cleaned with a petroleum-based product. Clean tools and equipment with water immediately after use. Dried material can only be removed mechanically.

NOTE TO SPECIFIER: Keep only the products in this section which were selected in Section 2.02.

Delete those not to be utilized.

A. Air/Water-Resistive Barriers:

1. FINESTOP RA/RS/VB: Mix with a clean, rust-free paddle and drill until thoroughly blended. Do not add water.

B. Base Coat:

- A/BC Base Coat: Mix base coat with a clean, rust-free paddle and drill until thoroughly blended, before adding Portland cement. Mix one-part (by weight) Portland cement with one-part base coat. Add Portland cement in small increments, mixing until thoroughly blended after each additional increment. Clean, potable water may be added to adjust workability.
- 2. FINEGUARD Base Coat: Mix base coat with a clean, rust-free paddle and drill until thoroughly blended, before adding Portland cement. Mix one-part (by weight) Portland cement with one-part base coat. Add Portland cement in small increments, mixing until thoroughly blended after each additional increment. Clean, potable water may be added to adjust workability.
- 3. FINEBUILD Base Coat: Mix base coat with a clean, rust-free paddle and drill until thoroughly blended, before adding Portland cement. Mix one-part (by weight) Portland cement with one-part

- base coat. Add Portland cement in small increments, mixing until thoroughly blended after each additional increment. Clean, potable water may be added to adjust workability.
- 4. A/BC 1-STEP Base Coat: Mix and prepare each bag in a 5-gallon (19-liter) pail. Fill the container with approximately 1.5-gallons (5.6-liters) of clean, potable water. Add Base Coat in small increments, mixing after each additional increment. Mix Base Coat and water with a clean, rust-free paddle and drill until thoroughly blended. Additional A/BC 1-STEP or water may be added to adjust workability.
- **C. SIKAWALL COLOR ADVANCE**: Mix the factory-prepared material with a clean, rust-free paddle and drill until thoroughly blended. A small amount of clean, potable water may be added to adjust workability. Do not overwater.
- **D. SIKAWALL TINTED PRIMER**: Mix the factory-prepared material with a clean, rust-free paddle and drill until thoroughly blended. A small amount of clean, potable water may be added to adjust workability. Do not overwater.

E. Finishes:

- 1. PEBBLETEX, PEBBLETEX TERSUS, CHROMA, and ENCAUSTO VERONA Finish: Mix the factory-prepared material with a clean, rust-free paddle and drill until thoroughly blended. A small amount of clean, potable water may be added to adjust workability. Do not overwater.
- SIKAWALL GRANITE AND STONE Finish: Gently mix the contents of the pail for 1 minute using a low RPM ½" drill equipped with a mixing paddle such as a Demand Twister or a Wind-Lock B-MEW, B-M1 or B-M9.

3.04 APPLICATION

A. Accessories: Attach Window/Door Drip Edge level and per manufacturer's instructions.

NOTE TO SPECIFIER: Keep only the products in this section which were selected in Section 2.02.

Delete those not to be utilized.

B. Air/Water-Resistive Barrier:

- 1. All sheathing joints and windows/openings must be protected, and the air/water-resistive barrier applied in accordance with Finestop product bulletin and details.
- 2. Substrate shall be dry, clean, sound, and free of releasing agents, paint, or other residue or coatings. Verify substrate is flat, free of fins or planar irregularities greater than 6.4 mm in 3 m (1/4" in 10').
- 3. Unsatisfactory conditions shall be corrected before application of the LaHabra Finestop air/water-resistive barriers.
- 4. Apply the SIKAWALL SHEATHING FABRIC and LaHabra Finestop air/water-resistive barrier in accordance with the LaHabra Finestop air/water-resistive barrier product bulletin.
- 5. Apply the SIKAWALL MAXFLASH in accordance with the MAXFLASH product bulletin.
- 6. Installed materials shall be checked before continuing system application.
- 7. Ensure SIKAWALL SHEATHING FABRIC and LaHabra Finestop air/water-resistive barrier or MAXFLASH overlaps the top flange of the flashing.
- 8. Installed materials shall be checked before continuing system application.

C. Mineral Wool Insulation Board:

1. General: Begin at base of wall with firm, temporary support or spacer. Stagger joints horizontally in a running bond pattern offset a minimum of 6" (152 mm). Pre-cut insulation board to fit openings and projections. Insulation board must be a single piece around corners of openings. Stagger vertical joints and corners. Stagger insulation and sheathing board joints. Offset insulation board joints from sheathing joints by a minimum of 8" (203 mm). Backwrap or pre-backwrap the terminating edges of the insulation application to properly encapsulate the insulation. Pre-

backwrapping should be done at drainage terminations to ensure drainage path is not impeded.

• Fasteners: 9 fasteners are required per 2' x 4' (610 mm x 1220 mm) piece of insulation board. Install mechanical fasteners at not more than 8" (203mm) o.c. vertically and 16" (406) mm o.c. horizontally.

4" (102 mm)

8" (203 mm)

8" (203 mm)

4" (102 mm)

1. Adhesive:

a. Apply mixed LaHabra Base Coat to entire surface of insulation board using a stainless-steel

notched trowel with 1/2"x1/2" (13 mm x 13 mm) notches spaced 2" (50 mm) apart. Ribbons of adhesive must be applied parallel to the 2' (610 mm) dimension of the insulation board to ensure they are vertical when the insulation board is applied to the substrate. Keep the trowel clean to avoid adhesive build-up between adhesive ribbons, remove or scrape off any excess adhesive left between ribbons.

- b. Immediately set board into place and apply pressure over entire surface of board to ensure positive uniform contact and high initial grab. Do not slide board into place. Do not allow base coat to dry prior to installing.
- **c.** Abut all joints tightly to prevent gaps and ensure overall flush level surface.
- d. Interlock boards at inside and outside corners
- e. Fill gaps in the insulation board 1/8" (3 mm) or greater with slivers of mineral wool insulation
- **f.** The straight edge of a trowel can be used to shave high spots in the mineral wool insulation to create an even plane.
- **g.** Preplan location of reveals so that they do not coincide with fastener locations or insulation board joints. Maintain a minimum 1" (25 mm) thickness of insulation board at the back of the reveal; bottom of reveal should have 6:12 slope.
- **h.** Allow adhesive application of insulation board to dry (minimum 8 to 10 hours) prior to installation of mechanical fasteners.

2. Fasteners 1 of 2:

- a. Install 4 fasteners per insulation board after adhesive application of the insulation board.
- b. Install fasteners along termination points within 4" (102 mm) of the horizontal edge and 8" (203 mm) vertical edge.
- c. Reference details for spacing/placement
- d. Where installation occurs over frame construction, ensure fasteners are installed into the framing members.
- e. Install fasteners to a depth to leave the ULP-302 plate flush or slightly recessed from the surface of the insulation, maximum recess of 1/16" (1.6 mm).

NOTE: Do not overdrive fasteners, washer should sit flush with face of insulation board or slightly (1/16') recessed. Same for

⊕ THROUGH INSULATION BOARD INTO FRAMING, BEFORE BASE COAT/MESH APPLICATION

O THROUGH REINFORCED BASE COAT INTO FRAMING

16" (406 mm)

0

MINERAL WOOL INSULATION BOARD FASTENING PATTERN

8" (203 mm) T

48" (1220 mm)

(610 mm

3. Base Coat and Reinforcing Mesh:

a. Base coat shall be applied to achieve reinforcing mesh embedment with no reinforcing mesh color visible. Follow reinforcing mesh installation instructions below. Allow base coat to dry completely.

4. Fasteners 2 of 2:

a. Install remaining 5 fasteners per board after the installation of the reinforced base coat. Follow same application guidelines as the initial fastener installation. Do not overdrive fasteners, ULP-302 plate should be flush or slightly recessed from the surface of the base coat.

5. Final Base Coat:

a. Spot all exposed fasteners (fasteners on outside of reinforced base coat) with LaHabra base coat prior to application of final skim coat layer of base coat. Multiple coats of base coat may be required to achieve a flat surface.

NOTE TO SPECIFIER: Indicate on drawings the required locations of standard, medium, high or ultra-high impact reinforcing mesh.

D. Base Coat/Reinforcing Mesh: Base coat shall be applied to achieve reinforcing mesh embedment with no reinforcing mesh color visible.

E. SIKAWALL CORNER MESH:

- 1. Install at corners, prior to application of reinforcing mesh.
- 2. Apply mixed LaHabra base voat to insulation board at outside corners using a stainless-steel trowel. Immediately place mesh against the wet base coat and embed into the base boat by troweling from the corner; butt edges and avoid wrinkles.
- 3. After base coat is dry and hard, apply a layer of STANDARD MESH 4, INTERMEDIATE 6 or 12 reinforcing mesh over the entire surface of the CORNER MESH in accordance with 3.04 F.

F. Standard Impact or Medium Impact Resistance Reinforcing Mesh: STANDARD MESH 4 INTERMEDIATE 6 and INTERMEDIATE 12

- 1. Install SikaWall reinforcing mesh where indicated on drawings.
- 2. Apply mixed LaHabra Base Coat to entire surface of insulation board with a stainless-steel trowel to embed the reinforcing mesh.
- 3. Immediately place SikaWall reinforcing mesh against wet base coat and embed the reinforcing mesh into the base coat by troweling from the center to the edges.
- 4. Lap reinforcing mesh 2 ½" (64 mm) minimum at edges.
- 5. Ensure reinforcing mesh is continuous at corners, void of wrinkles and embedded in base coat so that no reinforcing mesh color is visible.
- 6. If required, apply a second layer of base coat to achieve total nominal base coat/reinforcing mesh thickness of 1/16" (1.6 mm).
- 7. Allow base coat with embedded reinforcing mesh to dry hard (normally 8 to 10 hours).
- G. High Impact or Ultra High Impact Resistance Reinforcing Mesh: INTERMEDIATE 12, STRONG 15 and ULTRA HIGH 20

NOTE TO SPECIFIER: Where STRONG 15 or ULTRA HI 20 is specified, STANDARD MESH 4 or INTERMEDIATE 6 must be specified also.

- 1. Install SikaWall reinforcing mesh where indicated on drawings.
- 2. Apply mixed LaHabra base coat to entire surface of insulation board with a stainless-steel trowel to embed the reinforcing mesh.
- 3. Immediately place SikaWall reinforcing mesh against wet base coat and embed the reinforcing mesh into the base coat by troweling from the center to the edges.
- 4. Butt reinforcing mesh at all adjoining edges; do not use to backwrap or bend around corners.
- 5. Butt reinforcing mesh at adjoining edges of CORNER MESH.
- 6. Ensure reinforcing mesh is free of wrinkles and embedded in base coat so that no reinforcing mesh color is visible.
- 7. After base coat with embedded reinforcing mesh is dry and hard (normally 8 to 10 hours), apply a layer of STANDARD MESH 4 or INTERMEDIATE 6 Reinforcing Mesh over the entire surface in accordance with 3.04 F to achieve total nominal base coat/ reinforcing mesh thickness of 3/32" (2.4 mm).

H. SIKAWALL COLOR ADVANCE:

1. Apply material to the base coat/reinforcing mesh in sealant joints with a high-quality, latex-type paintbrush. Work material continuously until a uniform appearance is obtained. Allow to dry thoroughly (approximately 24 hours) prior to application of sealant primer and sealant.

I. SIKAWALL TINTED PRIMER:

- 1. Apply primer to the base coat/reinforcing mesh with a sprayer, 3/8" (10 mm) nap roller, or good quality latex paint brush at a rate of approximately 150-250 ft² per gallon (3.6–6.1m² per liter). Primer shall be dry to the touch before proceeding to the LaHabra finish coat application.
- J. Finish Coat: PEBBLETEX, PEBBLETEX TERSUS and CHROMA.
 - 1. Apply finish directly to the base coat with a clean, stainless steel trowel.
 - 2. Apply and level finish during the same operation to a minimum obtainable thickness consistent with

- uniform coverage. Maintain a wet edge on finish by applying and texturing continually over the wall surface
- 3. Work finish to corners, joints or other natural breaks and do not allow material to set up within an uninterrupted wall area. Float finish to achieve final texture.

K. SIKAWALL ALUMINA Finish:

- 1. Apply SIKAWALL TINTED PRIMER to the substrate in accordance with the current product bulletin. Primer shall be of the corresponding color for the selected finish color. Allow the primer to dry to the touch before proceeding with finish application.
- 2. Apply a tight coat of finish with a clean, stainless steel trowel. Maintain a wet edge on finish by applying and leveling continually over the wall surface.
- 3. Work finish to corners, joints or other natural breaks and do not allow material to set up within an uninterrupted wall area. Allow first coat to set until surface is completely dry prior to applying a second coat of finish.
- 4. Use a stainless-steel trowel and apply the second coat of finish. Achieve final texture using circular motions. Total thickness of finish may be between 1/16" (1.6 mm) and 1/8" (3.2 mm).

3.05 CLEANING

- A. Clean work under provisions of Section [01 74 00] [].
- **B.** Clean adjacent surfaces and remove excess material, droppings, and debris.

3.06 PROTECTION

- **A.** Protect materials from rain, snow and frost for 48–72 hours following application.
- **B.** Protect installed construction under provisions of Section [01 76 00] [].

END OF SECTION

WARRANTY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com/lahabra or by calling SIKA Facades' Technical Service Department at 1-800-589-1336. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at https://usa.sika.com/.

Sika Corporation 201 Polito Avenue Lyndhurst, NJ 07071 USA +1 201 933 8800 usa.sika.com/lahabra

