



## PRODUCT DATA SHEET

# Sikafloor® P 200

(formerly MasterTop® P 200)

### PRIMER FOR SIKAFLOOR®-100 SL PRONTO UNDERLAYMENT

#### PRODUCT DESCRIPTION

Sikafloor® P 200 is a high-quality primer and bonding agent that seals concrete surfaces and provides a maximum-strength binder coat for Sikafloor® underlayments and cementitious floor toppings.

#### USES

- Interior
- As a primer and binder coat for Sikafloor®-100 SL Pronto underlayment

#### Substrates

- On nonporous, semi-porous, and porous concrete

#### CHARACTERISTICS / ADVANTAGES

- Water-based for easy clean-up
- Single-component material is easy to use
- Tinted light blue to facilitate coverage
- Re-emulsifiable, long recoat window
- Low VOC level complies with all regional regulations

#### PRODUCT INFORMATION

<b>Packaging</b>	1 gallon (3.8 L) pails
<b>Shelf Life</b>	450 days when properly stored
<b>Storage Conditions</b>	Store in unopened containers in a clean, dry area. Keep from freezing.

#### APPLICATION INFORMATION

<b>Coverage</b>	One gallon of Sikafloor® P 200 diluted with 1 gallon of water covers approximately 200–400 ft <sup>2</sup> (18.6–37.2 m <sup>2</sup> ). Estimated coverage rate will vary based upon profile and porosity of the substrate.
<b>Drying Time</b>	Cure time is approximately 2–3 hours, depending on ambient temperatures and humidity. Allow Sikafloor® P 200 to dry 2–24 hours before applying a second coat of primer. The final coat of primer should dry to a tack-free condition before the placement of Sikafloor®-100 SL Pronto. Sikafloor®-100 SL Pronto must be applied within 12 hours after priming or the substrate will require another application of primer diluted 1 to 1 with water.

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## LIMITATIONS

### For Best Performance

- Do not allow to freeze. If material freezes, DO NOT USE.
- Test installations are encouraged. Test floors for vapor drive in accordance with ASTM D 4263. The finish used will determine the acceptable vapor drive. Sikafloor® P 200 is not suitable for permanently wet conditions. Minimum air and substrate application temperature is 40° F (4° C). Sikafloor® P 200 must be tack-free during placement of Sikafloor®-100 SL Pronto.
- Sikafloor®-100 SL Pronto must be placed within 12 hours after Sikafloor® P 200 application; otherwise, reapply Sikafloor® P 200.
- When diluting Sikafloor® P 200, use only clean potable water.
- For professional use only; not for sale to or use by the general public.
- Make certain the most current versions of product data sheet and SDS are being used; visit [usa.sika.com](http://usa.sika.com) to verify the most current versions.
- Proper application is the user's responsibility. Sika personnel's field visits are for making technical recommendations only and not for supervising or providing quality control on the job site.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## APPLICATION INSTRUCTIONS

**Refer to the product data sheet for Sikafloor®-100 SL Pronto underlayment before beginning installation.**

### SUBSTRATE PREPARATION

- Concrete surfaces must be fully cured, structurally sound, clean, and free of dust, oil, grease, water, curing compounds, sealers, waxes, paint, or any contaminants that might inhibit proper bond.
- Fill and grout all cracks and drilled or sawed holes to prevent seepage of Sikafloor® P 200 or Sikafloor®-100 SL Pronto.
- Designed joints in substrate must be carried through the application of Sikafloor®-100 SL Pronto.

- The surface to be repaired must be clean, strong, and prepared in accordance with ICRI Guideline No. 310.2 (CSP 3-5) to permit proper bond.

### MIXING

Stir for 1 to 2 minutes with a clean stir stick using the dilution ratios appropriate for the porosity of the substrate (see the Application section below).

### APPLICATION

1. Use Sikafloor® P 200 on dampened substrates only. Dampen the substrate before application, but do not oversaturate and leave puddles of water.
2. Apply Sikafloor® P 200 with a brush or roller, working the primer thoroughly into the substrate. Avoid leaving puddles of primer in low areas.
  - Nonporous surfaces: use 1 coat of undiluted Sikafloor® P 200.
  - Semi-porous surfaces (including steel troweled concrete): use 1 coat of Sikafloor® P 200 diluted 1 to 1 with clean water.
  - Porous surfaces: may require 2 coats of Sikafloor® P 200. Dilute the first coat with 2 parts clean water to 1 part primer. Dilute the second coat with 1 part clean water to 1 part primer.

### CLEANING OF TOOLS

Immediately clean equipment with soap and water.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL**

**APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

**Sika Corporation**

201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)



**Product Data Sheet**

Sikafloor® P 200  
June 2024, Version 01.01  
02081100000002038

SikafloorP200-en-US-(06-2024)-1-1.pdf

