

SYSTEM DATA SHEET

Sika ComfortFloor® PS-25

SEAMLESS, ELASTOMERIC DECORATIVE FLOORING FOR INTERIOR CONCRETE SURFACES FINISH ENGINEERED WITH SIKAFLOOR® - 330 @ 100 - 120 MILS (2.5 - 3.0 MM)

PRODUCT DESCRIPTION

Sika ComfortFloor® PS-25 is an ergonomic, sound dampening, low emission, flaked floor system that is UV stable and easy to maintain. Sika ComfortFloor® PS-25 is comprised of a 100% solids epoxy primer, a pigmented self leveling urethane body coat, a urethane receiver coat broadcast with decorative flakes, and a wear resistant, clear water based urethane top coat. Sika ComfortFloor® PS-25 is typically installed @ 100-120 mils (2.5 - 3.0 mm).

USES

Sika ComfortFloor® PS-25 may only be used by experienced professionals.

- Hospitals and clinics
- Education facilities
- Offices, corridor and lobbies
- Retail establishments
- Public spaces


CHARACTERISTICS / ADVANTAGES

- Durable and decorative
- Sound dampening
- Soft footfall
- Seamless and hygienic
- Excellent resistance to fire spread
- Low VOC content
- Attractive matte finish
- Resistant to mechanical and abrasion abuse
- Low maintenance

SYSTEM INFORMATION

System Structure

Sika ComfortFloor® PS-25 ~ 100 - 120 mils (2.5 - 3.0 mm)



Description	Products	Thickness mils
1. Primer	Sikafloor®-161	8 - 12
2. Body Coat	Sikafloor®-330 + Sikafloor® Epoxy Pigment Pack	80 - 100 minimum
3. Receiver Coat	Sikafloor®-305 W NA + Sikafloor® Decorative Flakes	5 - 8
4. Top Coat	Sikafloor®-304 W NA	5 - 8

Options		
Description	Products	Thickness mils
Primers	Sikafloor®-165 FS Sikafloor®-1620	8 - 10 12 - 15
Optional 2 nd Top Coat	Sikafloor®-304 W NA	5 - 8

Color

Refer to Sika ComfortFloor Color Additives Selection Guide.
The Sikafloor®-330 should be pigmented the same or close to the color of the Sikafloor®- 305 W NA top coat.

Nominal thickness

100 - 120 mils (2.5 - 3.0 mm)

Minimum thickness 100 mils (2.5 mm)

TECHNICAL INFORMATION

Testing	>80 (14 days)				ASTM D2240 73°F (23°C) and 50% R.H
Abrasion Resistance	CS-17/1000 rotations/1000 g-0.04g				ASTM D4060 73°F (23°C) and 50% R.H
Impact Strength	160 in/lbs				ASTM D4226 73°F (23°C) and 50% R.H
Tensile Strength	1,142 psi.(~ 8.0 N/mm ²)				ASTM D412 73°F(23°C) and 50% R.H
Tensile Adhesion Strength	> 500 Psi (3.5 MPa) (concrete failure)				ASTM D7234 73°F (23°C) and 50% R.H
Tear Strength	142.75 lb./in.(~ 25 N/mm 14 days)				ASTM D624 73°F(23°C) and 50% R.H
Crack Bridging Ability	Passed				ASTM C1305 73°F (23°C) and 50% R.H
Chemical Resistance	Contact Sika Technical Service for specific information				
Coefficient of Friction	0.6				ANSI 326.3 73°F (23°C) and 50% R.H
Indentation	0.002 in (800 lb load)				ASTM F970 73°F (23°C) and 50% R.H
Color	<div>Δ E 0.3 (7 days at 158°F/70°C)</div> <div>Very good</div>				ASTM F1514
Gloss level	5-15 (60°)				ASTM D-523 73°F (23°C) and 50% R.H
Footfall Sound Reduction	Flooring Type	Solid concrete Slab Thickness	IIC Rating of concrete slab alone	IIC Rating of ComfortFloor system on slab	ASTM E 492-09/ASTM E 989-06
	ComfortFloor Decorative Pro	8"	30	53	
	ComfortFloor Pro	8"	30	52	
	ComfortFloor Decorative	8"	30	40	
	ComfortFloor	8"	30	37	
	ComfortFloor Decorative	6"	26	36	
	ComfortFloor	6"	26	33	
	*All testing was done direct to concrete slab with no ceiling or other additional insulating structures				
Elongation at break	180%				ASTM D412 73°F (23°C) and 50% R.H
Compressive Strength	>0.45 W/cm ² (Class 1)				ASTM E648

APPLICATION INFORMATION

Coverage	Description	Products	Approximates Sq.Ft./kit
	1. Primer	Sikafloor®-161	900 @ 8 mils
	2. Body Coat	Sikafloor®-330 + Sikafloor® Epoxy Pigment Pack	154 @ 80 mils minimum 2 quart per 7.22 gallon kit
	3. Receiver Coat	Sikafloor®-305 W NA + Sikafloor Decorative Flakes	653 @ 5 mils 2 lbs per 2.04 gallon kit
	4. Top Coat	Sikafloor®-304 W NA	595 @ 5 mils
Options			
	Description	Products	Approximates Sq.Ft./kit
	Primers	Sikafloor®-165 FS Sikafloor®-1620 Sikafloor®-2570	1,000 @ 8 mils 534 @ 12 mils 2,667 @ 3 mils
	2 nd Top Coat	Sikafloor®-304 W NA	595 @ 5 mils
<hr/>			
Ambient Air Temperature	Minimum/Maximum 50°/85°F (10°/30°C)		
Substrate Temperature	Minimum/Maximum 50°/85°F (10°/30°C)		

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LIMITATIONS

Please refer to the individual Product Data Sheets for Limitations.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Concrete surfaces must be clean and sound. Remove all dust, dirt, existing paint films, efflorescence, exudates, laitance, form oils, hydraulic or fuel oils, brake fluid, grease, fungus, mildew, biological residues or any other

contaminants which may prohibit a good bond.

Prepare the surface by any appropriate mechanical means, in order to achieve a profile equivalent to ICRI - CSP 3-6. The compressive strength of the concrete substrate should be at least 3,625 psi (25 MPa) at 28 days and a minimum of 218 psi (1.5 MPa) in tension at the time of application.

Repairs to cementitious substrates, filling of blowholes, leveling of irregularities, etc. should be carried out using an appropriate Sika profiling mortar. Contact Sika Technical Service for a recommendation.

Priming

Priming for concrete substrate is required. Prime with either Sikafloor®-161, Sikafloor®-2570 WB, Sikafloor®-165 FS or Sikafloor®-1620.

Allow the primer to cure (varies with temperature and humidity) until tack free before applying subsequent coats. Ensure that the primer is pore-free, pinhole-free and provides uniform and complete coverage over the entire substrate. Please refer to the most current and respective Product Data Sheet for further information.

MIXING

Please refer to the individual Product Data Sheets

APPLICATION

Please refer to the individual Product Data Sheets

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



System Data Sheet
Sika ComfortFloor® PS-25
June 2025, Version 03.01
02081290000000108

SikaComfortFloorPS-25-en-US-(06-2025)-3-1.pdf

