

BUILDING TRUST

TECHNICAL DATA SHEET

SikaBiresin® AP077

(FORMERLY P-77)

POLYESTER FILLER SYSTEM STYRENE-FREE / HIGH TEMPERATURE / SANDABLE

DESCRIPTION

AP077 polyester filler and fairing compound offers the user a smooth workable paste with a set-fast cure to expedite those applications for repair or finish. AP077 is easier to sand than conventional fillers and can be finished to a feather edge. This material has excellent adhesive and bond strength to fiberglass, SMC, FRP, epoxy, graphite, and Kevlar® composites as well as aluminum, wood, and other substrates. AP077 can be easily applied with a squeegee, spatula, or flat tool, and once cured will accept virtually all types of coatings and decorative films. Applications include gel coat blister repair, fiberglass parts repair, filling cloth imprint on FRP panels, Edge filling on honeycomb panels. Elevated temperatures up to 200°C/392°F have to be tolerated with AP077.

PROPERTIES

- Exceptional adhesion
- Very quick setting
- Minimal shrinkage
- High service temperature
- Excellent finishing and machinability
- Accept virtually all types of finishes
- Low moisture absorption for above or below waterline applications

PHYSICAL PROPERTIES

Composition			POLYESTER	BPO HARDENER BPO	MIXED
		SikaBiresin® AP077			
Mix ratio by weight			100	2	
Mix ratio by volume at 25	°C				
Aspect			Paste	Cream Paste	Paste
Color	NOTE - Mixed color can be		White	White	
	varied with Cream BPO color			Red	
	(As a mixing aid/indicator and			Black	
	fina	al color choice)			
Viscosity at 25 °C	(cPs)	BROOKFIELD LVT			Paste
Vertical sag (inches)					<.05
Specific gravity at 25 °C	lbs./gal	ASTM D792	13.3	10	13.20
	(g/cc)		(1.59)	(1.20)	(1.58)
Pot Life at 25 °C (102 g)	(minutes)	ASTM D2471			9.0 – 11.0

TECHNICAL DATA SHEET SikaBiresin® AP077 February 19, Version 02 /2019



MECHANICAL PROPERTIES at 23 °C (1)

Hardness (Shore D)	ASTM D-2240	85-88
Water absorption – 24 hr/R.T. soak (%)	ASTM D-570	0.08
Adhesive pull strength to: (psi) Polyester Filler -	ASTM D-4541	400
Mahogany –		540
Epoxy glass laminate -		430

⁽¹⁾ Average values obtained on standard specimens / Cured 7 days at 25°C

PROCESSING

PROCESSING CONDITIONS

- Thoroughly blend 100 parts resin with 2 parts hardener by weight for 1 to 1½ minutes in clean dry container or on a clean dry surface.
- Carefully scrape the surfaces while blending to ensure complete mixing and uniformity.

SURFACE PREPARATION and APPLICATION

- The area to be filled or repaired should be thoroughly cleaned, roughened, cleaned again and dried to allow for the best possible adhesion.
- The mixed AP077 should be buttered into the area, avoiding trapping air during application.
- After curing to a tack-free state, the material can be sanded and finished as needed.

MIXING INSTRUCTIONS

Stir contents of can thoroughly using a spatula or putty knife. Place the required amount of filler and cream hardener on a disposable clean surface. Mix 100 parts paste to 2 parts BPO cream hardener by weight; i.e. approximatly size of golf ball (paste) to a two inch strip of BPO catalyst. Set up time of mix at room temperature will be 5-10 minutes. After 15-20 minutes the filler may be filed or sanded to final finish.

HANDLING PRECAUTIONS

Normal health and safety precautions should be observed when handling these products:

- Ensure good ventilation.
- Wear gloves, glasses and protective clothes.

For further information, please consult the Safety Data Sheets.

STORAGE CONDITIONS

- Product shelf life of polyester resin is 12 months when stored in original unopened containers between 65 77°F (15 25°C). Any opened can must be tightly closed. Product shelf life of BPO hardener is 18 months when stored in original unopened containers between 65 77°F (15 25°C). Any opened can must be tightly closed.
- Polyester resin contains filler which has the potential to separate in time, please re-homogenize prior to use.



Packaging information on request, please contact your local sales representative or find your local contact on www.sikaadvancedresins.us

LEGAL NOTICE

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

CONTACT – ADVANCED RESINS

GERMANY

Stuttgarter Straße 139
72574 Bad Urach – GERMANY
Tel.: (+49) 7 125 940 492
Fax.: (+49) 7 125 940 401
E-mail: tooling@de.sika.com
Website: www.sikaadvancedresins.de

FRANCE

ZI des Béthunes - 15, Rue de l'Equerre 95310 Saint-Ouen-l'Aumône CS 40444

95005 CERGY PONTOISE Cedex – FRANCE Tel.: (+33) 1 344 034 60

Website: www.sikaadvancedresins.fr

Fax: (+33) 1 344 034 00 Fax: (+33) 1 342 197 87 E-mail: advanced.resins@fr.sika.com

SPAIN

Polígon Industrial Congost - Guardaagulles, 8 08520 LES FRANQUESES DEL VALLES – SPAIN

Tel.: (+34) 932 25 16 20 E-mail: spain@axson.com

Website: www.sikaadvancedresins.es

ITALY Via Morandi 15

21047 Saronno (Va) – ITALY Tel.: (+39) 02 9670 2336 Fax: (+39) 02 9670 2369 E-mail: axson@axson.it

Website: www.sikaadvancedresins.it

UNITED KINGDOM

Unit 15 Studlands Park Ind. Estate Newmarket Suffolk, CB8 7AU – UNITED KINGDOM Tel.: (+44) 1638 660 062

Fax: (+44) 1638 665 078
E-mail: sales.uk@axson.com
Website: www.sikaadvancedresins.uk

SLOVAKIA

Tovarenska 49 95301 ZLATE MORAVCE – SLOVAKIA Tel: (+421) 376 422 526 Fax: (+421) 376 422 527 E-mail: axson.sk@axson.com Web site: www.sikaadvancedresins.sk

UNITED STATES

30800 Stephenson Highway Madison Heights, Michigan 48071 – USA Tel.: (+1) 248 588-2270 Fax: (+1) 248 577-0810

Fax: (+1) 248 577-0810 E-mail: axsonmh@axson.com Web site: www.sikaadvancedresins.us

MEXICO

Ignacio Ramírez #20
Despacho 202 Col. Tabacalera
C.P. 06030 CDMX – MEXICO
Tel.: (+52) 55 5264 4922
Fax: (+52) 55 5264 4916
E-mail: marketing@axson.com.mx
Website: www.sikaadvancedresins.mx

CHINA

N°53 Tai Gu Road Wai Gao Qiao Free Trade Zone, Pudong 200131 Shanghai – CHINA Tél.: (+86) 21 5868 3037 Fax: (+86) 21 5868 2601

E-mail: marketing.china@axson.com Website: www.sikaadvancedresins .cn

JAPAN

2-5-12 Onishi Okazaki Aichi 444-0871 – JAPAN Tel.: (+81) 564 26 2591 Farmail: sales.japan@axson.com Website: www.sikaadvancedresins.jp

INDIA

Office n°8, Building Symphony C - 3rd Floor Range Hills Road Bhosale Nagar PUNE 411 020 – INDIA

Tel: (+ 91) 20 25 56 07 10 Fax: (+ 91) 20 25 56 07 12 E-mail: info.india@axson.com Website: www.sikaadvancedresins.in

