



Sika® Level-225

HIGH FLOW, SELF-LEVELING UNDERLAYMENT

- Superior workability for easy installations
- Apply as low as 1/16" in pedestrian areas
- Can be installed above 1/16" up to 2" and up to 3" with aggregate
- Strong bond to the substrates

Available in
55 lb. Bag



BUILDING TRUST



Sika® Level-225

HIGH FLOW, SELF-LEVELING UNDERLAYMENT

WHERE TO USE

- Interior use only
- Levels, flattens, and smooths substrates before application of resilient floor
- Suitable on concrete, ceramic and quarry tile, OSB/Plywood, and well bonded LVT
- Leveling work for residential and commercial projects with normal wear requirements

TYPICAL DATA (Material and curing conditions @ 73°F (23°C) and 50% R.H.)

Color	Concrete Gray
Application Thickness	1/16" up to 2" (3 mm up to 51 mm) Can be extended with aggregate to 3" (76 mm)
Density (ASTM C185)	130 lbs/cu.ft.
Working Time	Approx. 25 minutes
Ready for Foot Traffic	2-3 hours
Flexural Strength (ASTM C348)	1,250 psi (8.6 MPa) at 28 days
Compressive Strength (ASTM C109)	4,500 psi (31 MPa) at 28 days
VOC (EPA METHOD 24)	0 g/l

FEATURES AND BENEFITS

- High flow
- Very smooth surface
- Install most floor covering in 16 hours
- Pumpable self-leveling
- Zero VOC content and low odor
- 1/16" in pedestrian areas

NOTE: Always refer to current PDS and SDS for detailed performance specifications prior to use.

Sika® Level 225

Strength					
Flow					
Depth					
Speed					



FOR MORE INFORMATION:

Contact Sika: Phone 800.933.SIKA(7452) Website: www.sikasecure.com

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 201-933-8800
Fax: 201-933-6225



BUILDING TRUST

