

## **BUILDING TRUST**

# PRODUCT DATA SHEET

# Sika® AnchorFix-2

## SUPER STRENGTH, TWO COMPONENT ADHESIVE ANCHORING SYSTEM

#### PRODUCT DESCRIPTION

Sika® AnchorFix-2 adhesive anchor system is solvent/styrene free, epoxy acrylate based, and has been specifically formulated as a high performance, two component adhesive anchor system for threaded bars in uncracked concrete.

## **USES**

Sika® AnchorFix-2 may only be used by experienced professionals.

#### As a fast curing anchoring adhesive for all grades of:

- Rebars / reinforcing steel
- Threaded rods
- Bolts and special fastening systems

#### In the following substrates:

- Concrete
- Solid masonry
- Steel
- Hard natural stone\*
- Solid rock\*
- \* These substrates may vary greatly, in particular with regard to strength, composition and porosity. Therefore, for each application the suitability of Sika® AnchorFix-2 Adhesive must be tested by first applying the Product only to a sample area. Check in particular bond strength, surface staining and discoloration.

# **CHARACTERISTICS / ADVANTAGES**

- Fast curing
- Standard guns can be used
- High load capacity
- Drinking Water certified
- Non-sag, even overhead
- Styrene-free epoxy acrylate
- Low wastage
- Fixing close to free edges.
- Versatile range of embedment depths.
- Anchoring without expansion forces.

# **APPROVALS / STANDARDS**

- EESR to AC308 by ICC-ES PENDING.
- ESR to AC308 by IAPMO-UES.
- Certified to ANSI / NSF 61 by UL.

## PRODUCT INFORMATION

Packaging	10 fl.oz. (299 ml) cartridge
Shelf Life	12 months from date of production All Sika® AnchorFix-2 cartridges have the expiry date printed on the label.
Storage Conditions	Cartridges should be stored in their original packaging, the correct way up, in cool conditions 41 °F to 77 °F (5 °C to 25 °C) out of direct sunlight.

#### **Product Data Sheet**

**Sika® AnchorFix-2**February 2020, Version 01.04
020205010020000001

#### **TECHNICAL INFORMATION**

#### **Tensile Adhesion Strength**

		Allowable Concrete Capacity / Bond Strength						
Anchor	Embedment		Tension (lb)			Shear (lb)		
Diameter Depth		f' <sub>c</sub> = 2,500 psi	f' <sub>c</sub> = 4,000	f' <sub>c</sub> = 8,000	f' <sub>c</sub> = 2,500	f' <sub>c</sub> = 4,000	f' <sub>c</sub> = 8,000	
	2-3/8"	1,390	1,457	1,562	1,854	1,943	2,082	
5/16"	3-1/16"	1,793	1,879	2,014	2,390	2,505	2,685	
	3-3/4"	2,195	2,301	2,466	2,927	3,068	3,288	
	2-3/8"	1,507	1,579	1,693	2,009	2,106	2,257	
3/8"	3-7/16"	2,181	2,286	2,450	2,908	3,048	3,266	
	4-1/2"	2,855	2,992	3,207	3,806	3,990	4,276	
	2-3/4"	2,397	2,513	2,693	3,197	3,350	3,591	
1/2"	4-3/8"	3,814	3,998	4,285	5,085	5,330	5,713	
	6"	5,231	5,482	5,876	6,974	7,310	7,835	
	3-1/8"	3,065	3,212	3,443	4,087	4,283	4,591	
5/8"	5-5/16"	5,210	5,461	5,853	6,947	7,281	7,804	
	7-1/2"	7,356	7,710	8,263	9,808	10,280	11,017	
	3-1/2"	3,495	3,663	3,926	4,659	4,884	5,234	
3/4"	6-1/4"	6,240	6,541	7,010	8,320	8,721	9,347	
	9"	8,986	9,418	10,094	11,981	12,558	13,459	
	4"	5,378	5,637	6,042	7,171	7,516	8,056	
1"	8"	10,757	11,274	12,084	14,342	15,033	16,112	
	12"	16,135	16,912	18,125	21,514	22,549	24,167	

<sup>1.</sup> The above values represent mean ultimate values and allowable working loads. The allowable working loads have been reduced using a safety factor of 4.0 for tension and 3.0 for shear, however, in some cases, such as life safety, safety factors of 10.0 or higher may be necessary.

#### **Service Temperature**

Long term	40 °F (4 °C) min. / 122 °F (50	(ETAG 001, Part 5)
	°C) max.	
Short term (1–2 hours)	176 °F (80 °C)	

### **Design Considerations**

Allowab	le Steel S	trength for Ti	readed Rods						
	Carbon Steel ASTM F 1554 Grade 36 (A307 Gr.C)		Carbon Steel ASTM A 193 B7		Stainless Steel ASTM F 593 CW		Stainless Steel ASTM F 593 SH		
	Diameter in)	Allowable Tension, N₃⊪	Allowable Shear, Vall	Allowable Tension, Nall	Allowable Shear, V <sub>all</sub>	Allowable Tension, N₃ıı	Allowable Shear, Vall	Allowable Tension, Nall	Allowable Shear, Vall
3/8"	lb	2,110	1,080	4,550	2,345	3,630	1,870	4,190	2,160
3/0	kN	9.4	4.8	20.2	10.4	16.1	8.3	18.6	9.6
1/2"	lb	3,750	1,930	8,100	4,170	6,470	3,330	7,450	3,840
1/2	kN	16.7	8.6	36.0	18.5	28.8	14.8	33.1	17.1
5/8"	lb	5,870	3,030	12,655	6,520	10,130	5,220	11640	6,000
3/0	kN	26.1	13.5	56.3	29.0	45.1	23.2	51.8	26.7
3/4"	lb	8,460	4,360	18,220	9,390	12,400	6,390	15,300	7,880
3/4	kN	37.6	19.4	81.0	41.8	55.2	28.4	68.1	35.1
7/8"	lb	11,500	5,930	24,800	12,780	16,860	8,680	20,830	10,730
110	kN	51.2	26.4	110.3	56.8	75.0	38.6	92.7	47.7
1"	lb	15,020	7,740	32,400	16,690	22,020	11,340	27,210	14,020
I"	kN	66.8	34.4	144.1	74.2	97.9	50.4	121.0	62.4
1 - 1/4"	lb	23,480	12,100	50,610	26,070	34,420	17,730	38,470	19,820
1 - 1/4"	kN	104.4	53.8	225.1	116.0	153.1	78.9	171.1	88.2

Allowable Tension,  $N_{all} = 0.33 x f_u x$  nominal cross sectional area Allowable Shear, Vall = 0.17 x f<sub>u</sub> x nominal cross section area

<sup>2.</sup> Allowable loads must be checked against steel capacity. The lowest value controls.

<sup>3.</sup> Tabulated data is applicable to single anchors in normal weight concrete unaffected by edge or spacing reduction factors. Values are valid for anchors installed into dry concrete in holes drilled with a hammer drill and ANSI carbide drill bit.

<sup>4.</sup> Service temperatures should remain approximately constant. The maximum long term temperature being 122 °F and the maximum short term temperature being 176 °F. Short term temperatures are those that occur over brief intervals, for example, diurnal cycling.

5. Linear interpolation is allowed.

<sup>\*</sup>The design professional on the job is ultimately responsible for the interpretation of the data provided above.

<sup>\*</sup>The design professional on the job is ultimately responsible for the interpretation of the data provided above.

Allowable Steel Strength for Rebar							
Allowable Stee	I Strength fo	r Rebar					
		Carbon Steel ASTM A 61	5 Grade 60				
Rebar S	Size	Allowable Tension, N <sub>all</sub>	Allowable Shear, V <sub>all</sub>				
#3	lb	3,280	1,690				
#3	kN	14.6	7.5				
#4	lb	5,831	3,004				
#4	kN	25.9	13.4				
#5	lb	9,111	4,693				
#5	kN	40.5	20.9				
#6	lb	13,121	6,759				
#6	kN	58.4	30.1				
#7	lb	17,859	9,200				
# /	kN	79.4	40.9				
#8	lb	23,326	12,016				
#8	kN	103.8	53.4				
#10	lb	37,623	19,381				
#10	kN	167.4	86.2				

Allowable Stee	Allowable Steel Strength for Rebar						
		Carbon Steel CAN/CSA-G30.18 Gr.400					
Rebar Size		Allowable Tension, N <sub>all</sub>	Allowable Shear, V <sub>all</sub>				
10M	lb	4,016	2,069				
10101	kN	17.9	9.2				
15Μ	lb	8,052	4,148				
13101	kN	35.8	18.5				
20M	lb	11,960	6,161				
20101	kN	53.2	27.4				
2514	lb	19,975	10,290				
25M	kN	88.9	45.8				
30™	lb	28,121	14,486				
30101	kN	125.1	64.4				
35Μ	lb	40,089	20,652				
33101	kN	178.3	91.9				

Tension = 0.33 x f<sub>u</sub> x nominal cross sectional area Shear = 0.17 x f<sub>u</sub> x nominal cross section area

<sup>\*</sup>The design professional on the job is ultimately responsible for the interpretation of the data provided above.

# SYSTEM INFORMATION

## **System Structure**

Installation Spec	ification							
Property	Sym- bol	Unit						
Threaded Rod Diameter	d <sub>a</sub>	in	5/16	3/8	1/2	5/8	3/4	1
Drill Bit Diameter	d <sub>o</sub>	in	3/8	1/2	9/16	11/16	13/16	1-1/16
Cleaning Brush Size	d <sub>b</sub>	in	0.5	551	0.7	'87	1.1	142
Minimum Embedment Depth	h <sub>ef,min</sub>	in	2-3/8	2-3/4	3-1/8	3-3/4	4	4
Maximum Embedment Depth	h <sub>ef,max</sub>	in	6-1/4	7-1/2	10	12-1/2	15	20
Minimum Con- crete Thickness	h <sub>min</sub>	in			1.3	5 h <sub>ef</sub>		
Critical Anchor Spacing	S <sub>cr</sub>	in	2.0 c <sub>ac</sub>					
Critical Edge Distance	C <sub>ac</sub>	in		c <sub>ac</sub> =h <sub>ef</sub> *	(t <sub>k, uncr</sub> /1160) <sup>0.4</sup> *	max[3.1 - 0.7(h	/h <sub>ef</sub> ); 1.4]	
Maximum Tightening Torque	T <sub>inst</sub>	ft.lb	7.5	15	25	55	80	120

<sup>\*</sup>The design professional on the job is ultimately responsible for the interpretation of the data provided above.

# **APPLICATION INFORMATION**

**Mixing Ratio** 

Component A: component B = 10: 1 by volume

Coverage

Anchor size	:	(in	.)	5/16	3/8	1/2	5/8	3/4	1	1 1/4
Drill Hole Diameter:		(in	(in.)		1/2	9/16	3/4	7/8	1 1/8	1 3/8
Embedmen	t Depth:	(in	.)	2 3/8	2 3/8	2 3/4	3 1/8	3 3/4	4	5
Estimated	Cartridge	300	ml	83	47	32	15	9	5	2
Number of Fixing *	Volume	850	ml	254	143	97	48	29	16	8
Anchor size	:	(in	.)	5/16	3/8	1/2	5/8	3/4	1	1 1/4
Drill Hole Diameter:		(in.)		3/8	1/2	9/16	3/4	7/8	1 1/8	1 3/8
Embedment Depth:		(in	.)	3 1/8	3 3/4	5	6 1/4	7 1/2	10	12 1/2
Estimated	Cartridge	300	ml	63	29	17	7	4	2	1
Number of Fixing *	Volume	850	ml	193	90	53	24	14	6	3
Anchor size	Anchor size:		)	5/16	3/8	1/2	5/8	3/4	1	1 1/4
Drill Hole D	iameter:	(in.	.)	3/8	1/2	9/16	3/4	7/8	1 1/8	1 3/8
Embedmen	t Depth:	(in.	)	3 3/4	4 1/2	6	7 1/2	9	12	15
Estimated	Cartridge	300	ml	53	24	14	6	4	1	0
Number of Fixing *	Volume	850	ml	161	75	44	20	12	5	2

<sup>\*</sup>Number of fixings assumes 30ml wastage in initial extrusion and holes filled to 3/4 full



Sag Flow	Non-sag, even overhead							
Product Temperature		Sika $^{\circ}$ AnchorFix-2 must be at a temperature of between 41 $^{\circ}$ F (5 $^{\circ}$ C) to 68 $^{\circ}$ F (20 $^{\circ}$ C) for application.						
Dew Point		<ul><li>Beware of condensation.</li><li>Beware of frost.</li></ul>						
Open Time	Working & Loading Times							
	Cartridge Temperature	T Work (minutes)	Base Material Temperature	T Load (hours)				
	Minimum 41°F	-	14 °F to 32 °F*	24 hours				
	Minimum 41 °F	-	32 °F to 41°F	180 minutes				
	41 °F to 50 °F	8	41 °F to 50 °F	100 minutes				
	50 °F to 68 °F	4	50 °F to 68 °F	70 minutes				
	68 °F to 77 °F	3	68 °F to 77 °F	40 minutes				
	77 °F to 86 °F	2	77 °F to 86 °F	40 minutes				
	86 °F	1	86 °F	40 minutes				



# **APPLICATION INSTRUCTIONS**

### **SUBSTRATE QUALITY**

Mortar and concrete must be older than 28 days. Substrate strength (concrete, masonry, natural stone) must be verified. Pull-out tests must be carried out if the substrate strength is unknown. The anchor hole must always be clean, dry, free from oil and grease etc. Loose particles must be removed from the holes.

Threaded rods and rebars have to be cleaned thoroughly from any oil, grease or any other substances and particles such as dirt etc.

#### **MIXING**


#### Getting the cartridge ready




1. Unscrew the cap



2. Cut the film



3. Screw on the static mixer



4. Place the cartridge into the gun and start application

When the work is interrupted the static mixer can remain on the cartridge after the gun pressure has been relieved. If the resin has hardened in the nozzle when work is resumed, a new nozzle must be attached.




#### **APPLICATION METHOD / TOOLS**


#### Anchors in solid masonry/concrete:




Drilling of hole with an electric drill to the diameter and depth required. Drill hole diameter must be in accordance with anchor size




The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2×) Important: use oil-free compressors.




The drill hole must be thoroughly cleaned with the special steel brush (brush at least 2×). The diameter of the brush must be larger than the diameter of the drill hole.




The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole (at least 2×). Important: use oil-free compressors.




The drill hole must be thoroughly cleaned with the special steel brush (brush at least 2×). The diameter of the brush must be larger than the diameter of the drill hole.




The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole (at least 2×). Important: use oil-free compressors.




Pump approx. twice until both parts come out uniformly. Do not use this material. Release the gun pressure and clean the cartridge opening with a cloth.



Inject the adhesive into the hole, starting from the bottom, while slowly drawing back the static mixer.In any case avoid entrapping air. For deep holes extension tubing can be used.



Insert the anchor with a rotary motion into the filled drill hole. Some adhesive must come out of the hole. Important: the anchor must be placed within the open time.



During the resin hardening time the anchor must not be moved or loaded. Wash tools immediately with Sika® Colma Cleaner. Wash hands and skin thoroughly with warm soap water.

#### **CLEANING OF TOOLS**

Tools must be cleaned as soon as possible with a clean rag.





## **BASIS OF PRODUCT DATA**

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## **OTHER RESTRICTIONS**

See Legal Disclaimer.

## **ENVIRONMENTAL, HEALTH AND SAFETY**

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## **LEGAL DISCLAIMER**

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF **MERCHANTABILITY OR FITNESS FOR A PARTICULAR** PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at https://usa.sika.com/en/group/SikaCorp/termsandconditions.html or by calling 1-800-933-7452.

#### Sika Corporation

201 Polito Avenue Lyndhurst, NJ 07071 Phone: +1-800-933-7452 Fax: +1-201-933-6225 usa.sika.com Sika Mexicana S.A. de C.V. Carretera Libre Celaya Km. 8.5

Fax: 52 442 2250537

Carretera Libre Celaya Km. 8.5 Fracc. Industrial Balvanera Corregidora, Queretaro C.P. 76920 Phone: 52 442 2385800



Product Data Sheet Sika® AnchorFix-2 February 2020, Version 01.04 020205010020000001 SikaAnchorFix-2-en-US-(02-2020)-1-4.pdf

