

# SYSTEM DATA SHEET

# Sikafloor® Pronto RB-1855 CP

METHACRYLATE-BASED, SELF-LEVELING FLOORING SYSTEM WITH A PIGMENTED, SMOOTH OR SLIP RESISTANT SURFACE

# PRODUCT DESCRIPTION

Sikafloor® Pronto RB-1855 CP is a methyl-methacrylate (MMA) self-leveling flooring system for use in areas that require a quick curing functional floor. The quick installation process makes this flooring system ideal for commercial industrial facilities where minimal downtime is required. Sikafloor® Pronto RB-1855 CP is an impervious, seamless flooring system, where dirt and spills will remain on the surface and are easily removed by most regular cleaning procedures. Sikafloor® Pronto RB-1855 CP makes cleaning, decontamination, sanitation and sterilization fast and easy. The unique chemistry of the Sikafloor® Pronto RB-1855 CP system provides a full cure in one hour or less for each component and provides a permanent chemical bond between each coat.

# **USES**

Sikafloor® Pronto RB-1855 CP may only be used by experienced professionals.

- Used to resurface and coat concrete floors
- Use where function is a concern
- Utilize clear aluminum oxide broadcast for areas that require a non-skid texture
- Pharmaceutical and Bio-Tech research
- Life Sciences
- Warehouses and Docks
- Public assembly facilities and stadiums
- Coolers and refrigerated storage
- Dry process areas
- Packaging rooms
- Laboratories and Quality Control

# **CHARACTERISTICS / ADVANTAGES**

 Fully cures in one hour, reducing downtime for a quick return to service

**BUILDING TRUST** 

- Seamless, impervious floor that is easy to sanitize, clean and maintain
- UV resistance that provides long term color performance
- Smooth surface profile makes cleaning fast and easy
- Excellent chemical resistance for a wide range of applications
- Cures at temperatures down to 30° F (-1.1° C) to meet a wide range of application and timing requirements

#### **System Data Sheet**

Sikafloor® Pronto RB-1855 CP
September 2024, Version 03.01

# SYSTEM INFORMATION

Color	Pigmented matte finish topcoat over solid colored floors when fully cured.				
TECHNICAL INFORMATION					
Water Absorption	Sikafloor®-41 P Pronto	Sikafloor®-61 BC Pronto	Sikafloor®-53 TC Pronto	(ASTM D570)	
	0.06% / 24 hours	0.05% / 24 hours	0.05% / 24 hours		
Shore D Hardness	Sikafloor®-41 P	Sikafloor®-61	Sikafloor®-53	(ASTM D2240)	
	Pronto	BC Pronto	TC Pronto		
	75	70	80		
Abrasion Resistance	Sikafloor®-53 TC Pronto (ASTM D4060				
	74 mg loss, 1000 cycles, CS17 wheel				
Compressive Strength	Sikafloor®-61 BC Pronto				
	6,000 - 8,000 psi (filled)				
Tensile Strength	Sikafloor®-41 P Pronto Sikafloo		pr®-61 BC Pronto	(ASTM D638)	
	3,550 psi	1,050 p	si		
	<u>1,450 ps</u>		si (filled)		
Elongation at break	Sikafloor®-41 P Pronto Sikafloo		or®-61 BC Pronto	(ASTM D638)	
	1.3%	34%			
Service Temperature	180°F (83°C)				

# **APPLICATION INFORMATION**

Coverage	Description	Products	Approximate Sq.Ft./batch		
	Primer	Sikafloor®-41 P Pronto	100/gal		
		+			
		Sikafloor®-103 IN Pronto			
	Self-Leveling BodyCoat	Sikafloor®-61 BC Pronto	40 @ 1/8"/batch		
		+			
		Sikafloor®-100 SL Pronto			
	TopCoat	Sikafloor®-53 TC Pronto	100/gal		
		+			
		Sikafloor® PGM 155			
		Pronto			
	•	All coverage rates are approximate. Coverage rates will vary with the desired texture and porosity of substrate.			

# **BASIS OF PRODUCT DATA**

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

# **ENVIRONMENTAL, HEALTH AND SAFETY**

For further information and advice regarding

read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

**System Data Sheet** 

**Sikafloor® Pronto RB-1855 CP**September 2024, Version 03.01
020813900000000030



transportation, handling, storage and disposal of

Data Sheets containing physical, environmental,

chemical products, user should refer to the actual Safety

toxicological and other safety related data. User must

# **APPLICATION INSTRUCTIONS**

#### **HOW TO APPLY**

Every Sikafloor® Pronto flooring system is a multiple component system that utilizes a methyl-methacrylate (MMA) resin. It is critical that the instructions listed in the Safety Data Sheet and on the product label for every component of the system be read, understood and followed. MMA resins are flammable liquids in their uncured state. Smoking, open flames or sparks should not be permitted during the handling of the product. Explosion safe ventilation must be used during the application to minimize vapor collection in the installation area and to improve overall air quality for the crew. All foodstuffs must be removed during installation of the flooring system.

Sikafloor® Pronto flooring systems are installed by approved contracting firms. The following is only a summary of the installation techniques used by Sikafloor® Pronto approved contractors.

#### SUBSTRATE PREPARATION

- Floors must be structurally sound and fully cured a minimum of 28 days. Conduct quantitative moisture testing in accordance with ASTM F2659-10 utilizing Tramex type impedance moisture meter. Please contact Sika Flooring Technical Support if the Tramex reading is over 4%.
- Repair concrete as necessary. If any patching is required, Sikafloor® Pronto 1817 PC should be mixed and placed according to the Sikafloor® Pronto Mixing Chart.
- 3. Use a commercial degreaser to clean floors of oil, grease and other bond-inhibiting materials.
- Remove curing and parting compounds and other surface hardeners and floor coatings in accordance with manufacturer's instructions.
- 5. Mechanical surface profiling is the method of surface preparation for both new and existing floors. Mechanically profile the floor to CSP-4 as described by the International Concrete Repair Institute. Do not use acid etching for surface preparation. Do not use any method that will fracture the concrete.
- 6. Bond tests should be performed once a small area has been mechanically profiled, so any adjustments can be made to the surface preparation process. Bond tests should be repeated every 500 1,000 ft². Please refer to Bond Test Instruction Guide for further information.
- 7. Cracks wider than 1/16" (1.6 mm) should be "chased out" and opened during surface preparation. Any existing joints should be treated according to project specifications. Please refer to Joint Repair Guide for further information.
- Areas around drains and other floor fixtures need to be ground and/or chipped to a depth between 1/2" 3/4" (13 19 mm) and tapered back 3" 6" (7.6 15.2 cm) away from drain (Refer to Sikafloor® Pronto Detail Drawing CB-27.3).

 Termination points should be saw cut to a depth of 1/4" (6.4 mm) and tapered back (Refer to Sikafloor® Pronto Detail Drawing CB-27.2).

#### **MIXING**

(Refer to Sikafloor® Pronto Mixing Chart for exact batch sizes and measurements)

#### SIKAFLOOR®-41 P PRONTO PRIMER

Measure resin and Sikafloor®-103 IN Pronto into pail and add proper amount of Sikafloor®-100 HD Pronto. Mix with high speed drill for 15 – 30 seconds or until the Sikafloor®-100 HD Pronto is completely dissolved.

#### SIKAFLOOR®-61 BC PRONTO BASECOAT

Measure resin and Sikafloor® PGM 155 Pronto into a 5 gallon pail. Add 1 bag of Sikafloor®-100 SL Pronto powder and mix using a spiral mixing blade for 40 - 50 seconds, until a homogenous mixture is obtained. Add proper amount of Sikafloor®-100 HD Pronto and mix for an additional 20 - 30 seconds.

#### SIKAFLOOR®-53 TC PRONTO TOPCOAT

Please contact Sika Flooring Technical Service if utilizing Sikafloor®-71 TC Pronto as a topcoat. Measure resin and Sikafloor® PGM 155 Pronto into pail and add proper amount of Sikafloor®-100 HD Pronto. Mix with drill mixer for 15-30 seconds or until the Sikafloor®-100 HD Pronto is completely dissolved.

Note: After mixing, apply immediately. There will be 7 – 15 minutes of working time, dependent on temperature and the amount of time the material sits in the bucket.

#### **APPLICATION**

#### **PRIMER**

Apply the properly mixed Sikafloor®-41 P Pronto resin to the properly repaired concrete or properly prepared aged coating at approximately 100 ft² (9.3 m²) per gallon. Allow primer to cure tack-free to an even, satinlike gloss. Re-prime any dry spots.

#### **COVE BASE**

If a cove base is to be installed, mix and apply according to the Sikafloor® Pronto Cove Base Application Guide. Install cove base prior to installation of basecoat. Allow to cure.

# SCRATCH COAT

Any rough areas or depressions less than 1/4" (6.4 mm) should receive a scratch coat of Sikafloor®-61 BC Pronto with Sikafloor®-100 SL Pronto to smooth and level these areas. Any drips or ridges over 1/16" (1.6 mm) should be ground or sanded smooth. Allow to cure.

#### **BASECOAT**

Apply the properly mixed Sikafloor®-61 BC SL Pronto basecoat at 40 ft² (3.7 m²) per batch, at 1/8" (3.2 mm) thickness. If texture is desired, broadcast may be added

#### System Data Sheet

**Sikafloor® Pronto RB-1855 CP**September 2024, Version 03.01
020813900000000030



at this time. Backroll material with porcupine roller. Allow to cure.

#### TOPCOAT

Apply the properly mixed Sikafloor®-53 TC Pronto topcoat at approximately  $90-110~\rm{ft^2}$  (8.4 –  $10.2~\rm{m^2}$ ) per gallon. Allow to cure.

#### **DRYING TIME**

All components of the Sikafloor® Pronto RB-1855 CP flooring system fully cure within one hour when properly installed.

#### **CLEANING OF TOOLS**

Clean tools as needed with Sikafloor®-100 CLN Pronto. Collect and dispose of all site wastes according to appropriate regulations.

# **MAINTENANCE**

#### **MAINTENANCE**

Regular cleaning and maintenance will prolong the life of all polymer flooring systems, enhance their appearance and reduce any tendency to retain dirt. Follow the Sika Maintenance Guide to maximize the life of the floor.

#### FOR BEST PERFORMANCE

- Please contact Sika Flooring Technical Service for applications over 90°F (32°C).
- Not for use in areas exposed to strong solvents (consult Sika Flooring Technical Service).
- Install at recommended thickness to ensure proper curing and leveling.
- Topcoat must be back-rolled immediately to ensure uniform finish.
- Each application must be completely cured prior to the next application.
- Protect or remove food items prior to application to avoid any possible contamination.
- Use clean pails when mixing to avoid the possibility of improper curing. Swap out as needed.
- Proper air flow is critical to curing MMA materials. The use of fans is mandatory where air flow is restricted.
- Apply a bond test every 500 1,000 ft² (46.5 93 m²) prior to floor installation.
- Make certain the most current versions of product data sheet and SDS are being used.
- Proper application is the responsibility of the user.
   Field visits by Sika personnel are for the purpose of making technical recommendations only and not for

\_\_\_\_\_\_

# **OTHER RESTRICTIONS**

See Legal Disclaimer.

# LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

supervising or providing quality control on the jobsite.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at https://usa.sika.com/en/group/SikaCorp/termsandconditions.html or by calling 1-800-933-7452.

#### Sika Corporation

201 Polito Avenue Lyndhurst, NJ 07071 Phone: +1-800-933-7452 Fax: +1-201-933-6225 usa.sika.com



System Data Sheet
Sikafloor® Pronto RB-1855 CP
September 2024, Version 03.01
020813900000000030

