

Sikalastic[®] 515 AC/FG

SINGLE COMPONENT, UV STABLE, HIGHLY ELASTIC, COLD APPLIED ACRYLIC ROOF COATING

- ASTM D6083 Type I compliant
- California Title 24 compliant
- No mixing, easy and ready to use
- UV resistant non-yellowing
- Seamless roof waterproofing membrane
- Crack-bridging retains flexibility even at low temperatures

| Available | in |
|------------------|----|
| Pail | |
| 5 gallons | |



BUILDING TRUST

Sikalastic[®] 515 AC/FG

EASY TO APPLY ROOF COATING WITH EXCELLENT UV RESISTANCE AND MECHANICAL PROPERTIES




BENEFITS OF A COOL ROOF

- Reduce energy consumption of air conditioning
- Reduce urban heat island effect
- Reduce thermal stress on a roof and material itself
- Positive impact on global environment
- Increase efficiency of photovoltaic panels
- Conformity with LEED v2009 (SSc 7.2) /v4 (SSc 5)



USES

- Enhance solar reflectivity index (SRI) of existing roofs
- Extend the life of existing roofs
- Economical Roof Recovery
- Excellent adhesion to various roof substrates including asphalt, single-ply and metal roofing
- Reinforce and waterproof roof seams, penetrations and vertical transitions and termincations
- Make spot repairs of existing roofs



| | 6004 |
|--------------------------------|-------------------------------|
| Solid content by weight | 69% |
| Solid content by volume | >52% |
| Tensile Strength | 250 ± 50 psi |
| Elongation at Break | 180 ± 50% (initial) |
| Elongation at Break | 100 ± 20% (after accelerated |
| | weathering) |
| Adhesion to Peel | 2 pli for SPUR (wet |
| | adhesion) |
| Tear Strength | 90 pli |
| Low Temperature Bend | Pass 1/2" @ -15°F |
| Permeability to Wear Vapor | 25 perms |
| Water Absorption | 9% water swelling |
| Behavior after Artificial Wea- | No cracking or checking after |
| thering | 1000 hr |
| Microbiological Resistance | No growth |



FOR MORE INFORMATION:

Contact Sika: Phone 800.933.SIKA(7452) Website: usa.sika.com

Sika Corporation

201 Polito Avenue Lyndhurst, NJ 07071 Phone: 201-933-8800 Fax: 201-933-6225

/06.2795.2/09/2020