

PRODUCT DATA SHEET

BMI Acrylic 300 Coarse Finish

Exterior and Interior Acrylic Finish for Building Façades

PRODUCT DESCRIPTION

BMI Acrylic 300 Coarse Finish is a ready mixed, flexible textured, decorative and protective wall finish over prepared vertical, above grade concrete, EIFS, masonry and plaster/stucco substrates. BMI Acrylic 300 Coarse Finish can be used on either interior or exterior surfaces. BMI Acrylic 300 Coarse Finish is available in light or dark tint bases and can be integrally colored with Colorfast pigment system.

USES

BMI Acrylic 300 Coarse Finish may be used over

- Stucco base coats
- EIFS
- Prepared exterior gypsum board lids
- Prepared concrete masonry in exterior/interior applications
- Drywall
- Cement board
- Sealed gypsum plaster

PRODUCT INFORMATION

Chemical Base	<ul style="list-style-type: none"> ▪ Binder base: 100% acrylic polymer ▪ Aggregate: Pure crushed marble, rust-free ▪ Water based: VOC compliant ▪ Pigment base: Titanium dioxide
Packaging	65 lb (29.5 kg) pail
Appearance / Color	Factory tinted to desired color
Shelf Life	15 months from date of production when stored properly in original, unopened and undamaged sealed packaging.
Storage Conditions	Store dry at 50–90 °F (10–32 °C). Protect from moisture, direct sunlight, and

CHARACTERISTICS / ADVANTAGES

- Excellent adhesion properties*
- Excellent UV resistance
- Efflorescence resistance*
- Resistant to dirt pick up, mildew, algae, and fungal growth
- Vapor permeable
- Durable; good surface hardening capabilities
- Available in light or dark tint bases
- Meets SCAQMD Rule 1113 when colored with Colorfast pigments

*When used with BMI Acrylic Primer 100

APPROVALS / STANDARDS

- Exceeds ASTM and ICC Acceptance Criteria
- SCAQMD Rule 1113 VOC compliant

freezing. If frozen, discard material. Do not stack more than 3 pails high.

pH-Value 8.0-10.0

TECHNICAL INFORMATION

Crack Bridging Ability	Result	ICC/ASTM Criteria	Flexibility (Mandrel bend) (ASTM D-522 Procedure B)
	1" diameter at -4°F(-20°C)	—	
Permeability to Water Vapor	40 perms		(ASTM E-96 Procedure B)
Resistance to Weathering	Result	ICC/ASTM Criteria	
	Pass @ 5,000 hours	No deleterious effects at 2000 hours when viewed under 5X magnification.	Accelerated Weathering (ASTM G-153)
	Pass @ 35 days	No growth supported during 28 day exposure period	Mildew Resistance (ASTM D-3273) (MIL 810B-508)
	Pass @ 28 days	—	
	Pass @ 1,000 L	No cracking or loss of film integrity at 500 L of sand	Abrasion Resistance (ASTM D-968)
	Pass @ 10,000 cycles	—	Scrub Resistance (ASTM D-2486)
Freeze-Thaw Stability	Result	ICC/ASTM Criteria	(ASTM E-2485)
	Pass @ 60 cycles	No deleterious effects at 10 cycles when viewed under 5X magnification	
Water Resistance	Result	ICC/ASTM Criteria	(ASTM D-2247)
	Pass @ 28 days	No deleterious effects at 14 day exposure	
Salt Spray Resistance	Result	ICC/ASTM Criteria	(ASTM B-117)
	Pass @ 900 hours	No deleterious effects at 300 hours	
Reaction to Fire	Result	ICC/ASTM Criteria	(ASTM E-84)
	Flame Spread:0 to 15	Flame Spread < 25	
	Smoke Developed: 0 to 15	Smoke Developed < 450	

APPLICATION INFORMATION

Coverage	One coat: 110–125 ft ² (10–11.5 m ²) per pail. Aggregate size: 1.5 mm. Normal coating system is one coat. Coverage figures do not include allowance for surface profile, porosity, material waste and suction.
Ambient Air Temperature	40–100 °F (4–37.8 °C)
Substrate Temperature	40–100 °F (4–37.8 °C)
Set Time	BMI Acrylic 300 Coarse Finish will completely cure within 21 days. During the cure time the finish must be protected from severe weather conditions and from potential abuse from other trades. High humidity and low temperatures will extend cure time.
Waiting / Recoat Times	BMI Acrylic 300 Coarse Finish is dry to touch within 1–4 hours. Waiting time is

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

Surfaces must be clean and free of bond-inhibiting materials such as dirt, dust, rust, grease, oil, efflorescence, mildew, fungus, form release agents, or any other contaminants. Remove or repair any loose paint, mortar, stucco, concrete or masonry by water blasting, sandblasting, scraping or using a wire brush. Make sure surface is level prior to application. Do not use BMI Acrylic 300 Coarse Finish to level or fill "hollows" in plaster base. Substrate should be securely fastened. Repair all cracks with appropriate patching compound. Mask off area accordingly. Prime all surfaces with BMI Acrylic Primer 100 before applying BMI Acrylic Finish. For interior drywall, prepare as for painting.

MIXING

Mix with a drill mixer and jiffler paddle or similar paddle. Do not exceed 400 rpm when mixing or the product could be air entrained which will increase "pin-holing" and decrease bonding characteristics. If BMI Acrylic 300 Coarse Finish is not factory tinted, add liquid color to the pail of finish. Make sure all the color is added by rinsing out the color vial with water into the pail. Up to 16 ounces of clean potable water may be added to BMI Acrylic 300 Coarse Finish until desired consistency is achieved.

APPLICATION

BMI Acrylic 300 Coarse Finish should be applied with a clean plastic float or a stainless-steel trowel. A plastic float will roll the large aggregates more than a stainless-steel trowel and may cause swirling. Continuously dry clean the plastic float or steel trowel while texturing. Use consistent pressure and motion to achieve the desired texture. Enough material should be applied to cover all surfaces. Always apply BMI Acrylic 300 Coarse Finish in a continuous application, working to a wet edge to avoid cold joints. Finish material with a plastic float using a "figure 8" pattern. Avoid water drops and runs on uncured material. Variations in color tint should be expected. For spray application, spray with consistent motion, pressure, distance and spray angle to achieve a consistent texture. A job-site mock up for spray application is advised.

CLEANING OF TOOLS

Water soluble prior to drying. Clean tools and equipment with water immediately after use.

LIMITATIONS

- Ambient and surface temperature must be above

40°F(4°C) and below 100°F(38°C) during application and cure time.

- Provide supplemental heat and protection from precipitation as needed.
- Use only on surfaces that are sound, clean, dry, and free from any residue that might affect the ability of BMI Acrylic 300 Coarse Finish to bond to the surface.
- Allow substrate sufficient time to dry after rain or other inclement conditions.
- Minimum age of concrete prior to the application is 28 days, depending on curing and drying conditions. Moisture content must be below 5%.
- Minimum age of Portland cement plaster must be 7 days.
- Finish color is very consistent but may vary slightly depending on suction, drying time, application technique and ambient conditions.
- Finish should be protected from rain for a minimum of 4 days. If curing at low temperatures, protect for 7 days.
- Normal coating system is one coat. Adhesion and compatibility testing is recommended.
- The use of a plastic trowel may cause large aggregates to roll, creating a swirl texture.
- Application in direct sunlight might adversely affect aesthetics. Dark colors are more subject to fading than light colors.
- Not designed for use as a vehicular traffic bearing surface.
- Protect from freezing. If frozen, discard.
- Not recommended for roofing.
- Sika is not responsible for color correctness after finish has been applied.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet

BMI Acrylic 300 Coarse Finish
March 2020, Version 02.01
02181510000000055

BMIAcrylic300CoarseFinish-en-US-(03-2020)-2-1.pdf

