

## PRODUCT DATA SHEET

# Sarnatherm® XPS

Rigid extruded polystyrene insulation board

### PRODUCT DESCRIPTION

Sarnatherm® XPS is a rigid extruded polystyrene insulation board that can be used in either a Sika roofing or waterproofing application.

### USES

Wherever insulation is required within a conventional roof assembly or waterproofing application.

### AREAS OF APPLICATION

- New Roofs
- Recover Roofs
- Mechanically Attached Systems
- Adhered Systems
- Waterproofing Systems

### CHARACTERISTICS / ADVANTAGES

- Low water absorption
- Available in various sizes

### APPROVALS / STANDARDS

- ASTM C 578, Type XII, X, XIII, IV, VI, VII, V
- CAN/ULC S701, Type 4

## PRODUCT INFORMATION

<b>Chemical Base</b>	Polystyrene foam core with a smooth skin surface on the face and back surfaces
<b>Packaging</b>	<ul style="list-style-type: none"> <li>▪ 4 ft x 4 ft (1.2 m x 1.2 m)</li> <li>▪ 4 ft x 8 ft (1.2 m x 2.4 m)</li> <li>▪ Various Thicknesses</li> </ul>
<b>Shelf Life</b>	N/A
<b>Storage Conditions</b>	When stored outdoors, the insulation should be stacked on pallets at least 4" (102 mm) above the surface level and protected from exposure to direct sunlight and weather using an opaque, light-colored tarpaulin. <b>Do not use a dark colored tarpaulin.</b> The factory applied packaging is intended only for protection during transit and should only be slit enough to prevent accumulation of condensation then removed prior to immediate use. Insulation that becomes wet or damaged should be removed and replaced with dry insulation

Thickness	Thickness	R-Value	C-Value
	1.0" (25 mm)	5.0	0.200
	1.5" (38 mm)	7.5	0.133
	2.0" (51 mm)	10.0	0.100
	2.5" (64 mm)	12.5	0.080
	3.0" (76 mm)	15.0	0.067
	4.0" (102 mm)	20.0	0.050

Not all available thicknesses are listed.

## TECHNICAL INFORMATION

<b>Compressive Strength</b>	<u>Type VI</u> 40.0 psi (276 kPa)	<u>Type VII</u> 60.0 psi (414 kPa)	<u>Type V</u> 100 psi (690 kPa)	(ASTM D-1621)
	Minimum values at yield or 10 % deformation, whichever occurs first.			
<b>Flexural Strength</b>	<u>Type VI</u> 60.0 psi (414 kPa)	<u>Type VII</u> 75.0 psi (517 kPa)	<u>Type V</u> 100 psi (690 kPa)	(ASTM C-203)
	Minimum values			
<b>Dimensional Stability</b>	<u>Type VI</u> <2%	<u>Type VII</u> <2%	<u>Type V</u> <2%	(ASTM D-2126)
<b>Thermal resistance</b>	<u>Type VI</u> 5.0	<u>Type VII</u> 5.0	<u>Type V</u> 5.0	(ASTM C-177)
<b>Service Temperature</b>	<b>Maximum Use Temperature</b>			
	<u>Type VI</u> 165°F (74°C)	<u>Type VII</u> 165°F (74°C)	<u>Type V</u> 165°F (74°C)	
<b>Water Absorption</b>	<u>Type VI</u> <0.3	<u>Type VII</u> <0.3	<u>Type V</u> <0.3	(ASTM C-272)
	% by volume, maximum values			
<b>Permeability to Water Vapor</b>	<u>Type VI</u> < 1.5 perm	<u>Type VII</u> < 1.5 perm	<u>Type V</u> < 1.5 perm	(ASTM E-96)
	*Water vapor permeance varies with product type and thickness. Values are based on the desiccant method and they apply to insulation 1" (25 mm) or greater in thickness			

## Reaction to Fire

Type VI	Type VII	Type V	
Oxygen Index	Oxygen Index	Oxygen Index	(ASTM D-2863)
24.0	24.0	24.0	
% by volume			
Type VI	Type VII	Type V	
Flame spread	Flame spread	Flame spread	(ASTM E-84)
5	5	5	
Type VI	Type VII	Type V	
Smoke Developed	Smoke Developed	Smoke Developed	(ASTM E-84)
165	165	165	

\*These values are not intended to reflect hazards presented by this or any other material under actual fire conditions

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## AVAILABILITY/WARRANTY

### AVAILABILITY

From Sika Corporation – Roofing Authorized Applicators for use within Sarnafil or Sikaplan systems.

### WARRANTY

Upon successful completion of the installed roof by the Sika Authorized Applicator in compliance with Sika requirements, Sika Corporation will provide a warranty to the Building Owner via the Sika Authorized Applicator.

## LIMITATIONS

- Care must be taken whenever solvents are present near polystyrene insulation.
- Do not use solvent based adhesives with systems incorporating polystyrene insulation for roof membrane attachment.
- Foam plastic insulation will ignite if exposed to fire of sufficient heat and intensity. Protect foam insulation from exposure to open flame or other ignition sources during shipment, storage, and installation.
- Polystyrene insulations should not be used in direct contact with chimneys, heater vents, steam pipes, or other surfaces where temperatures exceed 150°F (65°C).
- Bareback membranes cannot be installed in contact with polystyrene.
- Polystyrene insulations should have additional protection in addition to normally specified cover boards in areas where dark membranes are used and where "reflected solar energy" is expected to be present.
- Areas adjacent to higher walls or other structures with reflective cladding should be considered for additional

heat protection. For example, areas near metal or glass cladding, or near, or in between large groupings of mechanical equipment, or near higher reflective parapets, should be considered for additional heat protection. Additional heat protection for such roof areas include covering roofing membrane with Sarnafil PVC Protection Layer and then applying pavers or ballast to the affected area.

- Polystyrene insulation is susceptible to degradation when exposed to high temperatures or when exposed to solvents or solvent fumes. The typical maximum service temperature for polystyrene insulations is 165°F (74°C). Should ambient or surface temperature be expected to exceed this value, please consult the manufacturer of the insulation.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## APPLICATION INSTRUCTIONS

Sarnatherm XPS is installed either under or over the Sika roofing/waterproofing membrane depending on the system design. Overburden is utilized to hold the insulation in place in a waterproofing application. Polystyrene should not come in contact with PVC. Always place a separation layer such as Sarnafelt NWP between the Sarnatherm XPS and the membrane in both roofing and waterproofing applications. During installation in hot, sunny weather, protect the insulation with a white covering to prevent excessive heat build-up and potential warping. If the compressive strength of the EPS board is less than 20 psi, then a gypsum cover board must be installed over the board for load distribution and resistance purposes.

## MAINTENANCE

Standard maintenance of Sarnafil and Sikaplan systems should include regular inspections of flashings, drains and terminations sealants at least twice a year and after each storm.

## OTHER RESTRICTIONS

See Legal Disclaimer.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

**Sika Corporation**  
201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)

**Sika Sarnafil**  
100 Dan Road  
Canton, MA 02021  
Phone: +1 800-451-2504  
Fax: +1 781-828-5365  
[usa.sika.com/sarnafil](http://usa.sika.com/sarnafil)  
[webmaster.sarnafil@us.sika.com](mailto:webmaster.sarnafil@us.sika.com)

**Sika Mexicana S.A. de C.V.**  
Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



**Product Data Sheet**  
Sarnatherm® XPS  
November 2021, Version 04.01  
020935052000005010

SarnathermXPS-en-US-(11-2021)-4-1.pdf

