

PRODUCT DATA SHEET

Sika® Fibermesh®-150F

MICRO-SYNTHETIC MONOFILAMENT FIBER

PRODUCT DESCRIPTION

Sika® Fibermesh®-150F micro reinforcement system for concrete - 100 percent virgin homopolymer polypropylene multifilament (monofilament) fibers. Specifically engineered and manufactured in an ISO 9001 certified manufacturing facility. Sika® Fibermesh®-150F previously SikaFiber PPM.

USES

Applicable to all types of concrete which demonstrate a need for resistance to fire spalling, intrinsic cracking, and improved water tightness

- Tunnel
- High rise buildings
- Concrete framed structures
- Bridges / underpasses
- Multi story garages
- Oil Platforms
- Precast
- Shotcrete

CHARACTERISTICS / ADVANTAGES

- Reduces fire explosive spalling
- Inhibits and controls the formation of intrinsic cracking in concrete
- Increases cohesion and reduces segregation
- Reduces settlement and bleeding
- Provides durability

ENVIRONMENTAL INFORMATION

Lowers carbon footprint through the removal of rebar or wire mesh reinforcing which has a higher GWP.

A Type III Product-Specific Environmental Product Declaration (EPD) and a Manufacturer Inventory are available for Sika® Fibermesh®-150F. For further information, please visit: <https://usa.sika.com/en/sustainability.html>

APPROVALS / STANDARDS

- Complies with European Standard EN 14889-2:2006 Fibres for Concrete Part 2: Class 1b and carries CE marking
- UL Classified: Fibermesh 150. For use in Floor-Ceiling D700, D800, D900, G229, G243, G256, G514 Series Designs.
- Complies with ASTM C 1116/C 1116M, Type III fiber reinforced concrete and therefore ASTM D7508

PRODUCT INFORMATION

Fiber Volume Content

125 million fibers per kilogram at 12mm in length

Packaging	Sika® Fibermesh®-150F fibers are available in a variety of packaging options. The 2.2 lb degradable bags (1.0 kg) is standard. The bags are packed into cartons and palletized.
Shelf Life	When stored in dry conditions shelf life is 5 years
Storage Conditions	Sika® Fibermesh®-150F should be stored in a dry warehouse. Protect product from the rain.
Fiber Type	Monofilament micro synthetic fiber
Dimensions	<ul style="list-style-type: none"> ▪ Length: 0.25 or 0.5 inches (6 or 12.7 mm) ▪ Diameter: 0.0012 inches or 6 denier (0.03 mm) ▪ Aspect Ratio: 200 or 390
Density	0.91
Melting Point	324 °F (162 °C)

TECHNICAL INFORMATION

Resistance to Alkalinity	Excellent
---------------------------------	-----------

APPLICATION INFORMATION

Recommended Dosage	The dosage of the Sika® Fibermesh®-150F will vary according to the Fire Testing Requirements. Standard recommend dosage of Sika® Fibermesh®-150F according to the EN standard is 3.4 lb/yd ³ (2 kg/m ³) of concrete.
---------------------------	---

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA’s Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF**



MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet
Sika® Fibermesh®-150F
June 2024, Version 02.01
021408031010000005

SikaFibermesh-150F-en-US-(06-2024)-2-1.pdf

