



SikaGrout®

HIGH PERFORMANCE CEMENTITIOUS GROUT • ANCHORING GROUT

MATERIALS:

- Safety glasses and gloves Utility knife Bag of SikaGrout® Sufficient water for desired mix
- Mixing container Mixing paddle Trowel/shovel Drill & mortar paddle (for large quantities)

SITE PREP & PROCEDURE

- Remember to always wear waterproof gloves and safety goggles whenever mixing or using cement-based products.
- 2. Mix the grout with clean water in a separate mixing container for 3 minutes to obtain desired consistency. Add only enough water to achieve the flow required for the application.

Mixing Ratio

Plastic ¹	Flowable ¹	Fluid ²	
6 pt.+	6.5 pt.	8.5 pt.	

 1 CRD C-227: 100–124 % (plastic), 124–145 % (flowable) 2 CRD C-611: 10–30 sec efflux time.

- 3. Maximum addition of water is 8.5 pints per 50 lb. bag.
- Small quantities can be mixed with a trowel or shovel. For best results, larger quantities should be mixed with a slow speed drill and mortar paddle or a conventional mortar mixer.
- 5. Within 15 minutes of mixing, place the grout in the hole or void. Pour or ram grout as necessary, to fill the form area.









