

PRODUCT DATA SHEET

BMI Plain Stucco

Exterior Stucco

PRODUCT DESCRIPTION

BMI Plain Stucco is a cement-based product for a permanent decorative finish over exterior surfaces. Material is factory prepared using raw ingredients that meet or exceed ASTM specifications.

USES

- BMI Plain Stucco is economical and low maintenance.
- It is a decorative finish designed to be painted

CHARACTERISTICS / ADVANTAGES

- Long life cycle
- Economical
- Fire resistant
- Impact resistant
- Insect resistant

APPROVALS / STANDARDS

Material Standards:

- Hydrated Type-S Lime: ASTM C-206
- Portland Cement Type II/V: ASTM C-150 Type I
- BMI Exterior Stucco Finish: ASTM C-926

PRODUCT INFORMATION

Packaging	90 lb (40.77 kg) bag
Appearance / Color	<ul style="list-style-type: none"> ▪ Gray base ▪ Texture available in Float 16/20, Texture 20/30, Marble, Dash, 20 mesh, 30 mesh, 70 mesh, or upon job specification. ▪ It is not recommended to mix with BMI color packs integral coloring system
Shelf Life	12 months from date of production if stored properly in original, unopened and undamaged sealed packaging
Storage Conditions	Store dry at 40–95 °F (4–35 °C) Protect from moisture. If damp, discard material.

APPLICATION INFORMATION

Mixing Ratio	3 gal (11.4 L) per bag	
Coverage	Sand/Float finish	12–16 yd ³
	Machine/Dash finish	8–12 yd ³

(Coverage figures do not include allowance for surface profile and porosity or material waste)

Layer Thickness	1/16"–1/8"
Ambient Air Temperature	> 40 °F (5 °C)
Set Time	> 90 minutes

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

- The brown coat shall be a uniform properly prepared Portland cement-based substrate.
- The brown coat should be moist cured for at least 48 hours and allowed to dry completely for a minimum of 7 days.

MIXING

- BMI Plain Stucco shall be power mixed with clean water for at least 15 minutes to assure complete hydration.
- Do not attempt to temper material that has started to set.

APPLICATION

Hand application

- Apply using trowel.
- Spread on even coat then rubber float (sand finish) or trowel to desired texture.

Gun Application

- Spray first coat over dry surface and cover base coat completely.
- After first coat has dried, spray second coat in thinner consistency and bring to the desired texture.
- During periods of hot and dry weather, lightly mist with clean water.
- BMI Plain Stucco will normally dry and set the same day.
- Final hardness will be reached in 28 days.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

0 g/l (EPA method 24)

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD**

BY OTHERS.

Sale of Sika products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet

BMI Plain Stucco
March 2020, Version 02.01
02181010100000013

BMIPlainStucco-en-US-(03-2020)-2-1.pdf

