**Jika**®

**BUILDING TRUST** 

# PRODUCT DATA SHEET

## SikaLatex<sup>®</sup> R

Acrylic latex bonding agent/admixture for portland-cement mortar/concrete

## **PRODUCT DESCRIPTION**

SikaLatex<sup>®</sup> R is an acrylic-polymer latex. It is not reemulsifiable. It is a general purpose admixture which will produce polymer-modified concrete and mortar. Sika Latex R is also a bonding grout when mixed with sand and portland cement.

### USES

- Admixture (replacing water) used in cement based products to improve adhesion, achieve a denser surface, and improve overall performance
- As a bonding grout (prime coat) when mixed with sand and portland cement

## **PRODUCT INFORMATION**

## **CHARACTERISTICS / ADVANTAGES**

- Concrete/Mortar/Grout/etc. containing SikaLatex<sup>®</sup> R exhibits improved adhesion to pre-pared substrates
- Increased adhesive strength of mortar/concrete when used as a bonding grout
- Increased resistance to freeze/thaw durability
- Does not produce a vapor barrier

Packaging	1 qt. (.94 L), 6/case 1 gal. (3.8 L) jug, 4/case 5 gal. (19 L) pail 55 gal. (208 L) drum (special order)
Shelf Life	12 months in original, unopened containers
Storage Conditions	Store dry at 40 to 95 °F (4 to 35 °C). Condition material to 60 to 75 °F (15 to 167 °C) before using. Protect from freezing. If frozen, discard

## **TECHNICAL INFORMATION**

Tensile Adhesion Strength	Slurry, scrub coat	(ASTM C-882) Tested at: 73 °F (23 °C) 50 % R.H.
	2 parts sand, 1 part cement. SikaLatex <sup>®</sup> R added to produce a creamy consistency.	
	Plastic Concrete to Hardened Concrete 28 days > 500 psi (3.4 MPa) Bond Strength	

## **APPLICATION INFORMATION**

 Product Data Sheet

 SikaLatex® R

 October 2018, Version 01.02

 020301010010000098

As mixing solution: for Concrete/Mortar/Grout/etc. use neat, replacing the amount of water typically recommended As a bonding grout: estimated coverage based on amount of material (sand/cement) mixed

## **APPLICATION INSTRUCTIONS**

#### SURFACE PREPARATION

**Applying Concrete/Mortar:** Remove all deteriorated concrete, dirt, oil, grease, and all bond-inhibiting materials from surface. Be sure repair is not less than 1/8 in. (3.2 mm) in depth. Preparation work should be done by high pressure water blast, scabbler, or other appropriate mechanical means to obtain an aggregate-fractured surface with a minimum surface profile of 1/16 in. (1.6 mm). Saturate surface with clean water. Substrate should be saturated surface dry (SSD) with no standing water during application.

#### MIXING

As admixture/mixing solution: With mixer running, add materials in the following order: SikaLatex<sup>®</sup> R solution and then the cement based product. Replace the amount of water recommended by the product. Do not dilute with water.

As a bonding grout: With the mixer running, add in the following order. SikaLatex<sup>®</sup> R solution, aggregate, cement. The ratio is 1 part cement, 2 parts sand, and a sufficient amount of undiluted SikaLatex<sup>®</sup> R to produce a creamy paint consistency. Maximum 4 gal./sack of cement (15L/sack of cement).

**As a primer for acrylic coatings:** No dilution is required. Use as is.

#### **APPLICATION METHOD / TOOLS**

Admixture: Immediately trowel SikaLatex<sup>®</sup> R mortar or concrete mix into areas to be patched. Do not overfinish. As soon as the application is done, to prevent damage, cure with damp burlap and/or white pigmented polyethylene film. Curing should continue for 24 hours. Pre-testing is recommended when adding SikaLatex<sup>®</sup> R to a specific mix design to assure the results required.

**Bonding Grout:** Brush grout into area to be resurfaced with stiff-bristled broom or scrub brush. Be sure entire surface and all edges are coated. Apply topping immediately over scrub coat before the bonding slurry dries.

**Primer (for acrylic coatings only):** Apply undiluted SikaLatex<sup>®</sup> R to prepared concrete substrate using brushes, rollers, soft brooms, or spray. SikaLatex<sup>®</sup> R must be tack-free (film formation) prior to coating. Estimated coverage on a CSP-3 prepared surface is 300 ft<sup>2</sup>/gal. (7 m<sup>2</sup>/l) SikaLatex<sup>®</sup> R primer may be applied up to 24 hours ahead providing the area is kept dry and clean. Very porous concrete may require a second coat of

 Product Data Sheet

 SikaLatex® R

 October 2018, Version 01.02

 020301010010000098

SikaLatex<sup>®</sup> R to seal the surface.



## LIMITATIONS

- Not resistant to UV rays unless painted, covered or coated.
- Will not adhere to polyethylene, teflon, silicone, oils and greases, mold release agents and similar materials.
- Do not expose to open flame or temperatures above 120 °F (49 °C). Excessive heat can cause shorter shelf life.
- Not intended as a firestop.
- Do not use where temperatures rise above 240 °F (116 °C).
- As with all cement based materials, avoid contact with aluminum to prevent adverse chemical reaction and possible product failure. Insulate potential areas of contact by coating aluminum bars, rails, posts etc.

## **BASIS OF PRODUCT DATA**

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## **OTHER RESTRICTIONS**

See Legal Disclaimer.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at https://usa.sika.com/en/group/SikaCorp/termsandconditions.html or by calling 1-800-933-7452.

**BUILDING TRUST** 

#### Sika Corporation

201 Polito Avenue Lyndhurst, NJ 07071 Phone: +1-800-933-7452 Fax: +1-201-933-6225 usa.sika.com



Product Data Sheet SikaLatex® R October 2018, Version 01.02 020301010010000098

#### Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5 Fracc. Industrial Balvanera Corregidora, Queretaro C.P. 76920 Phone: 52 442 2385800 Fax: 52 442 2250537

SikaLatexR-en-US-(10-2018)-1-2.pdf

