

## PRODUCT DATA SHEET

# Sikafloor® Marine VEM

Self-smoothing visco-elastic damping mortar for interior decks

**TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)**

Chemical base		Polymer modified cement
Color		Grey
Cure mechanism		Hydraulic
Density	mixed	1.5 kg/l
	cured	1.3 kg/l
Mixing ratio	per 16 kg bag	5.3 – 5.8 litres
Substrate temperature		5 – 30 °C
Application thickness	max.	2 mm
Coverage	per 16 kg bag at layer thickness 2 mm	6 m <sup>2</sup>
Working time (CQP599-9)		30 minutes <sup>A</sup>
Ready to walk on (CQP600-3)	depending on humidity and ventilation	12 hours <sup>A</sup>
Tensile strength (CQP036-2)		0.6 MPa <sup>B</sup>
Elongation at break (CQP036-2)		55 % <sup>B</sup>
Shore A (CQP023-1)		75 <sup>B</sup>
Shelf life		12 months <sup>C</sup>

CQP = Corporate Quality Procedure

<sup>A</sup>) 23 °C / 50 % r. h.v<sup>B</sup>) after 28 days<sup>C</sup>) stored in a dry, cool place below 25 °C
**DESCRIPTION**

Sikafloor® Marine VEM is a 1-component damping, self-smoothing mortar based on polymer modified cement. It is specifically designed to be used in combination with Sikafloor® Marine-18, -118 FC or -190 mortars to reduce low frequency structure borne noise.

Sikafloor® Marine VEM is tested according to FTP Code system and approved according to the IMO Marine Equipment Directives.


**PRODUCT BENEFITS**

- Visco-elastic mortar
- Isocyanate free
- High damping factor
- Can be pumped
- One component, ready to mix
- Environmental friendly

**AREAS OF APPLICATION**

Sikafloor® Marine VEM is applied on interior decks in combination with Sikafloor® Marine-18, -118 FC and -190 mortars. It is suitable for application in dry and wet areas.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.



## CURE MECHANISM

Sikafloor® Marine VEM cures by way of hydraulic curing.

## METHOD OF APPLICATION

### Surface Preparation

For applications, the surface has to be clean, free from dust, grease, oils and other substances, which may impair adhesion. Rust has to be removed with a steel brush or other appropriate means, followed by vacuum cleaning. The surface has to be primed with Sikafloor® Marine Primer C using a long hair roller. After drying of the Sikafloor® Marine Primer C, Sikafloor® Marine VEM may be applied. Sikafloor® Marine VEM applications on aluminum or zinc rich shop primer coated decks, require a tie coat of SikaCor® ZP Primer or another suitable tie coat prior the priming step with Sikafloor® Marine Primer C.

### Mixing process

One bag of Sikafloor® Marine VEM is mixed with 5.3 to 5.8 liters cold potable water. The mixing time with a drilling machine and proper mixing paddles is approx. 5 minutes (not higher than 400 rpm).

Ensure the product is mixed homogenously including bottom and side walls of the mixing bucket.

### Application

Apply the mortar with an appropriate notched trowel in order to get a layer thickness of 1.5 – 2 mm.

Sikafloor® Marine VEM has to be applied within 30 minutes after mixing. At temperatures above 30 °C the open time will be reduced to 10 minutes or less.

For advice on selecting and setting up a suitable pump system, contact the System Engineering Department of Sika Industry.

## Curing

After application, the finished areas have to be protected against direct heat (e.g. cutting or welding from beneath), sunlight and draught during the curing process for at least 12 hours.

## Removal

Excess material can best be removed before curing with a trowel wipe or water.

Fresh Sikafloor® Marine VEM may be removed from tools and equipment with water. Once cured, the material can only be removed mechanically.

Exposed hands and skin shall be washed immediately with water. Use a suitable skin protection hand cream.

## Application Limits

For applications on sloping surfaces > 1 % contact the Technical Department of Sika Industry.

## FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheet
- Application Manual
- Sikafloor® Marine VEM With Constrained Mortars

## PACKAGING INFORMATION

Bag	16 kg
-----	-------

## BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## LEGAL DISCLAIMER

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by contacting SIKA's Technical Service Department via email at [tsmh@us.sika.com](mailto:tsmh@us.sika.com). Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.** Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling +1 800-933-7452.

## PRODUCT DATA SHEET

Sikafloor® Marine VEM  
Version 03.01 (07 - 2024), en\_US  
019319000184001000

## Sika Corporation

30800 Stephenson Highway  
Madison Heights, MI 48071  
U.S.A.  
Telephone: +1 248-577-0020  
Email: [tsmh@us.sika.com](mailto:tsmh@us.sika.com)  
[www.sikausa.com](http://www.sikausa.com)

