

# SYSTEM DATA SHEET

# Sikafloor® DecoDur Quartz FX

DECORATIVE EPOXY AND COLORED QUARTZ BROADCAST FLOOR SYSTEM ENGINEERED WITH SIKAFLOOR-217 @ 1/8" (3.1 MM)

#### PRODUCT DESCRIPTION

Sikafloor® DecoDur Quartz FX is a seamless, decorative, broadcast and sealed epoxy floor, using colored quartz aggregates and finished with a transpart top coat. The system provides a durable, impermeable lightly textured, slip resistant finish with excellent mechanical and chemical resistance. Sikafloor epoxy, polyaspartic and urethane top coats and surface textures are available to produce a wide range of slip resistant finishes suited to specific needs. Sikafloor® DecoDur Quartz FX is typically installed @ 1/8" (3.1 mm).

#### **USES**

Sikafloor® DecoDur Quartz FX may only be used by experienced professionals.

- Grocery stores
- Food packing rooms
- Commercial kitchens
- Department stores
- Factories
- Pharmaceutical laboratories and offices
- Hospitals, laboratories and health care facilities
- Museums and galleries
- Banks, office and government buildings
- Recreational facilities, change rooms and showers

# **CHARACTERISTICS / ADVANTAGES**

**BUILDING TRUST** 


- Durable, seamless and sanitary
- Excellent mechanical and chemical resistance
- Promotes a safe and hygienic work environment
- Very low maintenance
- Extensive color palette
- Low odor / low VOC
- Optional Integral cove base and curbs are available

**System Data Sheet** 

**Sikafloor® DecoDur Quartz FX**April 2021, Version 01.02
02081190000000169

#### **System Structure**

### Sikafloor® DecoDur Quartz FX @ (1/8" - 3.1mm)



Description	Products	Thickness mils
1. Primer	Sikafloor®-161	8 - 10
	Sikafloor®-217	
2. 1st Receiver Coat	+	12 - 16
	Sikafloor® Decorative Quartz	
	Sikafloor®-217	
3. 2 <sup>nd</sup> Receiver Coat	+	12 - 16
	Sikafloor® Decorative Quartz	
4. Top Coat	Sikafloor®-217	16 - 18
Options		
Primers	Sikafloor®-1610	8 - 10
	Sikafloor®-165 FS	8 - 10
	Sikafloor®-511*	
2 <sup>nd</sup> Receiver Coat	+	16 - 18
	Sikafloor® Decorative Quartz	
Top Coats	Sikafloor®-511*	15 - 18
	Sikafloor®-225 N**	15 - 18
	Sikafloor®-340***	4 - 6
2 <sup>nd</sup> Top Coats	Sikafloor®-315 N ***	4 - 6
	Sikafloor®-304 W NA****	5 - 8

 $<sup>\</sup>ensuremath{^*}$  Sikafloor-217 may be replaced by Sikafloor-511 for increased UV resistance, fast cure time

<sup>\*\*\*\*</sup> Sikafloor-304 W would be an optional  $2^{nd}$  top coat on top of Sikafloor-217 for gloss reduction or matte finish

Color	Available in various color patterns, refer to Sikafloor® Quartzite® Color Chart for details
Nominal thickness	1/8" (3.1 mm)
Minimum thickness	1/8" (3.1 mm).

**System Data Sheet** 

**Sikafloor® DecoDur Quartz FX**April 2021, Version 01.02
02081190000000169



<sup>\*\*</sup> Sikafloor-217 may be replaced by Sikafloor-225 N for increased UV resistance

<sup>\*\*\*</sup> Sikafloor-340 and Sikafloor-315 N clear would be an optional 2<sup>nd</sup> top coat for increased chemical resistance

# **TECHNICAL INFORMATION**

Water Absorption	0.13 % 2 hours boiling	ASTM C413 at 73°F (23°C) and 50% R.H
Shore D Hardness	80	ASTM D2240 at $73^{\circ}$ F ( $23^{\circ}$ C) and $50\%$ R.H
Abrasion Resistance	58 mg loss (CS-17/1000 rotations/1000g)	ASTM D4060 at 73°F (23°C) and 50% R.H
Indentation	1.30%	(MIL-PRF-24613)
Compressive Strength	12,500 psi (86 Mpa) (28 days	ASTM C579 at 73°F (23°C) and 50% R.H
Tensile Strength	5,078 psi (34 MPa)	ASTM D638 at 73°F (23°C) and 50% R.H
Flexural Strength	9,284 psi (64 MPa)	ASTM D790 at 73°F (23°C) and 50% R.H
Tensile Adhesion Strength	>400 psi (2.7 MPa) (100 % concrete failure)	ASTM D4541 at 73°F (23°C) and 50% R.H
Reaction to Fire	Class 1	ASTM E648 at 73°F (23°C) and 50% R.H
Chemical Resistance	Contact Sika Technical Service for specific info	rmation.
Coefficient of Friction	0.6	ANSI 326.3 at 73°F (23°C) and 50% R.H

# **APPLICATION INFORMATION**

#### Coverage

Description	Products	Approximates Sq.Ft./kit
1. Primer	Sikafloor®-161	900@8mils
	Sikafloor®-217	600@12 mils
2. 1st Receiver Coat	+	4.8 bags per
	Sikafloor® Decorative Quartz	4.5 gallon kit
3. 2 <sup>nd</sup> Receiver Coat	Sikafloor®-217	450@16 mils
	+	4.8 bags per
	Sikafloor® Decorative Quartz	4.5 gallon kit
3. Top Coat	Sikafloor®-217	450@16 mils
Options	Cile flee v® 1C10	000 @0 mile
Primers	Sikafloor®-1610	900@8mils
	Sikafloor®-165 FS	1,000@8mils
	Sikafloor®-511	972@16mils
2 <sup>nd</sup> Receiver Coat	+	8.8 bags per
	Sikafloor® Decorative Quartz	8.33 gallon kit
Top Coats	Sikafloor®-511	833@16mils
	Sikafloor®-225 N	1,500@15mils
	Sikafloor®-340	6,000@4mils
2 <sup>nd</sup> Top Coats	Sikafloor®-315 N	2,400@4mils
	Sikafloor®-304 W NA	595@5mils

System Data Sheet Sikafloor® DecoDur Quartz FX April 2021, Version 01.02 02081190000000169



Ambient Air Temperature	Minimum/Maximum 50/85 °F (10/30 °C)
Substrate Temperature	Minimum/Maximum 50/85 °F (10/30 °C)
PRODUCT INFORMATIO	DN
Packaging	Please refer to the individual Product Data Sheets
Shelf Life	Please refer to the individual Product Data Sheets
Storage Conditions	Please refer to the individual Product Data Sheets

#### **BASIS OF PRODUCT DATA**

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

#### **LIMITATIONS**

Please refer to the individual Product Data Sheets

## **ENVIRONMENTAL, HEALTH AND SAFETY**

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

#### APPLICATION INSTRUCTIONS

#### SUBSTRATE PREPARATION

Concrete surfaces must be clean and sound. Remove all dust, dirt, existing paint films, efflorescence, exudates, laitance, form oils, hydraulic or fuel oils, brake fluid, grease, fungus, mildew, biological residues or any other contaminants which may prohibit a good bond.

Prepare the surface by any appropriate mechanical means, in order to achieve a profile equivalent to ICRI - CSP 3-6. The compressive strength of the concrete substrate should be at least 3,625 psi (25 MPa) at 28 days and a minimum of 218 psi (1.5 MPa) in tension at the time of application.

Repairs to cementitious substrates, filling of blowholes, leveling of irregularities, etc. should be carried out using an appropriate Sika profiling mortar. Contact Sika Technical Service for a recommendation.

#### Primer

Priming for concrete substrate is required. Prime with either Sikafloor®- 161, Sikafloor®- 1610 or Sikafloor®- 165 FS. Allow the primer to cure (varies with temperature and humidity) until tack free before applying subsequent membrane coats. Ensure that the primer is pore-free, pinhole-free and provides uniform and complete coverage over the entire substrate.

Please refer to the individual most current and respective Product Data Sheet for specific and detailed information.

#### **MIXING**

Please refer to the individual Product Data Sheets

#### **APPLICATION**

Please refer to the individual Product Data Sheets



#### **OTHER RESTRICTIONS**

See Legal Disclaimer.

#### **LEGAL DISCLAIMER**

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at https://usa.sika.com/en/group/SikaCorp/termsandconditions.html or by calling 1-800-933-7452.

#### Sika Corporation

201 Polito Avenue Lyndhurst, NJ 07071 Phone: +1-800-933-7452 Fax: +1-201-933-6225 usa.sika.com Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5 Fracc. Industrial Balvanera Corregidora, Queretaro C.P. 76920

Phone: 52 442 2385800 Fax: 52 442 2250537



System Data Sheet
Sikafloor® DecoDur Quartz FX
April 2021, Version 01.02
02081190000000169