**Jika**®

**BUILDING TRUST** 

# PRODUCT DATA SHEET Sarnafil® G 410-72 Textured

Sarnafil G 410 Roof Membrane is a PVC thermoplastic membrane

# **PRODUCT DESCRIPTION**

Sarnafil<sup>®</sup> G 410-72 Textured Roof Membrane is a PVC thermoplastic membrane produced with an integral fiberglass mat reinforcement for excellent dimensional stability, with heat-weldable seams, and a textured surface.

## USES

Sarnafil G 410 is used in adhered applications with various adhesives, over various substrates.

#### AREAS OF APPLICATION

- New Roofs
- Reroofs
- Recovers

# **CHARACTERISTICS / ADVANTAGES**

- Embossed surface
- Excellent dimensional stability
- Hot-air welded seams for long-term performance
- Superior fire resistance
- Proven membrane performance

# **APPROVALS / STANDARDS**

- FM Global
- Underwriters Laboratories
- ICC Code Compliance ESR 1157
- Miami-Dade County
- Florida Building Code
- LEED / Green Globes
- NSF/ANSI 347: Platinum Certified

**Product Data Sheet Sarnafil® G 410-72 Textured** September 2020, Version 03.01 020905052190183002

# **PRODUCT INFORMATION**

Chemical Base	High quality, PVC membrane containing ultraviolet light stabilizers, flame retardant and fiberglass reinforcement		
Reinforcing Material	Fiberglass		
Packaging	72 mil (1.8 mm) Membrane* 10 ft x 100 ft (3.05 m x 30.5 m) roll, 470 lbs (214 kg) per roll, 4 rolls per pallet 5 ft x 100 ft (1.52 m x 30.5 m) roll, 235 lbs (107 kg) per roll, 9 rolls per pallet * Made to order, minimum volume required, extended production lead times. Consult with Sika – Roofing representative for further information.		
Appearance / Color	<ul><li>Top: Gray</li><li>Bottom: Dark Gray</li></ul>		
Shelf Life	N/A		
Storage Conditions	Store rolls on pallets and fully protected from the weather with clean canvas tarpaulins. Unvented polyethylene tarpaulins are not accepted due to the accumulation of moisture beneath the tarpaulin in certain weather conditions that may affect the ease of membrane weldability.		
Top surface	Textured		
Overall Thickness	72 mil (1.8 mm), minimum thickness 60 mil	(ASTM D-751 (ASTM Type II D-4434 Spec. Requirement	
Thickness Above Scrim	Exceed 16 mil	(ASTM D-7635 (ASTM Type III D-4434 Spec. Requirement	

# **TECHNICAL INFORMATION**

Resistance to Static Puncture	Pass	(ASTM D-5602)
	33 lbf (15 kg)	(ASTM Type II D-4434 Spec. Requirement)
Resistance to Dynamic Puncture	Pass	(ASTM D-5635)
	7.3 ft-lbf (10 J)	(ASTM Type II D-4434 Spec. Requirement)
Tensile Strength	100 lbf (445 N)	(ASTM D-751)
	55 lbf (245 N)	(ASTM Type II D-4434 Spec. Requirement)
Elongation at Break	250 & 220% MD & CMD <sup>1</sup>	(ASTM D-751)
	250 & 220% MD & CMD <sup>1</sup>	(ASTM Type II D-4434 Spec. Requirement)
	$^{1}$ MD = Machine Direction, CMD = Cross Machine Direction	
Linear Dimensional Change	-0.01%	(ASTM D-1204)
	0.1%	(ASTM Type II D-4434 Spec. Requirement)
Tear Strength	20.5 lbf (91 N)	(ASTM D-1004)
·	10 lbf (45 N)	(ASTM Type II D-4434 Spec. Requirement)
Seam Strength	Pass	(ASTM D-751)
-	75% of original <sup>2</sup>	(ASTM Type II D-4434 Spec. Requirement)
	<sup>2</sup> Failure occurs through membrane rupture not seam failure	
Low Temperature Bend	Pass	(ASTM D-2136)
	Pass -40°F (-40°C)	(ASTM Type II D-4434 Spec. Requirement)

 Product Data Sheet

 Sarnafil® G 410-72 Textured

 September 2020, Version 03.01

 020905052190183002



**BUILDING TRUST** 

Retention of Properties after Heat Agei	<b>g</b> Tensile Strength, % of original: Pass Elongation, % of original: Pass Tensile Strength, % of original: 90 Elongation, % of original: 90		(ASTM D-3045) (ASTM D-751) (ASTM Type II D-4434 Spec. Requirement)
UV Exposure	10,000 hours 5,000 hours		(ASTM G-154) (ASTM Type II D-4434 Spec. Requirement)
	Cracking (7x magnification)	None	
	Discoloration (by observation)	Negligib	le
	Crazing (7x magnification)	None	
Weight Change after Immersion in Wat	er Pass		(ASTM D-570)

+ 3.0%

(ASTM D-570) (ASTM Type II D-4434 Spec. Requirement)

# **APPLICATION INSTRUCTIONS**

## APPLICATION

Make sure Sarnafil G 410 Textured is installed with the textured side of the membrane facing up. Sarnafil G 410 is installed after proper preparation of the approved substrate. The membrane is unrolled into Sarnacol® adhesive in accordance with Sika's technical requirements and then pressed into place with a minimum 75 lb (34 kg) steel roller. Sarnafil G 410 seams are heat-welded together by trained operators using hot-air welding equipment. Different Sarnacol adhesives require different application methods. Please consult Sika's Specifications or Applicator Handbook for detailed installation procedures.

# MAINTENANCE

Standard maintenance of Sarnafil systems should include regular inspections of flashings, drains, and termination sealants at least twice a year and after each storm.

# **AVAILABILITY/WARRANTY**

## AVAILABILITY

From Sika Corporation – Roofing Authorized Applicators for use within Sarnafil or Sikaplan systems.

#### WARRANTY

Upon successful completion of the installed roof by the Sika Authorized Applicator, Sika Corporation will provide a warranty to the Building Owner via the Sika Authorized Applicator.

# **BASIS OF PRODUCT DATA**

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual

Product Data Sheet Sarnafil® G 410-72 Textured September 2020, Version 03.01 020905052190183002 site conditions and curing conditions.

# **OTHER RESTRICTIONS**

See Legal Disclaimer.

# **ENVIRONMENTAL, HEALTH AND SAFETY**

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.



## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
   FOR INDUSTRIAL USE ONLY

• FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD **BY OTHERS.** 

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at https://usa.sika.com/en/group/SikaCorp/termsandconditions.html or by calling 1-800-933-7452.

#### Sika Corporation

201 Polito Avenue Lyndhurst, NJ 07071 Phone: +1-800-933-7452 Fax: +1-201-933-6225 usa.sika.com



Product Data Sheet Sarnafil® G 410-72 Textured September 2020, Version 03.01 020905052190183002

#### Sika Sarnafil

100 Dan Road Canton, MA 02021 Phone: +1 800-451-2504 Fax: +1 781-828-5365 usa.sika.com/sarnafil webmaster.sarnafil@us.sika.com

#### Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5 Fracc. Industrial Balvanera Corregidora, Queretaro C.P. 76920 Phone: 52 442 2385800 Fax: 52 442 2250537

SarnafilG410-72Textured-en-US-(09-2020)-3-1.pdf



**BUILDING TRUST**