

TECHNICAL DATA SHEET

EPOLAM 2092 with EPOLAM 2092 Hardener

HIGH TEMP EPOXY LAMINATING / INFUSION SYSTEM 416°F (213°C) TG (TMA) – 553 CPS. MIXED VISCOSITY

DESCRIPTION

Epolam 2092 can be used in the production of composite tooling and structures by the usual impregnation methods (infusion, wet-lay-up).

APPLICATIONS

- *High performance, high temperature composite tools or parts for aerospace and other industries*
- *Suitable for infusion processing along with wet-layup and vacuum bagging processes*

PROPERTIES

- *Very High Tg*
- *Low mixed viscosity*
- *Very Long pot life*
- *R.T. set up 16 hrs (brittle state)*
- *Self-supporting with only 16 hr/122°F cure*
- *Excellent ultimate properties after final post-cure*

PROPERTIES

Composition	Units	2092 Resin	2092 Hardener	Mixed
Mix ratio – by weight		100	50	100/50
Mix ratio – by volume		100	63	100/63
Aspect		Liquid	Liquid	Liquid
Color	Visual	Lt. Amber	Colorless	Clear-Lt. Amber
Viscosity (25°C)	Cps	1,300	100	553
Specific Gravity (25°C)	lbs./gal (g/cc)	9.92 (1.19)	7.92 (.95)	9.48 (1.14) Cured
Gel Time (180 g) at 77°F (25°C)	minutes			730

PROCESSING

After mixing according to the indicated ratio, carry out impregnation of the reinforcements. To ensure an optimal use and a good impregnation, please use material stored at a temperature above 20 ° C. Do not leave large masses of material (more than 1" thickness in mixing cup) to cure at room temperature or above to prevent an exotherm and possible smoke generation of the material.

CURE CONDITIONS

In order to avoid any risk of distortion or tooling shrinkage a precise curing cycle must be observed. Demolding takes place only after a 16 hour pre-curing at 50°C-60°C. Then the following thermal treatment (Post-cure) can be carried out : 2 hours at 120°C, 4 hours at 180°C (4 hours at 150°C optional – see property tables) with an increase and a decrease in temperature ramp rates of 20°C per hour between stages cured of up fully and then stepped down.

Neat Cured Properties Tested at 74°F (23°C)			
	Test Method	Unit(s)	Test Results
Glass Transition Temperature (Tg) *Cure #1 **Cure #2	ASTM E1545	°F (°C)	346 (174) 416 (213)
Hardness *Cure #1 **Cure #2	ASTM D-2240	Shore D	88 92
Flexural Strength *Cure #1 **Cure #2	ASTM D790	psi (MPa)	11,203 (77) 9,059 (63)
Flexural Modulus *Cure #1 **Cure #2	ASTM D790	psi (MPa)	420,904 (2904) 467,510 (3226)
Tensile Strength *Cure #1 **Cure #2	ASTM D638	psi (MPa)	5,287 (37) 3,572 (25)
Tensile Modulus *Cure #1 **Cure #2	ASTM D638	psi (MPa)	275,690 (1,902) 292,640 (2,019)
Tensile Elongation *Cure #1 **Cure #2	ASTM-D638	%	2.2 1.3

*1hr/50°C + 1hr/80°C + 2hr/120°C + 4hr/150°C cure

**1hr/50°C + 1hr/80°C + 2hr/120°C + 4hr/180°C cure

HANDLING PRECAUTIONS

Normal health and safety precautions should be observed when handling these products:

- Ensure good ventilation.
- Wear gloves, glasses and protective clothes.

For further information, please consult the Safety Data Sheets.

STORAGE CONDITIONS

- This product has a shelf life of 6 months for the resin as indicated by the expiration date on the container when stored in original unopened containers between 47°F – 77°F (8°C – 25°C), 9 months if stored below 47°F (8°C) and 12 months if stored below 0°F (-18°C). The product shelf life for the hardener is 24 months between 60°F (15°C) and 77°F (25°C). Any opened can must be tightly closed.
- It is recommended that opened containers be stored under an inert and/or dry gas cover (ex : Dry air, Nitrogen).

PACKAGING

Packaging information on request, please contact your local sales representative or find your local contact on www.sikaadvancedresins.us

LEGAL NOTICE

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

CONTACT

UNITED STATES

Sika Corporation

30800 Stephenson Highway
Madison Heights, Michigan 48071 – USA
Tel.: (+1) 248 588-2270
Fax: (+1) 248 577-0810
E-mail: axsonmh@axson.com
Website: www.sikaadvancedresins.us