

TECHNICAL DATA SHEET

TCC-5000A/5070B

POLYURETHANE CASTING SYSTEM 70 SHORE A HARDNESS

DESCRIPTION

TCC-5000A/5070B is a two-component urethane casting system designed to give a 70 Shore A hardness material with exceptional toughness. This casting system offers outstanding performance properties including high strength, low shrinkage and easy processing. Ultimate properties are reached after 7 days at room temperature or by being cured for 16-20 hours at room temperature, then post cured for a minimum of 6 hours at 160°F (71°C)

APPLICATIONS

- *Long Lasting Flexible Molds*
- *Industrial Wheels*
- *Belts / Pulleys / Casters*
- *Nesting Fixtures*
- *Static Welding Fixtures*
- *Metal Forming Pads*
- *Sound Dampening Pads*

PHYSICAL PROPERTIES

Handling Properties @ 77°F (25°C)		
	Units	Mixed System
Mix Ratio (parts by weight)		100A/50B
Mixed Color	Visual	Amber
Mixed Viscosity	Cps	1,000
Pot Life (150 gram mass)	Minutes	15-20

Typical Physical Properties @ 77°F (25°C)		
	Units	Test Results
Specific Gravity - (cured)	g/cc	1.09
Hardness Build - (150 gram mass)	Shore A	50 – 55
24 Hours		60 – 65
48 Hours		68 – 73
72 Hours		
Tensile Strength	psi (MPa)	2,000 (14)
Elongation	%	500
Linear Shrinkage	in/in	<0.001
Tear Strength - Split	pli	100
Tear Strength - Die "C" graves	pli	250

MIXING PROCEDURE

Use an accurate gram scale to properly weigh and proportion A/B components into a straight sided metal or plastic container for mixing. Paper or wax lined mixing containers can contain moisture and contaminate material. Next, use a metal or plastic mixing spatula to gently but thoroughly blend resin and hardener together. Once the urethane appears to be well mixed, pour into a second container and continue to mix for another two to three minutes. This procedure eliminates the possibility of any unmixed material being poured into the final cast. Vacuum degass mixture before casting to produce an air free part.

HANDLING PRECAUTIONS

Normal health and safety precautions should be observed when handling these products:

- Ensure good ventilation.
- Wear gloves, glasses and protective clothes.

For further information, please consult the Safety Data Sheets.

STORAGE CONDITIONS

- This product has a shelf life of 24 months for the resin and hardener as indicated by the expiration date on the container when stored in original unopened containers. Store closed containers at 65°F-85°F (18°C-29°). Partially used containers must be flushed with dry nitrogen and resealed. Materials are sensitive to moisture contamination.

PACKAGING

Packaging information on request, please contact your local sales representative or find your local contact on www.sikaadvancedresins.us

LEGAL NOTICE

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

CONTACT

UNITED STATES

Sika Corporation

30800 Stephenson Highway
Madison Heights, Michigan 48071 – USA
Tel.: (+1) 248 588-2270
Fax: (+1) 248 577-0810
E-mail: advanced.resins@us.sika.com
Website: www.sikaadvancedresins.us

TECHNICAL DATA SHEET
TCC-5000A/5070B
February 19, Version 01 /2021

BUILDING TRUST

