

TECHNICAL DATA SHEET

SC 390 NA

EPOXY MODELING PASTE MASTER MODELS – PLUGS – DIRECT TO MOLD

DESCRIPTION

Extrudable epoxy paste for models, tools, and plug production by extrusion process.

APPLICATIONS

- *Models*
- *Tools*
- *Plugs*

PROPERTIES

- *Very good surface aspect.*
- *Good behavior on vertical support up to 1.20 in. (30 mm)*
- *Separate resin and hardener colors aid in good mix indication*
- *High use temperature*
- *Low CTE with good dimensional stability*

PHYSICAL PROPERTIES

	Test Method	Test Result	Test Result	Test Result
Composition		Resin	Hardener	Mixed
Mix ratio by weight		100	100	100/100
Mix ratio by volume at 77° (25°C)		1	1	1/1
Aspect		Viscous paste	Viscous paste	Viscous paste
Color		Gray	White	Gray
Viscosity at 77°F (25°C) (Cps)	ASTM 2393	9,000,000	7,000,000	7,000,000
Density 77°F (25°C) (Lbs/gal)	ASTM D792	9.0	8.9	8.9
Specific Gravity at 77°F (25°C) (g/cm ³)	ASTM D792	1.08	1.08	1.08
Pot life at 77°F (25°C) on 500 g (min.)				140

MECHANICAL and THERMAL PROPERTIES at 74°F (23°C) ⁽¹⁾				
Property	Test Method	Units	Test Result	Test Result
Applied thickness			1.2 in. (30 mm)	0.6 in. (15 mm)
Glass transition temperature (Tg) 24 hrs at 77°F (25°C) +16 hours at 140°F (60°C) +16 hours at 176°F (80°C)	TMA ASTM E1545	°F (°C)	160 (71) 181 (83) 192 (89)	129 (54) 180 (82) 196 (91)
Coefficient of thermal expansion (CTE) 24 hrs at 77°F (25°C) +16 hours at 140°F (60°C) +16 hours at 176°F (80°C)	ISO 11359 : 1999	ppm/°F (°C)	33 (59) 29 (53) 31 (55)	34 (61) 33 (59) 32 (58)
Hardness 24 hrs at 77°F (25°C) +16 hours at 176°F (80°C)	ISO 868 : 2003	Shore D (D15)	73 (71) 75 (74)	69 (65) 75 (74)
MECHANICAL and THERMAL PROPERTIES at 74°F (23°C) ⁽¹⁾				
Heat deflection temperature (HDT)	ISO 75 : 2004	°F (°C)	172 (78)	
Tensile strength	ISO 527 : 1993	psi (MPa)	3,000 (21)	
Tensile modulus	ISO 527 : 1993	psi (MPa)	348,000 (2,400)	
Elongation	ISO 527 : 1993	%	2.2	
Flexural strength	ISO 178 : 2001	psi (MPa)	5,200 (36)	
Flexural modulus	ISO 178 : 2001	psi (MPa)	290,000 (2,000)	
Compressive strength	ISO 604 : 2002	psi (MPa)	5,200 (36)	

(1) Average values obtained on standard specimens cured 24 hours at 77°F (25°C) + 16 hours at 176°F (80°C)

PROCESSING


During extrusion, the dispensing nozzle must be maintained perpendicular to the surface on which the product is applied. Ensure overlap of ribbon.

CAUTION: Exotherm mostly depends on the type of machine and on the working parameters such as:

- Room temperature.
- Insulating property of frame.
- The mixture temperature (depending on the type of mixer: static or dynamic) and the speed of mixing and output.
- Applied thickness.

EXOTHERMIC PEAK AND HARDENING TIME *				
Thickness In. (mm)	Product temperature °F (°C)	Exothermic peak (minutes)	Exothermic peak °F (°C)	Workability (hours)
1.2 (30)	84 (29)	140	180 (82)	12
0.6 (15)	84 (29)	140	115 (46)	16

*Room temperature: 77°F (25°C); polystyrene support.



PROCESSING CONDITIONS

On vertical support, it is recommended to apply a thin coat of product with a spatula; this will help to reinforce the bonding on the support.

For ceiling application, we recommend a maximum thickness of 1.2 in. (30 mm).

A pre-cure of 16 hours at 104°F (40°C) is recommended before filling shrinkage relief gaps and rough machining. Final postcure temperature and duration are dependent on tool construction and size. Please see note below.

TOOL CONSTRUCTION

The overall stability of a tool is dependent on the size, construction materials, construction techniques, applied paste depth and temperature, and post cure time and temperature. Generally as the tool gets larger the need for increased rigidity of the tool and support structure and closer matching the coefficient of thermal expansion of the materials as well as reducing the maximum post cure temperature need to be evaluated for tool durability. In many instances, equivalent thermal performance can be achieved at a lower post cure temperature for a longer period of time. Please consult Axson for additional information.

HANDLING PRECAUTIONS

Normal health and safety precautions should be observed when handling these products:

- Ensure good ventilation.
- Wear gloves, glasses and protective clothes.

For further information, please consult the Safety Data Sheets.

STORAGE CONDITIONS

Shelf life is 12 months of the manufacturing date. Expiration date indicated on the packaging.

PACKAGING

Packaging information on request, please contact your local sales representative or find your local contact on www.sikaadvancedresins.us

LEGAL NOTICE

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

CONTACT

UNITED STATES

Sika Corporation

30800 Stephenson Highway
Madison Heights, Michigan 48071 – USA
Tel.: (+1) 248 588-2270
Fax: (+1) 248 577-0810
E-mail: advanced.resins@us.sika.com
Website: www.sikaadvancedresins.us

TECHNICAL DATA SHEET
SC 390 NA
February 19, Version 01 /2021