

## PRODUCT DATA SHEET

# SikaTile®-880 Sanded Caulk

### PREMIUM, ONE-PART, SILICONIZED ACRYLIC-BASED CAULKING COMPOUND

#### PRODUCT DESCRIPTION

SikaTile®-880 Sanded Caulk is a premium-grade, one-part, siliconized, acrylic-based caulking compound that is easy-to-use, easy-to-clean, and mold and mildew resistant. SikaTile®-880 Sanded Caulk is available in an unsanded version and color-coordinated to match all SikaTile Grout colors.

#### USES

- SikaTile®-880 Sanded Caulk is used to fill joints up to 1/4" (6 mm) in width between panels, cracks, walls, around tubs, showers, sinks, countertops, etc.
- For filling joints where tile abuts different surfaces or planes
- For interior and exterior use in both residential and commercial applications

#### SUITABLE TILE TYPES

- Brick and thin brick
- Cement-based precast terrazzo
- Impervious porcelain and glass tile
- Natural stone tile, granite, and slate
- Vitreous, semi-vitreous or non-vitreous tile:
  - Ceramic, mosaic, quarry, cement body tile

#### CHARACTERISTICS / ADVANTAGES

- For filling joints where tile abuts different surfaces or planes
- Formulated to match all SikaTile® grout colors
- Mold and mildew resistant
- Available in sanded and unsanded
- One-component ready to use
- Excellent adhesion, bonds to many substrates without priming
- Flexible filler between horizontal and vertical surfaces to prevent cracked tile due to expansion
- Fast Curing
- Mold and mildew resistant

#### ENVIRONMENTAL INFORMATION

Sika® is committed to environmental responsibility in both products produced and in manufacturing practices. Complete the LEED Product Data Request Form [SikaTile.com](http://SikaTile.com) for detailed information based on project location. The use of this product can contribute towards LEED® v4.1 certification:

- IEQ Credit 4.1, Low-Emitting Materials – Adhesives & Sealants
- IEQ Credit 4.3, Low-Emitting Materials – Flooring Systems

#### APPROVALS / STANDARDS

- Conforms to the requirements for plastic joint sealants, ASTM-C920. Meets ASTM C-834 for low-movement sealant.
- Resilient Floor Covering Institute - (RFCI) Recommended Work Practices for Removal of Resilient Floor Coverings

- Tile Council of North America (TCNA) - TCNA Handbook for Ceramic Tile Installation, TCNA EJ171 Movement Joint Guidelines.

## PRODUCT INFORMATION

<b>Chemical Base</b>	Siliconized acrylic latex resins with fine fillers and colored pigments
<b>Packaging</b>	10.3 oz. (304.6 ml) tube; 6 per carton
<b>Color</b>	Available in 18 colors; Refer to SikaTile® grout kit or color card for actual colors
<b>Shelf Life</b>	24 months from date of production when stored in original, sealed package
<b>Storage Conditions</b>	Store in undamaged, original, sealed package, in dry conditions at 73° F (23° C)

## APPLICATION INFORMATION

Coverage	Joint Size	Approximate Coverage*
	1/16" (1.5 mm)	48 lin. ft. (14.6 m)
	1/8" (3 mm)	25 lin. ft. (7.6 m)
	3/16" (4.5 mm)	17 lin. ft. (5.2 m)
	1/4" (6 mm)	13 lin. ft. (4.0 m)

\*Coverage shown is for estimating purposes only. Actual coverage may vary due to installation techniques, actual tile types, sizes, and waste used on the job.

## BASIS OF PRODUCT DATA

Property	Test Method	Typical Results
Open Time	-	10 - 20 Minutes
Set Time	-	48 Hours
Full Cure	-	14 days
Paintable	-	Yes, after a 7 day cure
Extrudability	ASTM C834, ASTM C731	≥ 2 g/s
Shrinkage	ASTM C834, ASTM C1261	< 30%
Slump	ASTM C834, ASTM D2202	≤ 4 mm
VOC Emissions	Rule 1168	0 - 2.5 g/L
Odor	-	Mild

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## AVAILABILITY/WARRANTY

### CLEANING:

Water is all that is needed to remove excess SikaTile®-880 Sanded Caulk while it is still wet. Unused caulk should be capped and stored in a cool, dry place and

used within one year.

### MOVEMENT JOINTS:

All expansion, control, construction, cold, saw-cut, isolation, contraction, and seismic joints in the structure should continue through the tilework, including such joints at vertical surfaces, as specified per TCNA Method EJ171 or TTMAC Specification Guide 09 30 00, Detail 301MJ.

### PROTECTION:

Do not disturb caulk or walk over installed tiles for at least 24 hours after setting. Protect from water exposure until fully cured for at least 72 hours. Allow 7 days of drying time before painting.

### FINAL CLEAN UP:

Clean hands and tools with soap and water. Clean tools and tile with water before the material dries. Clean up any misapplied sealant with a damp cloth or sponge. The cured sealant may be carefully cut away with a sharp-edged tool. Dispose of empty cartridges and saturated sponges according to state and local regulations. The unused portion of SikaTile®-880 Sanded Caulk should be capped and stored in a cool dry place.

## ENVIRONMENTAL, HEALTH AND SAFETY

## APPLICATION INSTRUCTIONS

## SUBSTRATE PREPARATION

For best results, the temperature of the substrate or tile must be between 40°F and 95°F (4°C and 35°C) while applying caulk. For proper curing, maintain this temperature range for 72 hours after application. Before applying caulk, make sure that the tiles or stones are firmly set and that the adhesive or mortar is completely dry. Joints must be clean and free of standing water, dust, dirt, and foreign matter. Clean the tile or stone surface to remove dust, dirt, mortar, adhesive, and other contaminants that may cause discoloration.

## APPLICATION METHOD / TOOLS

Read all installation instructions before installation. This product may contain high levels of color pigment and may stain some porous materials such as wallpaper, wood, and walls. Use painter's tape or shield these areas for protection. Test in an inconspicuous area to determine if staining will occur. Caulking may be done either before or after grouting. Insert the tube into a standard caulking gun and cut off the tip of the tube at a slant to the desired size. Apply caulk into the opening using a continuous bead at a 45-degree angle. Smooth with a wet putty knife, caulking tool, or gloved finger. Excess caulk should be removed with a damp cloth before the caulk skins over. When applied in areas exposed to moisture allow the caulking to cure a minimum of 24 hours at 70° F (21° C) prior to putting the area into use. Complete cure is achieved in 48 to 72 hours depending on ambient temperature and humidity.

## OTHER RESTRICTIONS

See Legal Disclaimer.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its

subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

### Sika Corporation

201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)

### Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



### Product Data Sheet

SikaTile®-880 Sanded Caulk  
August 2021, Version 01.01  
02051404000000125

SikaTile-880SandedCaulk-en-US-(08-2021)-1-1.pdf

